

**Glass in building - Structural sealant glazing - Part 2:
Assembly rules**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13022-2:2014 sisaldab Euroopa standardi EN 13022-2:2014 inglisekeelset teksti.	This Estonian standard EVS-EN 13022-2:2014 consists of the English text of the European standard EN 13022-2:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 04.06.2014.	Date of Availability of the European standard is 04.06.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 81.040.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Glass in building - Structural sealant glazing - Part 2: Assembly rules

Verre dans la construction - Système de vitrage extérieur collé (VEC) - Partie 2: Règles d'assemblage

Glas im Bauwesen - Geklebte Verglasungen - Teil 2: Verglasungsvorschriften für Structural-Sealant-Glazing (SSG-) Glaskonstruktionen

This European Standard was approved by CEN on 9 February 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Requirements	5
5 Assembling/bonding	6
6 Assembling/bonding control	7
6.1 Assembling/bonding control requirements	7
6.1.1 General	7
6.1.2 Organization	7
6.1.3 Assembling – quality system	7
6.2 Inspection and testing tables for assembling glass elements into or onto framework with structural sealant	8
Annex A (normative) Dynamic tensile and peel test on structural sealant	14
A.1 Purpose	14
A.1.1 General	14
A.1.2 Project Test	14
A.1.3 Convenience test	14
A.1.4 Factory production control test	14
A.2 Test specimens	14
A.2.1 Tensile test	14
A.2.2 Peel test	14
A.3 Conditioning of test specimens	14
A.4 Test procedure	15
A.4.1 In the case of tensile test	15
A.4.2 In the case of peel test	15
A.5 Observation	15
A.6 Report	15
Annex B (informative) Design guidance	17
B.1 Characteristics	17
B.2 Characteristic details	18
B.2.1 General	18
B.2.2 Safety in the case of fire – reaction to fire	18
B.2.3 Health – release of dangerous substances	19
B.2.4 Safety in use	19
B.2.5 Structural seal dimensions	19
B.3 Initial assessment of the design	26
B.4 Assembling details	27
Annex C (normative) Adhesion tests in assembling/bonding control	28
C.1 General	28
C.2 Purpose	28

C.3	Peel test – Method 1	28
C.3.1	Test specimens	28
C.3.2	Curing time	29
C.3.3	Test procedure	29
C.3.4	Observation	29
C.4	Static tensile test – Method 2	29
C.4.1	Test specimens	29
C.4.2	Curing time	29
C.4.3	Test procedure	30
C.4.4	Observation	30
C.5	Dynamic tensile test	30
C.5.1	Test specimens	30
C.5.2	Curing time	30
C.5.3	Test procedure	30
C.5.4	Observation	30
C.6	Report	30
Annex D	(informative) Two-component sealant: Check on the thoroughness of mixing and air inclusions	32
D.1	General	32
D.2	Purpose	32
D.3	Test specimen	32
D.4	Test procedure	32
D.5	Report	32
Annex E	(informative) Sealants, hardness measurements	34
E.1	General	34
E.2	Purpose	34
E.3	Definitions	34
E.3.1	Curing time	34
E.3.2	Free surface	34
E.4	Instruments	34
E.5	Calibration	34
E.6	Test specimens	35
E.7	Test procedure	35
E.8	Report	35
Annex F	(informative) Provisions for voluntary involvement of third party(ies)	37
F.1	General	37
F.2	Voluntary tasks for third parties	37
F.3	Marking and labelling	37
	Bibliography	38

Foreword

This document (EN 13022-2:2014) has been prepared by Technical Committee CEN/TC 129 "Glass in building", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014 and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13022-2:2006+A1:2010.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This part of EN 13022 is one of a series of interrelated standard parts dealing with:

- glass products for structural sealant glazing systems;
- installation of glass products in a structural manner on building façades;
- UV-resistant and structural sealant for use in structural sealant glazing.

The interrelated parts are:

- EN 13022-1: *Glass in building — Structural sealant glazing — Part 1: Glass products for structural sealant glazing systems for supported and unsupported monolithic and multiple glazing*
- EN 13022-2: *Glass in building — Structural sealant glazing — Part 2: Assembly rules*
- EN 15434: *Glass in building — Product standard for structural and/or ultra-violet resistant sealant (for use with structural sealant glazing and/or insulating glass units with exposed seals)*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard deals with the assembling and bonding of glass elements in a frame, window, door or curtain walling construction, or directly into the building by means of structural bonding of the glass element into or onto framework or directly into the building.

It gives information to the assembler to enable him to organize his work and comply with requirements regarding quality control.

Structural sealant glazing can be incorporated into the façades (curtain walls, doors and windows) or roofs as follows:

- either vertically; or
- up to 7° from the horizontal, i.e. 83° from the vertical.

This European Standard only deals with the bonding to glass surfaces, i.e. coated or uncoated or enamelled, and metallic surfaces, i.e. aluminium (anodised or coated), stainless steel, as considered in G.2 of EN 15434:2006+A1:2010.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13022-1:2014, *Glass in building — Structural sealant glazing — Part 1: Glass products for structural sealant glazing systems for supported and unsupported monolithic and multiple glazing*

EN 15434:2006+A1:2010, *Glass in building — Product standard for structural and/or ultra-violet resistant sealant (for use with structural sealant glazing and/or insulating glass units with exposed seals)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13022-1:2014, EN 15434:2006+A1:2010 and the following apply.

3.1

structural bonding

assembling of glass elements into or onto window, door or curtain walling framework by means of a structural seal

3.2

structural sealant

elastic sealant used for making a structural seal

4 Requirements

The assembling of the glass elements into or onto the window, door or curtain-walling framework or directly in the building or construction shall take place under the following controlled environmental conditions:

- temperature of the surface of the frame and of the glass and of the near environment shall be not less than 10 °C and not more than 35 °C;
- for a given temperature, the RH value shall be at least 5 % below the value corresponding to the dew point of the support to which the seal is being applied;