

**Paints and varnishes - Bend test (cylindrical mandrel)  
(ISO 1519:2011)**

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 1519:2011 sisaldab Euroopa standardi EN ISO 1519:2011 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.01.2011 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.01.2011.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 1519:2011 consists of the English text of the European standard EN ISO 1519:2011.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.01.2011 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.01.2011.

The standard is available from Estonian standardisation organisation.

ICS 87.040

area, coatings, cylindrical shape, drying, drying stages, evaluations, mandrel bending test, materials testing, methods, painting, paints, piercers, sampling, sampling methods, surfaces, testing, tests, varnishes

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

English Version

Paints and varnishes - Bend test (cylindrical mandrel) (ISO  
1519:2011)

Peintures et vernis - Essai de pliage sur mandrin  
cylindrique (ISO 1519:2011)

Beschichtungsstoffe - Dornbiegeversuch (zylindrischer  
Dorn) (ISO 1519:2011)

This European Standard was approved by CEN on 8 January 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Page

Foreword .....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Principle .....	1
4 Apparatus.....	2
5 Sampling .....	5
6 Test panels.....	5
7 Procedure .....	6
8 Expression of results .....	7
9 Precision .....	7
10 Test report.....	7
Bibliography.....	9

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1519 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 1519:2002), which has been technically revised. The main changes are:

- a) A principle clause has been added.
- b) The requirement to carry out the test at a controlled relative humidity has been deleted (although the relative humidity is measured and recorded during the test). A maximum limit for the time between conditioning and testing has therefore been added.
- c) The supplementary test conditions (formerly Annex A) have been integrated in the test report.
- d) Information has been given on the precision of the method.

## Introduction

This International Standard is one of six which specify empirical test procedures for assessing the resistance of coatings of paints, varnishes and related products to cracking and/or detachment from the substrate under different conditions of deformation.

The other five documents are:

- ISO 1520, *Paints and varnishes — Cupping test*
- ISO 6272-1, *Paints and varnishes — Rapid-deformation (impact resistance) tests — Part 1: Falling-weight test, large-area indenter*
- ISO 6272-2, *Paints and varnishes — Rapid-deformation (impact resistance) tests — Part 2: Falling-weight test, small-area indenter*
- ISO 6860, *Paints and varnishes — Bend test (conical mandrel)*
- ISO 17132, *Paints and varnishes — T-bend test*

The method chosen will depend on the property to be measured and on agreement between the interested parties. In principle, all these tests differ from each other technically and in their accuracy.

# Paints and varnishes — Bend test (cylindrical mandrel)

## 1 Scope

This International Standard specifies an empirical test procedure for assessing the resistance of a coating of paint, varnish or related product to cracking and/or detachment from a metal or plastics substrate when subjected to bending round a cylindrical mandrel under standard conditions.

For a multi-coat system, each coat can be tested separately or the complete system can be tested.

The method specified can be carried out

- either as a “pass/fail” test, by carrying out the test with a single specified size of mandrel, to assess compliance with a particular requirement;
- or by repeating the procedure using successively smaller mandrels to determine the diameter of the first mandrel over which the coating cracks and/or becomes detached from the substrate.

Two types of apparatus are specified, type 1 being appropriate for use on test panels of thickness up to 0,3 mm, and type 2 for use on test panels of thickness up to 1,0 mm. Both types of apparatus have been found to give similar results with the same coating, but normally only one will be used for testing a given product.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

## 3 Principle

A coated test panel is clamped in the test apparatus and then bent round a cylindrical mandrel. The bent panel is examined to see if the coating has been cracked when using the agreed or specified size of mandrel (“pass/fail test”) or, alternatively, the diameter of the first (smallest) mandrel over which the coating cracks and/or becomes detached from the substrate is determined.