

Müürimörtide katsemeetodid. Osa 2: Mördiproovide võtmine ja katsemörtide valmistamine

Methods of test for mortar for masonry - Part 2: Bulk sampling of mortars and preparation of test mortars

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 1015-2:2004 sisaldab Euroopa standardi EN 1015-2:1998 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 18.06.2001 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 21.10.1998.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 1015-2:2004 consists of the English text of the European standard EN 1015-2:1998.

This standard is ratified with the order of Estonian Centre for Standardisation dated 18.06.2001 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 21.10.1998.

The standard is available from Estonian standardisation organisation.

ICS 91.100.10

Võtmesõnad: kipskrohv, lubi, mördid, müüritööd, proovide võtmine, sertifitseerimine, tsement

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

ICS 91.100.10

Descriptors: Building materials, mortar, masonry, sampling.

English version

Methods of test for mortar for masonry

Part 2: Bulk sampling of mortars and preparation of test mortars

Méthodes d'essai des mortiers pour
maçonnerie – Partie 2: Echantillonnage
global des mortiers et préparation des
mortiers d'essai

Prüfverfahren für Mörtel für Mauer-
werk – Teil 2: Probenahme von
Mörteln und Herstellung von Prüf-
mörteln

This European Standard was approved by CEN on 1998-09-04.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Contents	Page
Foreword	2
1 Scope.....	3
2 Normative references.....	3
3 Definitions	3
4 Minimum bulk test sample size.....	3
5 Preparation of the bulk test sample and individual test samples.....	4
6 Preparation of test mortars from dry constituents and water or prebatched mixes and binders	6

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 125 "Masonry", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 1999, and conflicting national standards shall be withdrawn at the latest by September 2000.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association and includes the performance requirements referred to in the Eurocode for masonry Structures.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies methods for taking a bulk sample of fresh mortar, and the preparation of a bulk test sample from this. It also specifies a procedure for producing test mortars from dry constituents and water.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 196-1	Method of testing cement - Part 1: Determination of strength
prEN 998-1	Specification for mortar for masonry - Part 1: Rendering and plastering mortar with inorganic binding agents
prEN 998-2	Specification for mortar for masonry - Part 2 : Masonry mortar
prEN 1015-3	Methods of test for mortar for masonry - Part 3 : Determination of consistence of fresh mortar (by flow table)

3 Definitions

For the purposes of this standard the following definitions apply.

3.1 lot: Quantity of mortar produced under conditions presumed uniform. After specified tests this quantity is regarded as a whole "complying" or "not complying" with the specifications.

3.2 increment: Quantity of mortar taken in a single operation of the sampling equipment used.

3.3 spot sample: A sample taken at the same time and from one and the same place. It can be obtained by taking increments one after another.

3.4 bulk sample: The aggregation of sample increments meant to represent the lot sampled.

3.5 bulk test sample: The reduced sample taken from the bulk sample which is used for the testing purposes of this standard.

4 Minimum bulk test sample size

The minimum bulk test sample size shall be 10 kg.