

Steel rod, bars and wire for cold heading and cold extrusion - Part 4: Technical delivery conditions for steels for quenching and tempering

Steel rod, bars and wire for cold heading and cold extrusion - Part 4: Technical delivery conditions for steels for quenching and tempering

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

| | |
|--|---|
| <p>Käesolev Eesti standard EVS-EN 10263-4:2001 sisaldab Euroopa standardi EN 10263-4:2001 + AC:2002 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 19.12.2001 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p> | <p>This Estonian standard EVS-EN 10263-4:2001 consists of the English text of the European standard EN 10263-4:2001 + AC:2002.</p> <p>This document is endorsed on 19.12.2001 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p> |
|--|---|

| | |
|---|---|
| <p>Käsitlusala:</p> <p>This part 4 of EN 10263 is applicable to round rod and round bars and wire with a diameter up to and including 100 mm, of non-alloy and alloy steel, intended for cold heading and cold extrusion and subsequent quenching and tempering.</p> | <p>Scope:</p> <p>This part 4 of EN 10263 is applicable to round rod and round bars and wire with a diameter up to and including 100 mm, of non-alloy and alloy steel, intended for cold heading and cold extrusion and subsequent quenching and tempering.</p> |
|---|---|

ICS 77.140.60, 77.140.65

Võtmesõnad: acceptance testing, extrusions, measurement, metal bars, objection, ph, production, properties, specification (approval), specifications, steels, testing, tolerances, tolerances (measurement), unalloyed, unalloyed steels, wire rods, wires

Hinnagrupp J

ICS 77.140.60; 77.140.65

English version

**Steel rod, bars and wire for cold heading and cold extrusion -
Part 4: Technical delivery conditions for steels for quenching and
tempering**

Barres, fil machine et fils en acier pour transformation à
froid et extrusion à froid - Partie 4: Conditions techniques
de livraison des aciers pour trempe et revenu

Walzdraht, Stäbe und Draht aus Kaltstauch- und
Kaltfließpreßstählen - Teil 4: Technische Lieferbedingungen
für Vergütungsstähle

This European Standard was approved by CEN on 19 April 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

CONTENTS

| | Page |
|---|----------|
| FOREWORD | 3 |
| 1 Scope | 4 |
| 2 Normative references | 4 |
| 3 Terms and definitions | 4 |
| 4 Classification and designation | 4 |
| 4.1 Classification | 4 |
| 4.2 Designation | 4 |
| 5 Production Process | 4 |
| 5.1 Steelmaking process | 4 |
| 5.2 Deoxidation | 4 |
| 6 Requirements | 5 |
| 6.1 Delivery conditions | 5 |
| 6.2 Chemical composition | 5 |
| 6.3 Mechanical properties | 5 |
| 6.4 Hardenability | 5 |
| 6.5 Surface requirements | 5 |
| 6.6 Supplementary or special requirements | 5 |

FOREWORD

This European Standard has been prepared by Technical Committee ECISS/TC 15 "Wire-rod - Qualities, dimensions, tolerances and specific tests", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2001, and conflicting national standards shall be withdrawn at the latest by December 2001.

This European Standard EN 10263 is subdivided as follows:

- Part 1: General technical delivery conditions;
- Part 2: Technical delivery conditions for steels not intended for heat treatment after cold working;
- Part 3: Technical delivery conditions for case hardening steels;
- Part 4: Technical delivery conditions for steels for quenching and tempering
- Part 5: Technical delivery conditions for stainless steels.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

1.1 This Part of EN 10263 is applicable to round rod and round bars and wire with a diameter up to and including 100 mm, of non-alloy and alloy steel, intended for cold heading and cold extrusion and subsequent quenching and tempering

1.2 This Part of EN 10263 is complemented by EN 10263-1.

2 Normative references

This European Standard incorporates by date or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For date references, subsequent amendments to or revisions of, any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

| | |
|------------|--|
| EN 10020 | Definitions and classification of grades of steel. |
| EN 10263-1 | Steel rod, bars and wire for cold heading and cold extrusion - Part 1: General technical delivery conditions |

3 Terms and definitions

For the purposes of this standard the definitions in EN 10263-1 and the following apply.

3.1

Quenched and tempered steels

For the purpose of this European Standard quenched and tempered steels are engineering steels which, because of their chemical composition are suitable for hardening and in the quenched and tempered condition have good toughness at a given tensile strength

4 Classification and designation

4.1 Classification

All steels covered by this Part of EN 10263 are special steels according to EN 10020.

Steel grades from C35EC to C45RC as quoted in table 2 are non-alloy steels and all others are alloy steels according to EN 10020.

4.2 Designation

See EN 10263-1:2001.

5 Production Process

5.1 Steelmaking process

See EN 10263-1:2001

5.2 Deoxidation

All steels shall be killed with aluminium and/or silicon. Aluminium and/or silicon may be replaced by another element having a similar effect.