

Unplasticized poly(vinyl chloride) (PVC-U) profiles for the fabrication of windows and doors - Classification, requirements and test methods - Part 1: Non-coated PVC-U profiles with light coloured surfaces

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12608-1:2016 sisaldab Euroopa standardi EN 12608-1:2016 ingliskeelset teksti.	This Estonian standard EVS-EN 12608-1:2016 consists of the English text of the European standard EN 12608-1:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 09.03.2016.	Date of Availability of the European standard is 09.03.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.140.99, 91.060.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Unplasticized poly(vinyl chloride) (PVC-U) profiles for the
fabrication of windows and doors - Classification,
requirements and test methods - Part 1: Non-coated PVC-U
profiles with light coloured surfaces

Profils de poly(chlorure de vinyle) non plastifié (PVC-U) pour la fabrication des fenêtres et des portes - Classification, exigences et méthodes d'essai - Partie 1: Profils en PVC-U non revêtus avec des faces de teinte claire

Profile aus weichmacherfreiem Polyvinylchlorid (PVC-U) zur Herstellung von Fenstern und Türen - Klassifizierung, Anforderungen und Prüfverfahren - Teil 1: Nicht beschichtete PVC-U Profile mit hellen Oberflächen

This European Standard was approved by CEN on 15 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	4
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
3.1 General.....	7
3.2 Profile definitions.....	7
3.3 Geometrical definitions	8
3.4 Material definitions.....	9
4 Classifications.....	10
4.1 General.....	10
4.2 Classification of climatic zones.....	10
4.3 Classification of main profiles according to the resistance to impact by falling mass.....	11
4.4 Classification of main profiles according to the wall thickness of the external walls.....	11
5 Requirements	13
5.1 Material.....	13
5.1.1 UV resistant virgin material	13
5.1.2 Non-UV resistant virgin material	13
5.1.3 Reprocessed, recycled materials and non-UV resistant virgin materials	13
5.2 Appearance.....	14
5.3 Dimensions and tolerances	14
5.3.1 General.....	14
5.3.2 Nominal shape.....	14
5.3.3 Wall thickness of main profiles.....	14
5.3.4 Tolerances on other dimensions.....	15
5.3.5 Deviation from straightness of the main profiles.....	15
5.4 Linear weight of the main profiles.....	15
5.5 Heat reversion.....	15
5.5.1 Main profile.....	15
5.5.2 Auxiliary profiles.....	15
5.6 Resistance to impact of main profiles by falling mass.....	16
5.7 Behaviour after heating at 150 °C	16
5.8 Charpy impact resistance of main profile	16
5.9 Resistance to weathering	16
5.9.1 Exposure procedure.....	16
5.9.2 Impact strength after artificial weathering of main profiles	17
5.9.3 Colour fastness.....	17
5.10 Strength of welded corners and T-joints of main profiles.....	17
5.10.1 Test method	17
5.10.2 Tensile bending test.....	17
5.10.3 Compression bending test	17
6 Test methods	17
6.1 Determination of the appearance.....	17
6.2 Determination of dimensions.....	18
6.2.1 Measuring devices	18

6.2.2	Test specimen	18
6.2.3	Conditioning	18
6.2.4	Procedure	18
6.3	Determination of the linear weight of the profile.....	18
6.3.1	Apparatus	18
6.3.2	Test specimen	18
6.3.3	Conditioning	18
6.3.4	Procedure	18
6.4	Determination of the thickness of a coextruded layer.....	19
6.5	Determination of colorimetric co-ordinates	19
6.6	Permissible tolerances on standard colours	19
7	Marking	19
7.1	Main profiles.....	19
7.2	Auxiliary profiles	20
Annex A	(normative) Material characteristics, preparation of samples and requirements	21
A.1	General	21
A.2	Test specimens	21
A.3	Preparation of pressed plates	21
A.4	Material characteristics	21
A.4.1	Vicat softening temperature.....	21
A.4.2	Flexural modulus of elasticity	22
A.4.3	Tensile impact strength.....	22
A.5	Test report	22
Annex B	(normative) Calculation method for the determination of the radiant exposure and exposure time to be used for artificial weathering.....	23
B.1	General	23
B.2	Calculation.....	23

European foreword

This document (EN 12608-1:2016) has been prepared by Technical Committee CEN/TC 33 “Doors, windows, shutters, building hardware and curtain walling”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by March 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12608:2003.

The major modifications to the previous edition are:

- Change in structure of definitions (general, profile, geometrical and material);
- Review of definitions of own reprocessed (previously reprocessable) material (3.4.5) and external reprocessed (previously reprocessable) material (3.4.6);
- Including a new material (non-UV resistant virgin material);
- Review of Table 1, which defines the classification of climatic zones in Europe; (correction of a mistake in EN12608:2003);
- Addition of a class (no performance determined) for the classification of main profiles according to the resistance to impact by falling mass (Table 2);
- Complete review of 5.1, giving the requirements for materials, establishing the distinction between UV resistant virgin material (5.1.1), non UV-resistant virgin material (5.1.2) and reprocessed (previously reprocessable), recycled (previously recyclable) materials and non-UV resistant virgin materials (5.1.3) with the addition of Table 4 which defines the uses allowed according to the type of material);
- Review of the test of Charpy impact resistance of main profiles (5.8); Introduction of dependence on classes of wall thickness;
- Review of the methods to determine the colorimetric co-ordinates (6.5);
- Addition of new subclause 6.4 for the determination of the thickness of a co-extruded layer;
- Addition of a requirement for individual values for the Vicat softening temperature (A.4.1);
- Addition of a requirement for individual values for the flexural modulus of elasticity (A.4.2);
- Addition of a requirement for individual values for the tensile impact strength (A.4.3);
- Deletion of the Charpy impact resistance from Annex A (material characteristics);
- Editorial review of the whole document and updating of normative references.

EN 12608, *Unplasticized poly(vinyl chloride) (PVC-U) profiles for the fabrication of windows and doors - Classification, requirements and test methods* consists of the following parts:

- *Part 1: Non-coated PVC-U profiles with light coloured surfaces*
- *Parts 2: PVC-U profiles with laminated foils* (in preparation)
- *Parts 3: PVC-U profiles with coextruded coloured top-layer* (in preparation)
- *Parts 4: PVC-U profiles with lacquered-coating* (in preparation)

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the classifications, requirements and test methods for non-coated unplasticized poly(vinyl chloride) (PVC-U) profiles with light coloured surfaces intended to be used for the fabrication of windows and doors.

It is applicable to PVC-U profiles with the colorimetric co-ordinates measured on the visible surfaces, as follows:

- $L^* \geq 82$ (chromaticity co-ordinate $Y \geq 60$),
- $-2,5 \leq a^* \leq 5$,
- $-5 \leq b^* \leq 15$.

NOTE 1 For editorial reasons in this document the term "window" is used for window/door.

NOTE 2 Profiles made from PVC-U materials with reinforcements (e.g. glass fibres) are not part of this scope.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 477, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Determination of the resistance to impact of main profiles by falling mass*

EN 478, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Appearance after exposure at 150 °C - Test method*

EN 479, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Determination of heat reversion*

EN 513, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Determination of the resistance to artificial weathering*

EN 514, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Determination of the strength of welded corners and T-joints*

EN ISO 105-A01:2010, *Textiles - Tests for colour fastness - Part A01: General principles of testing (ISO 105-A01:2010)*

EN ISO 178, *Plastics - Determination of flexural properties (ISO 178)*

EN ISO 179-1, *Plastics - Determination of Charpy impact properties - Part 1: Non-instrumented impact test (ISO 179-1)*

EN ISO 306, *Plastics - Thermoplastic materials - Determination of Vicat softening temperature (VST) (ISO 306)*

EN ISO 1163-2:1999, *Plastics - Unplasticized poly(vinyl chloride) (PVC-U) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 1163-2:1995)*

EN ISO 8256, *Plastics - Determination of tensile-impact strength (ISO 8256)*

EN ISO 11664-1, *Colorimetry - Part 1: CIE standard colorimetric observers (ISO 11664-1)*

EN ISO 11664-2, *Colorimetry - Part 2: CIE standard illuminants (ISO 11664-2)*

EN ISO 11664-4, *Colorimetry - Part 4: CIE 1976 L*a*b* Colour space (ISO 11664-4)*

EN 20105-A02, *Textiles - Tests for colour fastness - Part A02: Grey scale for assessing change in colour (ISO 105-A02)*

ISO 18314-1, *Analytical colorimetry — Part 1: Practical colour measurement*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 General

3.1.1

durability

ability of a profile to maintain satisfactory properties in a window over an estimated working life which is at least the economically reasonable working life of the window installed in a building (works)

Note 1 to entry: The indications given on the working life of a product cannot be interpreted as a guarantee given by the producer, but are regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3.2 Profile definitions

3.2.1

profile

product produced by extrusion

3.2.2

non-coated profile

profile without any surface treatment and without non-PVC-U coextruded layer(s)

EXAMPLE Profiles without laminated foils or painted surfaces.

3.2.3

main profile

profile, which defines the structure of the window

3.2.4

auxiliary profile

profile intended to be used for the fabrication of a window which is not a main profile

Note 1 to entry: Main and auxiliary profiles can be different according to the window construction techniques in the individual countries.

3.2.5

external wall (of a main profile)

wall of a main profile corresponding to its sight and non-sight surfaces