

Plastics - Methods of test for the determination of the effects of immersion in liquid chemicals

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 175:2010 sisaldab Euroopa standardi EN ISO 175:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.11.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.10.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 175:2010 consists of the English text of the European standard EN ISO 175:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.11.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.10.2010.

The standard is available from Estonian standardisation organisation.

ICS 83.080.01

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

English Version

Plastics - Methods of test for the determination of the effects of
immersion in liquid chemicals (ISO 175:2010)

Plastiques - Méthodes d'essai pour la détermination des
effets de l'immersion dans des produits chimiques liquides
(ISO 175:2010)

Kunststoffe - Prüfverfahren zur Bestimmung des Verhaltens
gegen flüssige Chemikalien (ISO 175:2010)

This European Standard was approved by CEN on 14 October 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 175:2010) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2011, and conflicting national standards shall be withdrawn at the latest by April 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 175:2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 175:2010 has been approved by CEN as a EN ISO 175:2010 without any modification.

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope.....	1
2 Normative references	1
3 Principle	2
4 General requirements and procedure	2
4.1 Test liquids.....	2
4.2 Test conditions	2
4.3 Immersion time	3
4.4 Test specimens.....	3
4.5 Conditioning	4
4.6 Procedure	4
4.7 Expression of results	5
5 Determination of changes in mass, dimensions and appearance	6
5.1 General	6
5.2 Apparatus	6
5.3 Test specimens.....	7
5.4 Determination of changes in mass.....	8
5.5 Determination of changes in dimensions.....	10
5.6 Determination of changes in colour or other appearance attributes.....	12
6 Determination of changes in other physical properties	13
6.1 General	13
6.2 Apparatus	13
6.3 Test specimens.....	13
6.4 Procedure	13
6.5 Calculation and expression of results	14
7 Precision	14
8 Test report.....	15
Annex A (normative) Types of test liquid.....	16
Annex B (informative) Notes on the absorption of moisture by plastic specimens in equilibrium with a conditioning atmosphere	19
Bibliography.....	20

Introduction

Because of their varied applications, plastics are frequently brought into contact with liquids such as chemical products, motor fuels, lubricants, etc., and, possibly, with their vapours.

Under the action of a liquid, a plastic material may be subjected to several phenomena which may occur simultaneously. On the one hand, absorption of liquid and extraction of constituents soluble in the liquid may occur. On the other hand, a chemical reaction, often resulting in a significant change in the properties of the plastic, may occur. The equilibrium swelling ratio for a crosslinked polymer in a liquid that is a solvent for the same but non-crosslinked polymer is a measure of the degree of crosslinking.

The behaviour of plastics in the presence of liquids can be determined only under arbitrarily fixed conditions aimed at making comparisons between different materials. The choice of test conditions (nature of the liquid, immersion temperature and immersion time), as well as the choice of the properties in which changes are to be measured, depends on the eventual application of the plastic under test.

It is not possible, however, to establish any direct correlation between the experimental results and the behaviour of the plastic in service. These tests do, nevertheless, permit a comparison to be made of the behaviour of different plastic materials under specified conditions, thus allowing an initial evaluation of their behaviour in relation to certain groups of liquids.

NOTE In view of its special importance, the particular case of the determination of the quantity of water absorbed is dealt with in ISO 62. ISO 175 is concerned with the effects of water only where changes in the dimensions and physical properties of the plastic occur as a result of the action of the water.

Plastics — Methods of test for the determination of the effects of immersion in liquid chemicals

1 Scope

1.1 This International Standard specifies a method of exposing test specimens of plastic materials, free from all external restraint, to liquid chemicals, and methods for determining the changes in properties resulting from such immersion. It does not cover environmental stress cracking (ESC) which is dealt with by the various parts of ISO 22088.

1.2 It only considers testing by immersion of the entire surface of the test specimen¹⁾.

NOTE This method may not be appropriate for simulating partial or infrequent wetting of plastics.

1.3 It is applicable to all solid plastics that are available in the form of moulding or extrusion materials, plates, tubes, rods or sheets having a thickness greater than 0,1 mm. It is not applicable to cellular materials.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291:2008, *Plastics — Standard atmospheres for conditioning and testing*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

1) Although it is not within the scope of this International Standard, it may also be of interest, when dealing with volatile liquids or those which give off vapours, to subject the specimen to only the gaseous phase above the liquid. In this event, it is advisable to proceed exactly as indicated, but to suspend the specimen above the liquid, seal the container and maintain it at the test temperature throughout.