

**Textiles - Quantitative chemical analysis - Part 9:
Mixtures of acetate and triacetate fibres (method using
benzyl alcohol)**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 1833-9:2010 sisaldab Euroopa standardi EN ISO 1833-9:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.10.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 13.10.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 1833-9:2010 consists of the English text of the European standard EN ISO 1833-9:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.10.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 13.10.2010.

The standard is available from Estonian standardisation organisation.

ICS 59.060.20

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

ICS 59.060.20

English Version

Textiles - Quantitative chemical analysis - Part 9: Mixtures of
acetate and triacetate fibres (method using benzyl alcohol) (ISO
1833-9:2006)

Textiles - Analyse chimique quantitative - Partie 9:
Mélanges de fibres d'acétate et de triacétate (méthode à
l'alcool benzylique) (ISO 1833-9:2006)

Textilien - Quantitative chemische Analysen - Teil 9:
Mischungen aus Acetat- und Triacetatfasern
(Benzylalkohol-Verfahren) (ISO 1833-9:2006)

This European Standard was approved by CEN on 12 September 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

The text of ISO 1833-9:2006 has been prepared by Technical Committee ISO/TC 38 "Textiles" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 1833-9:2010 by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2011, and conflicting national standards shall be withdrawn at the latest by April 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 1833-9:2006 has been approved by CEN as EN ISO 1833-9:2010 without any modification.

Textiles — Quantitative chemical analysis —

Part 9:

Mixtures of acetate and triacetate fibres (method using benzyl alcohol)

1 Scope

This part of ISO 1833 specifies a method, using benzyl alcohol, to determine the percentage of acetate, after removal of non-fibrous matter, in textiles made of binary mixtures of

- acetate
- and
- triacetate fibres.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1833-1, *Textiles — Quantitative chemical analysis — Part 1: General principles of testing*

3 Principle

The acetate fibre is dissolved out from a known dry mass of the mixture, with benzyl alcohol. The residue is collected, washed, dried and weighed; its corrected mass is expressed as a percentage of the dry mass of mixture. The percentage of acetate is found by the difference.

4 Reagents

Use the reagents described in ISO 1833-1 together with those given in 4.1 and 4.2.

4.1 Benzyl alcohol.

4.2 Ethanol.