
Graphic technology — Communication of graphic paper properties

*Technologie graphique — Communication des propriétés des papiers
graphiques*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 List of required criteria for communication of paper properties	5
5 ISO standards related to required criteria	6
5.1 Sampling and general information useful for technical communication	6
5.2 Brand name and paper mill	6
5.3 Grammage	7
5.4 Bulk and/or thickness	7
5.5 Roughness for evaluation of surface properties	7
5.6 Gloss	7
5.7 Opacity	8
5.8 Brightness and whiteness of unprinted paper	8
5.9 Colour measurement of paper white point in printing conditions (D50/2°).....	9
5.10 Colour measurement of unprinted paper in outdoor conditions (D65/10°).....	10
5.11 Supported colour gamut in the context of prepress design	10
5.12 Fluorescence in the context of prepress	10
5.13 Storage conditions, influence of aging and testing conditions for proofing substrates	11
5.14 Bending resistance (bending stiffness) for Sheet-Fed Offset printing substrates	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This International Standard was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 130, *Graphic technology*.

Introduction

This International Standard is intended to improve communication between the graphic papermaking industry and the printing industry based on their need to be able to produce quality printing. Paper properties and their measurement are presented and their use in the printing context is described.

This International Standard describes data to be provided for reliable printing. A substrate description can be assessed to be in conformance with this International Standard, not a substrate itself.

Printing press settings depend on paper grade, and several paper properties are required in order to define a grade.

Paper measurement standards developed within ISO/TC 6 are referenced in this International Standard. They were mainly used to develop paper industry test methods and allow the papermaking processes to be reproducible and reliable within paper mills. It is advisable that paper purchasing specifications be based on paper industry standards. This recommendation also applies to paper proofing substrates. Special requirements for paper substrates for the reliable production of printed products need to be communicated on the basis of standards developed by ISO/TC 6 whenever possible.

The evaluation of colour of the unprinted paper is critical to define prepress white point settings. This measurement can be performed with either diffuse:0° integrating sphere instruments (papermakers' equipment) or 45°:0° instruments (printers' equipment). Results are often close if the UV calibration is performed correctly. This International Standard specifies 45°:0° instruments (printers' equipment) to perform this evaluation as per ISO 13655, because of their wide availability at printers' facilities.

For the evaluation of printed colours, measurement devices are developed according to ISO 13655 which differ from the colour measurement devices which conform to ISO 2469 and ISO 5631-1, ISO 5631-2 and ISO 5631-3. The latter type of instrument is used within paper mills for quality evaluation during paper manufacturing and unprinted paper colour evaluation.

Properties linked to the printing process (e.g. dimensions, blistering and picking resistance in offset, missing dots in gravure) are not described in this International Standard, since they are implicitly needed when purchasing the paper meant for this printing process.

Properties that are not based on ISO standards are not described here.

The bibliography lists basic references in graphic technology standards,^{[1][2]} Paper and board standards,^[3] previously published references,^[4] commercial classifications,^[5] conditions of sale,^[6] and reference lists of printing characterization data publicly available.^[8]

Graphic technology — Communication of graphic paper properties

1 Scope

This International Standard specifies the list of relevant properties of paper substrates to be communicated between the paper and printing industries.

This International Standard is applicable to papers intended to be printed in rotogravure, cold-set web offset, heat-set web offset, sheet-fed offset, and flexographic printing processes and to proofing substrates.

Where multiple methods exist, the preferred procedure and its International Standard are specified.

All methods for measuring of properties specified in this International Standard are described in other ISO Standards.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 534, *Paper and board — Determination of thickness, density and specific volume*

ISO 536, *Paper and board — Determination of grammage*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ISO 2470-2, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 2: Outdoor daylight conditions (D65 brightness)*

ISO 2471, *Paper and board — Determination of opacity (paper backing) — Diffuse reflectance method*

ISO 2493-1, *Paper and board — Determination of bending resistance — Part 1: Constant rate of deflection*

ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20 degrees, 60 degrees and 85 degrees*

ISO 5627, *Paper and board — Determination of smoothness (Bekk method)*

ISO 5631-2, *Paper and board — Determination of colour by diffuse reflectance — Part 2: Outdoor daylight conditions (D65/10 degrees)*

ISO 8254-1, *Paper and board — Measurement of specular gloss — Part 1: 75 degree gloss with a converging beam, TAPPI method*

ISO 8254-2, *Paper and board — Measurement of specular gloss — Part 2: 75 degree gloss with a parallel beam, DIN method*

ISO 8254-3, *Paper and board — Measurement of specular gloss — Part 3: 20 degree gloss with a converging beam, TAPPI method*

ISO 8791-2, *Paper and board — Determination of roughness/smoothness (air leak methods) — Part 2: Bendtsen method*

ISO 8791-4, *Paper and board — Determination of roughness/smoothness (air leak methods) — Part 4: Print-surf method*

ISO 11475, *Paper and board — Determination of CIE whiteness, D65/10 degrees (outdoor daylight)*

ISO 11476, *Paper and board — Determination of CIE whiteness, C/2 degrees (indoor illumination conditions)*

ISO 12647-7, *Graphic technology — Process control for the production of half-tone colour separations, proof and production prints — Part 7: Proofing processes working directly from digital data*

ISO 13655, *Graphic technology — Spectral measurement and colorimetric computation for graphic arts images*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 grammage basis weight

mass of a unit paper area, expressed in grams per square metre

[SOURCE: ISO 536:2012, 3.1, modified]

3.2 single sheet thickness

distance between one surface of a paper and the other, measured under an applied static load

Note 1 to entry: This term is most commonly used for paper thickness.

[SOURCE: ISO 534:2011, 3.1, modified]

3.3 bulking thickness

thickness of a single sheet of paper, calculated from the thickness of several superimposed sheets in a pack, and measured under an applied static load

[SOURCE: ISO 534:2011, 3.2, modified]

3.4 apparent sheet density

mass per unit volume, expressed in grams per cubic centimetre, and calculated from the single sheet thickness

[SOURCE: ISO 534:2011, 3.3]

3.5 apparent bulk density

mass per unit volume, expressed in grams per cubic centimetre, and calculated from the bulking thickness

[SOURCE: ISO 534:2011, 3.4]

3.6 apparent specific sheet volume

volume per unit mass, expressed in cubic centimetres per gram, and calculated from the single sheet thickness

Note 1 to entry: This term is normally applicable to paper and most commonly calculated for paper bulk.