

**LÖÖKI PEHMENDAV MÄNGUVÄLJAKU ALUSPINNA
KATE. KRIITILISE KUKKUMISKÕRGUSE MÄÄRAMINE**

**Impact attenuating playground surfacing -
Determination of critical fall height**

EESTI STANDARDI EESSÕNA**NATIONAL FOREWORD**

See Eesti standard EVS-EN 1177:2008 sisaldab Euroopa standardi EN 1177:2008 ingliskeelset teksti.	This Estonian standard EVS-EN 1177:2008 consists of the English text of the European standard EN 1177:2008.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 28.05.2008.	Date of Availability of the European standard is 28.05.2008.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 97.200.40

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Impact attenuating playground surfacing - Determination of critical fall height

Sols d'aires de jeux absorbant l'impact - Détermination de la hauteur de chute critique

Stoßdämpfende Spielplatzböden - Bestimmung der kritischen Fallhöhe

This European Standard was approved by CEN on 25 April 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	3
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Test method	7
4.1 Principle	7
4.2 Apparatus	7
4.3 Accuracy of tests	8
4.4 Conditions for testing	9
4.4.1 Testing in the laboratory	9
4.4.2 Testing on site	10
4.5 Procedure	10
4.5.1 Time/acceleration trace	10
4.5.2 Selection and definition of the test position	10
4.5.3 Procedures for specific types of product	11
4.5.4 Selection of data for determination of critical fall height	12
4.6 Calculation of results	12
4.7 Test report	13
4.7.1 General	13
4.7.2 Tests carried out in the laboratory	13
4.7.3 Tests carried out on site	13
Annex A (informative) Test rig for determination of critical fall height	15
Annex B (informative) Typical examples of trace of acceleration against time and curve of HIC values against drop height	16

Foreword

This document (EN 1177:2008) has been prepared by Technical Committee CEN/TC 136 “Sports, playground and other recreational facilities and equipment”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2008, and conflicting national standards shall be withdrawn at the latest by May 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

This document supersedes EN 1177:1997.

European standards for playground equipment and surfacing comprise this European Standard and EN 1176, which consists of a number of parts as follows:

EN 1176-1, *Playground equipment and surfacing — Part 1: General safety requirements and test methods*

EN 1176-2, *Playground equipment and surfacing — Part 2: Additional specific safety requirements and test methods for swings*

EN 1176-3, *Playground equipment and surfacing — Part 3: Additional specific safety requirements and test methods for slides*

EN 1176-4, *Playground equipment and surfacing — Part 4: Additional specific safety requirements and test methods for cableways*

EN 1176-5, *Playground equipment and surfacing — Part 5: Additional specific safety requirements and test methods for carousels*

EN 1176-6, *Playground equipment and surfacing — Part 6: Additional specific safety requirements and test methods for rocking equipment*

EN 1176-7, *Playground equipment and surfacing — Part 7: Guidance on installation, inspection, maintenance and operation*

EN 1176-10, *Playground equipment and surfacing — Part 10: Additional specific safety requirements and test methods for fully enclosed play equipment*

EN 1176-11, *Playground equipment and surfacing — Part 11: Additional specific safety requirements and test methods for spatial network*

For inflatable play equipment see

EN 14960, *Inflatable play equipment — Safety requirements and test methods*

The principal changes from the previous edition of this European Standard are that all safety requirements have been removed and are now included in EN 1176-1 so that this standard is now only a method for assessing impact attenuation. As a result of round robin testing, additional criteria for carrying out the test procedure and additional requirements for the test equipment have been introduced.

This document is a preview generated by EVS

Introduction

This European Standard is based on the safety principles given in EN 1176-1 for playground equipment and provides a method for the assessment of impact attenuation of surfaces intended for use in the impact area as defined in EN 1176-1.

Injuries caused by falls from playground equipment occur for a variety of reasons but the most severe injuries are likely to be injuries to the head. The committee responsible for this European Standard recognizes that there are many factors that influence injury mechanisms independent of the surfacing, e.g. body orientation, awkwardness of fall, bone density, etc. Recent research has indicated that permanent disabilities and long bone injuries could be influenced by the duration of the acceleration pulse. The committee responsible for this European Standard intends to consider recent research in this area in a future revision of this standard.

Consequently, priority has been given to developing a criterion for surfacing materials intended to assess their ability to reduce the likelihood of head injuries.

On the basis of statistical analysis of available data the Head Injury Criterion (HIC) at a tolerance level of 1 000 has been used as the upper limit for the brain injury severity unlikely to have disabling or fatal consequences. By choosing measurement of HIC as the criterion of safety, the method considers only the kinetic energy of the head when it impacts the surface of the impact area. This is considered to be the best model available to predict the likelihood of head injury from falls. Surfaces fulfilling the test requirements of this standard are considered to be in compliance with the requirements for impact attenuation in EN 1176-1.

NOTE The HIC value of 1 000 is merely one data point on a risk severity curve where a HIC of 1 000 is equivalent to a 3 % chance of a critical injury (MAIS¹⁾ 5), a 18 % probability of a severe (MAIS 4) head injury, a 55 % probability of a serious (MAIS 3) head injury, a 89 % probability of a moderate injury (MAIS 2), and a 99,5 % chance of a minor head injury (MAIS 1), to an average male adult.

There are a variety of materials available providing impact attenuation, including rubber tiles, mats, slabs, continuous synthetic surfacing, either prefabricated or formed 'in-situ', loose particulate material, such as gravel, sand, wood chips, bark, etc. The method in this European Standard can be used to assess any of these surfaces.

1) Maximum Abbreviated Injury Scale, first developed by the Association for the Advancement of Automotive Medicine and used extensively in the automotive industry as an indicator of the severity of head-related injuries.

1 Scope

This European Standard specifies a method for determining the impact attenuation of playground surfacing. It defines a "Critical Fall Height" (see 3.2) for surfacing, which represents the upper limit of its effectiveness in reducing head injury when using playground equipment conforming to EN 1176. The test methods described in the European Standard are applicable for tests carried out in a laboratory and for tests on site.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 933-1, *Tests for geometrical properties of aggregates – Part 1: Determination of particle size distribution – Sieving method*

EN 1176-1:2008, *Playground equipment and surfacing — Part 1: General safety requirements and test methods*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)*

ISO 6487:2002, *Road vehicles – Measurement techniques in impact tests – Instrumentation*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1176-1:2008 and the following apply.

3.1

impact attenuation

property of a surface, which dissipates the kinetic energy of an impact by localized deformation or displacement such that the acceleration is reduced

3.2

critical fall height

maximum free height of fall, for which a surface will provide an acceptable level of impact attenuation, determined as described in 4.4

3.3

head injury criterion (HIC) value

criterion for head injuries caused from falls as calculated in accordance with 4.6.1

3.4

test position

position on the material to be tested located vertically below the centre of the headform

3.5

drop height

distance between the test position on the surfacing and the lowest point of the free falling headform prior to release

NOTE In the case of a guided headform this value is calculated from measurement of velocity at impact (see 4.2.6).

3.6

impact measurement

HIC value from the recorded acceleration of the headform falling from one fall height onto one test position