

## **Multilayer piping systems for hot and cold water installations inside buildings - Part 1: General**

Multilayer piping systems for hot and cold water installations inside buildings - Part 1: General

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 21003-1:2008 sisaldab Euroopa standardi EN ISO 21003-1:2008 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 18.08.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 01.07.2008.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 21003-1:2008 consists of the English text of the European standard EN ISO 21003-1:2008.

This standard is ratified with the order of Estonian Centre for Standardisation dated 18.08.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 01.07.2008.

The standard is available from Estonian standardisation organisation.

ICS 23.040.01, 91.140.60

**Võtmesõnad:**

### Standardite reprodutseerimis- ja levitamisoigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

English Version

**Multilayer piping systems for hot and cold water installations  
inside buildings - Part 1: General (ISO 21003-1:2008)**

Systèmes de canalisations multicouches pour installations  
d'eau chaude et froide à l'intérieur des bâtiments - Partie 1:  
Généralités (ISO 21003-1:2008)

Mehrschichtverbund-Rohrleitungssysteme für die Warm-  
und Kaltwasserinstallation innerhalb von Gebäuden - Teil 1:  
Allgemeines (ISO 21003-1:2008)

This European Standard was approved by CEN on 15 June 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Foreword

This document (EN ISO 21003-1:2008) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2009, and conflicting national standards shall be withdrawn at the latest by January 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative Annex ZA, B, C or D, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 21003-1:2008 has been approved by CEN as EN ISO 21003-1:2008 without any modification.

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>2</b>
<b>3 Terms and definitions</b> .....	<b>3</b>
3.1 Definitions related to construction.....	3
3.2 Definitions related to geometry.....	4
3.3 Definitions related to service conditions.....	4
3.4 Definitions related to materials.....	5
3.5 Definitions related to material characteristics.....	5
3.6 Definitions related to temperature.....	5
<b>4 Symbols and abbreviated terms</b> .....	<b>6</b>
4.1 Symbols.....	6
4.2 Abbreviated terms.....	7
<b>5 Classification of service conditions</b> .....	<b>7</b>
<b>6 Material</b> .....	<b>8</b>
6.1 General.....	8
6.2 Influence on water intended for human consumption.....	8
<b>Annex A (normative) List of reference product standards</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>10</b>

## Introduction

The system standard of which this is Part 1 specifies the requirements for a multilayer piping system.

The multilayer piping system is intended to be used for hot and cold water installations inside buildings.

In respect of potentially adverse effects on the quality of water intended for human consumption caused by the products covered by ISO 21003:

- no information is provided as to whether the products may be used without restriction in any of the member states of the EU or EFTA;
- it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of these products remain in force.

Requirements and test methods for components of the piping system are specified in ISO 21003-2 and ISO 21003-3. Characteristics relating to fitness for purpose (mainly for joints) are covered in ISO 21003-5. ISO/TS 21003-7 gives guidance on the assessment of conformity.

This part of ISO 21003 specifies the general aspects of multilayer piping systems.

For ancillary equipment, separate standards can apply.

Guidance on installation of plastics piping systems made from various materials intended to be used for hot and cold water installations is given in ENV 12108.

Other system standards which, at the date of publication of this part of ISO 21003, had been published for plastics piping systems used for the same application are listed in Annex A.

# Multilayer piping systems for hot and cold water installations inside buildings —

## Part 1: General

### 1 Scope

This part of ISO 21003 specifies the general aspects of multilayer piping systems intended to be used for hot and cold water installations inside buildings for the conveyance of water — whether or not the water is intended for human consumption (domestic systems) or heating systems — under specified design pressures and temperatures appropriate to the class of application (see Table 1).

ISO 21003 is a reference product standard (see 3.4.3). It is applicable to multilayer pipes, fittings, their joints, and also to joints with components made of other plastics and non-plastics materials intended to be used for hot and cold water installations. This part of ISO 21003 is intended for use only in conjunction with all the other parts of ISO 21003.

ISO 21003 applies only to multilayer pipes with their inner layer made of plastics.

It covers a range of service conditions (application classes) and design pressures. It is not applicable for values of design temperature,  $T_D$ , maximum design temperature,  $T_{max}$ , and malfunction temperature,  $T_{mal}$ , in excess of those in Table 1.

NOTE 1 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

The polymeric materials used for the stress-designed layers are the following: polybutylene (PB), polyethylene of raised temperature resistance (PE-RT), crosslinked polyethylene (PE-X), polypropylene (PP) and chlorinated poly(vinyl chloride) (PVC-C).

The PE-X used shall be fully crosslinked and shall comply with the requirements of the relevant reference product standard (ISO 15875).

NOTE 2 For the purposes of ISO 21003, crosslinked polyethylene (PE-X) as well as adhesives are considered as thermoplastic materials.

Solid-wall pipes with thin outer layers (applied as protection layers or barrier layers, for instance) are not covered by ISO 21003 but are specified in the Amendments to ISO 15874-2, ISO 15875-2 and ISO 15876-2. The total thickness of such outer layers, including the thickness of the adhesives used, shall be  $\leq 0,4$  mm.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3, *Preferred numbers — Series of preferred numbers*

ISO 472, *Plastics — Vocabulary*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 15874-1, *Plastics piping systems for hot and cold water installations — Polypropylene (PP) — Part 1: General*

ISO 15874-2, *Plastics piping systems for hot and cold water installations — Polypropylene (PP) — Part 2: Pipes*

ISO 15874-3, *Plastics piping systems for hot and cold water installations — Polypropylene (PP) — Part 3: Fittings*

ISO 15874-5, *Plastics piping systems for hot and cold water installations — Polypropylene (PP) — Part 5: Fitness for purpose of the system*

ISO 15875-1, *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 1: General*

ISO 15875-2, *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 2: Pipes*

ISO 15875-3, *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 3: Fittings*

ISO 15875-5, *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) — Part 5: Fitness for purpose of the system*

ISO 15876-1, *Plastics piping systems for hot and cold water installations — Polybutylene (PB) — Part 1: General*

ISO 15876-2, *Plastics piping systems for hot and cold water installations — Polybutylene (PB) — Part 2: Pipes*

ISO 15876-3, *Plastics piping systems for hot and cold water installations — Polybutylene (PB) — Part 3: Fittings*

ISO 15876-5, *Plastics piping systems for hot and cold water installations — Polybutylene (PB) — Part 5: Fitness for purpose of the system*

ISO 15877-1, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 1: General*

ISO 15877-2, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 2: Pipes*

ISO 15877-3, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 3: Fittings*



ISO 15877-5, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 5: Fitness for purpose of the system*

ISO 21003-2, *Multilayer piping systems for hot and cold water installations inside buildings — Part 2: Pipes*

ISO 21003-3, *Multilayer piping systems for hot and cold water installations inside buildings — Part 3: Fittings*

ISO 21003-5, *Multilayer piping systems for hot and cold water installations inside buildings — Part 5: Fitness for purpose of the system*

ISO/TS 21003-7, *Multilayer piping systems for hot and cold water installations inside buildings — Part 7: Guidance for the assessment of conformity*

ISO 22391-1, *Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) — Part 1: General*

ISO 22391-2, *Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) — Part 2: Pipes*

ISO 22391-3, *Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) — Part 3: Fittings*

ISO 22391-5, *Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT) — Part 5: Fitness for purpose of the system*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 3 and ISO 472, and the following, apply.

#### 3.1 Definitions related to construction

##### 3.1.1

##### **multilayer pipe**

pipe comprised of different stress-designed layers

##### 3.1.2

##### **multilayer M-pipe**

pipe comprised of polymeric stress-designed layers and one or more metallic stress-designed layers (e.g. PE-Xb/Al/PE-Xb or PE-RT/Al/PE-Xb)

NOTE The wall thickness of the pipe consists of at least 60 % of polymeric material.

##### 3.1.3

##### **multilayer P-pipe**

pipe comprised of more than one polymeric stress-designed layer (e.g. PVC-C/PE-Xb or PE-Xb/EVOH/PE-Xb)

NOTE Pipes consisting of one polymeric stress-designed layer and an outer polymeric layer which is not stress-designed are covered by the appropriate reference product standard (see Annex A).

##### 3.1.4

##### **inner layer**

layer in contact with the fluid which is conveyed

##### 3.1.5

##### **outer layer**

layer exposed to the outer environment