

**Natural stone products - Dimensional stone work -
Requirements CONSOLIDATED TEXT**

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12059:2008+A1:2011 sisaldab Euroopa standardi EN 12059:2008+A1:2011 ingliskeelset teksti.	This Estonian standard EVS-EN 12059:2008+A1:2011 consists of the English text of the European standard EN 12059:2008+A1:2011.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 21.12.2011.	Date of Availability of the European standard is 21.12.2011.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.15

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Natural stone products - Dimensional stone work - Requirements

Produits en pierre naturelle - Pierre de taille - Exigences

Natursteinprodukte - Steine für Massivarbeiten -
Anforderungen

This European Standard was approved by CEN on 12 January 2008 and includes Amendment 1 approved by CEN on 13 November 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.





EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Requirements	5
4.1 Requirements for geometric characteristics	5
4.1.1 General.....	5
4.1.2 Requirements for thickness	5
4.1.3 Requirements for flatness	6
4.1.4 Requirements for length and width	6
4.1.5 Requirements for angles and special shapes	6
4.1.6 Requirements for edges.....	6
4.1.7 Requirements for surface finish.....	6
4.2 Requirements of natural stone for dimensional work	7
4.2.1 General.....	7
4.2.2 Denomination.....	8
4.2.3 Visual appearance	8
4.2.4 Flexural strength.....	9
4.2.5 Water absorption at atmospheric pressure	9
4.2.6 Reaction to fire.....	10
4.2.7 Water absorption by capillarity	10
4.2.8 Apparent density and open porosity	10
4.2.9 Frost resistance	10
4.2.10 Thermal shock resistance.....	10
4.2.11 Compressive strength.....	11
5 Marking, packaging	11
6 Evaluation of conformity and factory production control.....	11
6.1 Evaluation for conformity	11
6.2 Initial type testing	11
6.3 Factory production control.....	12
Annex A  (informative)  Sampling	14
A.1 General.....	14
A.2 Principles of sampling	14
A.3 Taking bulk samples	14
A.4 Preparing a sampling plan.....	14
A.5 Sampling apparatus	15
A.6 Sampling methods.....	15
A.6.1 General.....	15
A.6.2 Sampling from quarries	15
A.6.3 Sampling from plants	16
A.6.4 Sampling from buildings.....	16
A.7 Marking, packaging and dispatch of the samples.....	16
A.8 Sampling report	16
Bibliography	18

Foreword

This document (EN 12059:2008+A1:2011) has been prepared by Technical Committee CEN/TC 246 "Natural stones", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2012, and conflicting national standards shall be withdrawn at the latest by June 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1, approved by CEN on 2011-11-13.

This document supersedes EN 12059:2008.

The start and finish of text introduced or altered by amendment is indicated in the text by tags **A1** and **A1**.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies requirements for the following stone units:

- a) Structural solid stone units:
 - i. Load bearing stone elements, typically subject to prevailing compression stresses, such as solid columns, arches and similar;
 - ii. Solid stone elements used for parapets, handrails, balustrades, copings and the like, intended to withstand horizontal live loadings in addition to any dead load.
- b) Finishing solid stone units:
 - i. Curved cladding panels, for the external finishing of walls, columns or pilasters;
 - ii. Stone elements for framing one or more side openings in building walls or floors, such as sills, jambs, architraves and similar.

This European Standard does not include stone masonry units, as defined in EN 771-6, stone which is a 'cast-on' finish to pre-cast concrete or agglomerated stones. Moreover it does not cover commemorative or funeral stones and sculptures, when they do not show the above mentioned characteristics.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 772-1, *Methods of test for masonry units — Part 1: Determination of compressive strength* [A1]

EN 1925, *Natural stone test methods — Determination of water absorption coefficient by capillarity*

EN 1926, *Natural stone test methods — Determination of uniaxial compressive strength*

EN 1936, *Natural stone test methods — Determination of real density and apparent density, and of total and open porosity*

EN 12371, *Natural stone test methods — Determination of frost resistance*

EN 12372, *Natural stone test methods — Determination of flexural strength under concentrated load*

EN 12407, *Natural stone test methods — Petrographic examination*

EN 12440, *Natural stone — Denomination criteria*

EN 12670:2001, *Natural stone — Terminology*

EN 13161, *Natural stone test methods — Determination of flexural strength under constant moment*

EN 13373:2003, *Natural stone test methods — Determination of geometric characteristics on units*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13755, *Natural stone test methods — Determination of water absorption at atmospheric pressure*

EN 14066, *Natural stone test methods — Determination of resistance to ageing by thermal shock*

NOTE Besides the European Standards for test methods mentioned in this clause there exist further standards which can be used for scientific examinations, but which are not relevant for the application in practice according to this standard.

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12670:2001 and the following apply.

3.1

dimensional stone work

stone element worked to any specific dimensions for inside or outside application in the building sector

NOTE Dimensional stone work includes:

- flat stone elements which are not used as slabs for cladding, (see EN 1469) or slabs for floors and stairs (see EN 12058) and also for furniture (e.g. tables, kitchen tops);
- curved stones or three-dimensional shaped stone elements.

4 Requirements

4.1 Requirements for geometric characteristics

4.1.1 General

A₁ The dimensions shall be given in the appropriate design drawings indicating e.g. thickness, length and width. **A₁**

All measurements shall be carried out in accordance with EN 13373 and all measured values of individual units shall fall within the required tolerances.

4.1.2 Requirements for thickness

The thickness shall not deviate from the nominal thickness by more than the tolerances given in Table 1.

Table 1 — Tolerances on the nominal thickness

Nominal thickness in mm	Tolerance
More than 15 up to and including 30	$\pm 10\%$ ^a
More than 30 up to and including 80	$\pm 3\text{ mm}$ ^b
More than 80	$\pm 5\text{ mm}$ ^c
^a in case of elements to be assembled the tolerance of the visual thickness shall become respectively $\pm 0,5\text{ mm}$ ^b in case of elements to be assembled the tolerance of the visual thickness shall become respectively $\pm 1\text{ mm}$ ^c in case of elements to be assembled the tolerance of the visual thickness shall become respectively $\pm 2\text{ mm}$	

Stricter tolerances may be declared by the supplier.