TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN/TS 14416

February 2014

ICS 59.080.70

Supersedes CEN/TS 14416:2005

English Version

Geosynthetic barriers - Test method for determining the resistance to roots

Barrières géosynthétiques - Méthode d'essai pour la détermination de la résistance aux racines

Geosynthetische Dichtungsbahnen - Prüfverfahren zur Bestimmung des Widerstandes gegen Wurzeln

This Technical Specification (CEN/TS) was approved by CEN on 9 December 2013 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

CEN/TS 14416:2014 (E)

اOد	ntents	Page
	eword	
ntro	oduction	
1	Scope	
2	Principle	
3	Apparatus	
1	Procedure	
5	Evaluation	
6	Test reportiography	6
Bibli	iography	7
2		

Foreword

This document (CEN/TS 14416:2014) has been prepared by Technical Committee CEN/TC 189 "Geosynthetics", the secretariat of which is held by NBN.

This document supersedes CEN/TS 14416:2005.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, aly nia, S. Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

ation uch resis

.lcation does n. This Technical Specification defines a method for testing the resistance of a geosynthetic barrier to penetration by roots. Such resistance is a requirement for many uses of geosynthetic barriers.

This Technical Specification does not purport to address all safety problems, if any, associated with its use.

1 Scope

This Technical Specification describes a laboratory procedure for the rapid testing of the resistance of polymeric, bituminous or clay geosynthetic barriers to root penetration. It is suitable for testing of welded seams or other areas of potential weakness.

A longer test that may be more suitable for testing the long-term resistance of geosynthetic barriers is described in EN 13948.

2 Principle

A section of geosynthetic barrier is placed in soil into which seeds are sown. Six to eight weeks later the geosynthetic barrier is examined to see whether it has been penetrated by the roots of the young plants.

3 Apparatus

The following equipment shall be used:

- four dry unglazed clay flower pots approximately 220 mm high. The diameter at the base of the pot shall be approximately 140 mm, the diameter at the top 250 mm, and the angle between side and central axis approximately 13°. A 40 mm wide band shall be painted on the inside of the pot, about 100 mm above the base, and allowed to dry;
- lime-free soil (pH 5 to 6), mixed with a little loam or high quality potting soil;

Compost should not be used.

- lupin seeds (lupinus alba);
- silicone mastic sealant or mortar-sand mixture;
- bitumen 85/40;
- glass tubes;
- anti-mould agent.

4 Procedure

- Fill the pots with the soil as far as the lower edge of the painted band, then seal and humidify.
- Cut three discs of geosynthetic barrier to cover the soil exactly.
- Place the geosynthetic barrier on the soil of three of the pots with the upper side uppermost.
- Carefully seal the gap between geosynthetic barrier and pot with the sealant or mortar-sand mixture.
- Prepare the fourth pot in which the geosynthetic barrier is replaced by a 20 mm thick layer of bitumen 85/40 (oxidized grade bitumen with a softening point of (85 ± 5) °C and a penetration temperature of (40 ± 5) °C).
- Cover the geosynthetic barrier or the bitumen with 90 mm of soil, then seal and humidify.