

**Kummi või plastiga pealistatud
kangasmaterjalid. Kangarulli omadused.
Osa 1: Pikkuse, laiuse ja netomassi
määramise meetodid**

Rubber- or plastics-coated fabrics - Determination of
roll characteristics - Part 1: Methods for
determination of the length, width and net mass

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 2286-1:2000 sisaldab Euroopa standardi EN ISO 2286-1:1998 ingliskeelset teksti. Käesolev dokument on jõustatud 20.03.2000 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes. Standard on kättesaadav Eesti standardiorganisatsioonist.	This Estonian standard EVS-EN ISO 2286-1:2000 consists of the English text of the European standard EN ISO 2286-1:1998. This document is endorsed on 20.03.2000 with the notification being published in the official publication of the Estonian national standardisation organisation. The standard is available from Estonian standardisation organisation.
--	---

Käsitlusala: Rahvusvahelise standardi ISO 2286 selles osas on kindlaks määratud rulli pikkus, ümardatuna allapoole lähima 0,1 meetrini, keskmine laius 5 millimeetrise täpsusega, minimaalne kasulik laius ja rulli netomass täpsusega 100 g. Kasulik laius on dubleeritud kanga laius, välja arvatud ultusäär, mis oma omadustelt on ühtne, ühtlaselt viimistletud ja ilma lubatamatute defektideta.	Scope:
--	----------------------

ICS 59.080.40

Võtmesõnad: dubleeritud kangad, kangad, katsed, kummiga dubleeritud kangad, laius, mass, massi mõõtmine, mõõtmete määramine, määramine, pikkus, plastiga dubleeritud kangad, riie, rullid

ICS 59.080.40

Descriptors: Textiles, coated fabrics, roll characteristics, testing.

English version

**Rubber- or plastics-coated fabrics – Determination
of roll characteristics**

**Part 1: Methods for determination of length, width and net mass
(ISO 2286-1 : 1998)**

Supports textiles revêtus de
caoutchouc ou de plastique –
Détermination des caractéristiques
des rouleaux – Partie 1: Méthodes de
détermination de la longueur, de la
largeur et de la masse nette
(ISO 2286-1 : 1998)

Mit Kautschuk oder Kunststoff
beschichtete Textilien – Bestimmung
der Rollencharakteristik –
Teil 1: Bestimmung der Länge, Breite
und Nettomasse
(ISO 2286-1 : 1998)

This European Standard was approved by CEN on 1998-04-18.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Foreword

International Standard

ISO 2286-1 : 1998 Rubber- or plastics-coated fabrics – Determination of roll characteristics – Part 1: Methods for determination of length, width and net mass,

which was prepared by ISO/TC 45 'Rubber and rubber products' of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 248 'Textiles and textile products', the Secretariat of which is held by BSI, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by December 1998 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 2286-1 : 1998 was approved by CEN as a European Standard without any modification.

WARNING – Persons using this part of ISO 2286 should be familiar with normal laboratory practice. This part of ISO 2286 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This part of ISO 2286 describes methods of determining the length, width and net mass of a roll of rubber- or plastics-coated fabric.

2 Definition

For the purposes of this part of ISO 2286, the following definition applies.

2.1 usable width: That width of a coated fabric, excluding the selvedge, which is consistent in its properties, uniformly finished, and free of unacceptable flaws.

3 Apparatus

3.1 Measuring surface, comprising a flat horizontal surface not less than 5 m long and at least as wide as the roll to be examined. Both longitudinal edges of this surface shall be marked off in 1 m lengths. At least one of these lengths, preferably at the end of the surface, shall be marked at 1 cm intervals.

3.2 Measuring scale, of a length greater than the width of the fabric to be measured, graduated in millimetres.

3.3 Balance, accurate to the nearest 100 g.

4 Procedure

4.1 Determination of length

Proceed either as described in the following paragraph of this subclause, or use any other suitable mechanical, electromechanical or photoelectric equipment for measuring coated-fabric length.

NOTE – The above alternative means of measurement may not, however, be suitable for extensible coated fabrics such as those having a knitted substrate.