

Nafta-, naftakeemia- ja maagaasitööstused. Nafta ja gaasi tootmisel kasutatavate ainetega kontaktis olevad mittemetallilised materjalid. Osa 1: Termoplastikud

Petroleum, petrochemical and natural gas industries - Non-metallic materials in contact with media related to oil and gas production - Part 1: Thermoplastics

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 23936-1:2009 sisaldab Euroopa standardi EN ISO 23936-1:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 29.05.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.04.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 23936-1:2009 consists of the English text of the European standard EN ISO 23936-1:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 29.05.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.04.2009.

The standard is available from Estonian standardisation organisation.

ICS 75.180.01

Võtmesõnad:

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

English Version

Petroleum, petrochemical and natural gas industries - Non-metallic materials in contact with media related to oil and gas production - Part 1: Thermoplastics (ISO 23936-1:2009)

Industries du pétrole, de la pétrochimie et du gaz naturel -
Matériaux non-métalliques en contact avec les fluides
relatifs à la production d'huile et de gaz - Partie 1: Matières
thermoplastiques (ISO 23936-1:2009)

Erdöl-, petrochemische und Erdgasindustrie -
Nichtmetallische Werkstoffe mit Medienkontakt bei der Öl-
und Gasproduktion - Teil 1: Thermoplaste (ISO 23936-
1:2009)

This European Standard was approved by CEN on 13 March 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 23936-1:2009) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2009, and conflicting national standards shall be withdrawn at the latest by October 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 23936-1:2009 has been approved by CEN as a EN ISO 23936-1:2009 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	2
3.1 Terms and definitions.....	2
3.2 Abbreviated terms.....	4
4 Functional requirements	5
4.1 General.....	5
4.2 Pipelines, piping and liners.....	5
4.3 Seals, washers and gaskets.....	10
4.4 Encapsulations, electrical insulations, injection lines.....	12
5 Requirements for technical information	12
6 Requirements for manufacturers	13
6.1 General requirements.....	13
6.2 Raw material manufacturer.....	14
6.3 Component manufacturer.....	14
6.4 Validity of qualification.....	14
7 Qualification of thermoplastic materials	14
7.1 General.....	14
7.2 Requirements for chemical resistance tests.....	14
Annex A (informative) Typical chemical properties of commonly used thermoplastic materials in media encountered in oil and gas production	16
Annex B (normative) Test media, conditions, equipment, procedures and test report requirements	20
Bibliography	25

Introduction

Non-metallic materials are used in the petroleum and natural gas industries for pipelines, piping, liners, seals, gaskets and washers, among others. Specifically, the use of piping and liners will considerably increase in the future. The purpose of ISO 23936 is to establish requirements and guidelines for systematic and effective planning, for the reliable use of non-metallic materials to achieve cost effective technical solutions, taking into account possible constraints due to safety and/or environmental issues.

ISO 23936 will be of benefit to a broad industry group ranging from operators and suppliers to engineers and authorities. It covers relevant generic types of non-metallic material (thermoplastics, elastomers, thermosetting plastics) and includes the widest range of existing technical experience. This is particularly important because the subject has not been summarized before in a technical standard. Coatings are excluded from the scope of ISO 23936.

ISO 23936 was initiated during work on ISO 15156-1, ISO 15156-2 and ISO 15156-3, which give the requirements and recommendations for the selection and qualification of low-alloy steels, corrosion-resistant alloys and other alloys for service in equipment used in environments containing H_2S in oil and natural gas production and natural gas treatment plants, where failure of such materials could pose a risk to the health and safety of the public and personnel or to the environment. A fourth part of ISO 15156 was originally envisaged to cover, likewise, the selection and qualification of non-metallic materials in the same environment. However, at a later stage it was decided that due to the differences in the corrosion mechanisms of metallic and non-metallic materials it would be too limiting to solely consider hydrogen sulfide as the corrosive component for non-metallic materials, because in oil and gas production services other systems parameters must also be considered as being corrosive and deteriorating for non-metallic materials.

It was therefore decided to produce a stand-alone International Standard, covering all systems parameters that are considered relevant in the petroleum and natural gas industries to the avoidance of corrosion damages to non-metallic equipment. ISO 23936 supplements, but does not replace, the materials requirements of the appropriate design codes, standards or regulations.

ISO 23936 applies to the qualification and selection of materials for equipment designed and constructed using conventional design criteria for technical application of non-metallic materials. Designs utilizing other criteria are excluded from its scope. ISO 23936 is not necessarily suitable for application to equipment used in refining or downstream processes and equipment.

Petroleum, petrochemical and natural gas industries — Non-metallic materials in contact with media related to oil and gas production —

Part 1: Thermoplastics

CAUTION — Non-metallic materials selected using the parts of ISO 23936 are resistant to the given environments in the petroleum and natural gas industries, but not necessarily immune under all service conditions. ISO 23936 allocates responsibility for suitability for the intended service in all cases to the equipment user.

1 Scope

ISO 23936 as a whole presents general principles and gives requirements and recommendations for the selection and qualification, and gives guidance for the quality assurance, of non-metallic materials for service in equipment used in oil and gas production environments, where the failure of such equipment could pose a risk to the health and safety of the public and personnel or to the environment. It can be applied to help to avoid costly corrosion failures of the equipment itself. It supplements, but does not replace, the material requirements given in the appropriate design codes, standards or regulations.

This part of ISO 23936 addresses the resistance of thermoplastics to the deterioration in properties that can be caused by physical or chemical interaction with produced and injected oil and gas-field media, and with production and chemical treatment. Interaction with sunlight is included; however, ionizing radiation is excluded from the scope of this part of ISO 23936.

Furthermore, this part of ISO 23936 is not necessarily suitable for application to equipment used in refining or downstream processes and equipment.

The equipment considered includes, but is not limited to, non-metallic pipelines, piping, liners, seals, gaskets and washers.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 2578, *Plastics — Determination of time-temperature limits after prolonged exposure to heat*

ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

ISO 15156-1, *Petroleum and natural gas industries — Materials for use in H₂S-containing environments in oil and gas production — Part 1: General principles for selection of cracking-resistant materials*

ISO 15156-2, *Petroleum and natural gas industries — Materials for use in H₂S-containing environments in oil and gas production — Part 2: Cracking-resistant carbon and low-alloy steels, and the use of cast irons*

ISO 15156-3, *Petroleum and natural gas industries — Materials for use in H₂S-containing environments in oil and gas production — Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys*

ASTM D638, *Standard Test Method for Tensile Properties of Plastics*

ASTM D746, *Standard Test Method for Brittleness Temperature of Plastics and Elastomers By Impact*

ASTM D792, *Standard Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement*