

**Petroleum, petrochemical and natural gas industries -
Nonmetallic materials in contact with media related to
oil and gas production - Part 2: Elastomers (ISO 23936-
2:2011)**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 23936-2:2011 sisaldab Euroopa standardi EN ISO 23936-2:2011 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 23936-2:2011 consists of the English text of the European standard EN ISO 23936-2:2011.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 15.12.2011.	Date of Availability of the European standard is 15.12.2011.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 75.180.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

ICS 75.180.01

English Version

Petroleum, petrochemical and natural gas industries - Non-metallic materials in contact with media related to oil and gas production - Part 2: Elastomers (ISO 23936-2:2011)

Industries du pétrole, de la pétrochimie et du gaz naturel -
Matériaux non métalliques en contact avec les fluides
relatifs à la production de pétrole et de gaz - Partie 2:
Élastomères (ISO 23936-2:2011)

Erdöl-, petrochemische und Erdgasindustrie -
Nichtmetallische Werkstoffe mit Medienkontakt bei der Öl-
und Gasproduktion - Teil 2: Elastomere (ISO 23936-
2:2011)

This European Standard was approved by CEN on 14 December 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 23936-2:2011) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2012, and conflicting national standards shall be withdrawn at the latest by June 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 23936-2:2011 has been approved by CEN as a EN ISO 23936-2:2011 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	2
3.1 Terms and definitions	2
3.2 Abbreviated terms	4
4 Technical requirements	4
5 Documentation requirements	5
6 Requirements for manufacturers	6
6.1 General requirements	6
6.2 Validation of compliance	7
7 Qualification of elastomer materials (ageing and RGD)	8
7.1 General	8
7.2 Requirements for ageing tests	8
7.3 Requirements for rapid gas decompression testing	9
8 Qualification of elastomeric materials in bonded flexible hose	9
8.1 General	9
8.2 Qualification of bonded flexible hose liner material	10
8.3 Qualification of bonded flexible hose – Layers outside the liner	14
9 Qualification of elastomeric materials in other large components	15
9.1 General	15
9.2 Qualification of elastomeric materials in flexible joints	15
9.3 Qualification of elastomeric materials in blow-out preventers	15
9.4 Qualification of elastomeric materials for packers	16
Annex A (normative) Test media, conditions, equipment and procedures for ageing of elastomeric materials	17
Annex B (normative) Test media, conditions, equipment and procedures for rapid gas decompression testing of elastomeric materials	26
Annex C (informative) Most commonly used elastomeric materials	40
Annex D (normative) Procedure for estimation of material service life using the Arrhenius relationship	42
Annex E (informative) Physical and chemical ageing	47
Annex F (informative) Rapid gas decompression (RGD)	62
Bibliography	66

Introduction

ISO 23936 is intended to be of benefit to a broad industry group, ranging from operators and suppliers to engineering companies and authorities. ISO 23936 covers relevant generic types of non-metallic material (thermoplastics, elastomers, thermosetting plastics, fibre-reinforced plastics, etc.) and draws upon a wide range of existing technical experience, which has never before been summarized in a technical standard.

ISO 23936 does not cover polymeric coatings such as thermal insulation and paint that are applied to the outside of components but that are not in contact with oilfield fluids.

The evaluation and qualification process described in this part of ISO 23936 is intended to ensure that the user of non-metallic materials has sufficient understanding and knowledge of the applicable materials to obtain acceptable performance in the specified environment, and that the user can rely on stable quality to meet given specifications. A quality system is useful to ensure compliance with the requirements of this part of ISO 23936.

Successful qualification of a manufacturer and a specific material is intended to be valid for other projects and different operators. The consideration of qualification of a manufacturer is at the discretion and determination of the purchaser, normally on the basis of documentation provided by the manufacturer, as required in this part of ISO 23936 or any specific additional documentation.

The purchaser is responsible for ensuring (if necessary, with external competence) that the manufacturers selected are qualified.

This part of ISO 23936 is based on NORSOK standard M-710.

Petroleum, petrochemical and natural gas industries — Non-metallic materials in contact with media related to oil and gas production —

Part 2: Elastomers

1 Scope

ISO 23936 describes general principles and gives requirements and recommendations for the selection and qualification of non-metallic materials for service in equipment used in oil and gas production environments, where the failure of such equipment could pose a risk to the health and safety of the public and personnel, or to the environment. It can be applied to help avoid failures of the equipment itself. It supplements, but does not replace, the material requirements given in the appropriate design codes, standards or regulations.

This part of ISO 23936 describes the requirements and procedures for qualification of elastomeric material used in equipment for oil and gas production.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1:2010, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 815-1, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 1: At ambient or elevated temperatures*

ISO 2781, *Rubber, vulcanized or thermoplastic — Determination of density*

ISO 2921, *Rubber, vulcanized — Determination of low-temperature retraction (TR test)*

ISO 3601-3:2005, *Fluid power systems — O-rings — Part 3: Quality acceptance criteria*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

ISO 13628-10:2005, *Petroleum and natural gas industries — Design and operation of subsea production systems — Part 10: Specification for bonded flexible pipe*

ASTM D297, *Standard Test Methods for Rubber Products — Chemical Analysis*

ASTM D395, *Standard Test Methods for Rubber Property — Compression Set*

ASTM D412, *Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers — Tension*

ASTM D624, *Standard Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers*

ASTM D1414, *Standard Test Methods for Rubber O-Rings*

ASTM D1415, *Standard Test Method for Rubber Property — International Hardness*

ASTM D2240, *Standard Test Method for Rubber Property — Durometer Hardness*

API 17K, *Specification for Bonded Flexible Pipe*

3 Terms, definitions and abbreviated terms

For the purposes of this document, the following terms, definitions and abbreviated terms apply.

3.1 Terms and definitions

3.1.1

accelerated test

test undertaken under conditions designed to speed material deterioration

NOTE This is usually accomplished by increasing temperature, in order to raise chemical reaction rates, but fluid concentration and stress are variables which can also be manipulated.

3.1.2

asset operator

person who operates an asset, who has knowledge of well parameters and who transmits this information to the **user** (3.1.15)

NOTE 1 An asset can be a well, a production train, a plant, etc.

NOTE 2 Well parameters can be fluid exposure, temperatures, pressures, duration, etc.

3.1.3

compression set

difference between the original sample height and the post-test height, divided by the interference, expressed as a percentage

3.1.4

elastomer

rubber

amorphous material mechanically mixed with other constituents to form a rubber compound, which is then shaped by flow into articles by means of the manufacturing processes of moulding or extrusion, and then (invariably) chemically cured at elevated temperature to form an elastic insoluble material

3.1.5

fluid

medium such as a gas, liquid, supercritical gas, or a mixture of these