

Keevitusmaterjalid. Kattega elektroodid legeerimata ja peenterateraste käsikaarkeevituseks. Liigitamine

Welding consumables - Covered electrodes for manual metal arc welding of non-alloy and fine grain steels - Classification

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 2560:2009 sisaldab Euroopa standardi EN ISO 2560:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.12.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.10.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 2560:2009 consists of the English text of the European standard EN ISO 2560:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.12.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.10.2009.

The standard is available from Estonian standardisation organisation.

ICS 25.160.20

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

English Version

**Welding consumables - Covered electrodes for manual metal
arc welding of non-alloy and fine grain steels - Classification
(ISO 2560:2009)**

Produits consommables pour le soudage - Électrodes
enrobées pour le soudage manuel à l'arc des aciers non
alliés et des aciers à grains fins - Classification (ISO
2560:2009)

Schweißzusätze - Umhüllte Stabelektroden zum
Lichtbogenhandschweißen von unlegierten Stählen und
Feinkornstählen - Einteilung (ISO 2560:2009)

This European Standard was approved by CEN on 17 September 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 2560:2009) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2010, and conflicting national standards shall be withdrawn at the latest by April 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2560:2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 2560:2009 has been approved by CEN as a EN ISO 2560:2009 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	3
4.1 Symbol for the product/process	3
4.2 Symbols for strength and elongation of all-weld metal	3
4.3 Symbol for impact properties of all-weld metal	4
4.4 Symbol for the chemical composition of all-weld metal	5
4.5 Symbol for type of electrode covering	6
4.6 Symbol for condition of post-weld heat-treatment of all-weld metal	7
4.7 Symbol for nominal electrode efficiency and type of current	7
4.8 Symbol for welding position	8
4.9 Symbol for diffusible hydrogen content of deposited metal	8
5 Mechanical tests	9
5.1 Preheating and interpass temperatures	9
5.2 Pass sequence	13
6 Chemical analysis	13
7 Fillet weld test	16
8 Rounding procedure	18
9 Retests	18
10 Technical delivery conditions	18
11 Examples of designation	19
Annex A (informative) Classification systems	20
Annex B (informative) Description of types of electrode covering — Classification by yield strength and 47 J impact energy	23
Annex C (informative) Description of types of electrode covering — Classification by tensile strength and 27 J impact energy	25
Annex D (informative) Notes on diffusible hydrogen and the avoidance of cold cracking	28
Bibliography	29

Introduction

This International Standard recognizes that there are two somewhat different approaches in the global market to classifying a given electrode, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both, where suitable) identifies a product as classified in accordance with this International Standard. The classification in accordance with system A is mainly based on EN 499:1994^[1]. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

This International Standard provides a classification in order to designate covered electrodes in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield strength to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Therefore, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of Table 1A or to Table 1B and Table 8B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify the electrodes vary from those obtained in production joints because of differences in welding procedure such as electrode size, width of weave, welding position, welding current, interpass temperature and parent metal composition.

Welding consumables — Covered electrodes for manual metal arc welding of non-alloy and fine grain steels — Classification

1 Scope

This International Standard specifies requirements for classification of covered electrodes and deposited metal in the as-welded condition and in the post-weld heat-treated condition for manual metal arc welding of non-alloy and fine grain steels with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa.

This International Standard is a combined specification providing for classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- a) Paragraphs and tables which carry the suffix letter “A” are applicable only to covered electrodes classified to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal in this International Standard.
- b) Paragraphs and tables which carry the suffix letter “B” are applicable only to covered electrodes classified to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal in this International Standard.
- c) Paragraphs and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all covered electrodes classified in this International Standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and markings*

ISO 2401, *Covered electrodes — Determination of the efficiency, metal recovery and deposition coefficient*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in ferritic steel arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947, *Welds — Welding positions*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14344, *Welding and allied processes — Procurement of welding consumables*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-3:2000, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld* (as amended by ISO 15792-3:2000/Cor.1:2006)

ISO 80000-1, *Quantities and units — Part 1: General*

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the following subclauses. In most cases, a given commercial product can be classified in both systems. Then either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a covered electrode as given below. The classification is based on an electrode size of 4,0 mm, with the exception of the symbol for welding position, which is based on ISO 15792-3. Where the defined diameter has not been manufactured, the closest diameter to 4,0 mm shall be used for all-weld metal tests.

3A Classification by yield strength and 47 J impact energy

The classification is divided into eight parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal (see Table 2A);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3A);
- 5) the fifth part gives a symbol indicating the type of electrode covering (see 4.5A);
- 6) the sixth part gives a symbol indicating the nominal electrode efficiency and type of current (see Table 5A);
- 7) the seventh part gives a symbol indicating the welding position (see Table 6A);
- 8) the eighth part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see Table 7).

3B Classification by tensile strength and 27 J impact energy

The classification is divided into seven parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the strength of all-weld metal (see Table 1B);
- 3) the third part gives a symbol indicating the type of electrode covering, the type of current, and the welding position (see Table 4B);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3B);
- 5) the fifth part gives a symbol indicating the condition of post-weld heat treatment under which the all-weld metal test was conducted (see 4.6B);
- 6) the sixth part gives a symbol indicating that the electrode has satisfied a requirement for 47 J impact energy at the temperature normally used for the 27 J requirement;
- 7) the seventh part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see Table 7).