

**Mössiga pindamine. Katsemeetodid. Osa 8: Mössikihi
visuaalne defekteerimine**

**Slurry surfacing - Test methods - Part 8: Visual
assessment of defects**

EESTI STANDARDI EESSÕNA

See Eesti standard EVS-EN 12274-8:2005 sisaldab Euroopa standardi EN 12274-8:2005 ingliskeelset teksti.

Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.

Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 28.09.2005.

Standard on kättesaadav Eesti Standardikeskusest.

NATIONAL FOREWORD

This Estonian standard EVS-EN 12274-8:2005 consists of the English text of the European standard EN 12274-8:2005.

This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.

Date of Availability of the European standard is 28.09.2005.

The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

ICS 93.080.20

English Version

Slurry surfacing - Test methods - Part 8: Visual assessment of defects

Matériaux bitumineux coulés à froid - Méthodes d'essai -
Partie 8: Evaluation visuelle

Dünne Asphaltschichten in Kaltbauweise - Prüfverfahren -
Teil 8: Augenscheinliche Beurteilung

This European Standard was approved by CEN on 4 August 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms, definitions and symbols	4
4 Visual assessment of defects	6
5 Expression of Results	10
6 Test report	12
Annex A (normative) Qualitative assessment – Estimated "drive-over" method	13
Annex B (normative) Quantitative assessment – Measured method	15
Annex C (informative) Photographs of defects	16
Bibliography	22

Foreword

This European Standard (EN 12274-8:2005) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2006, and conflicting national standards shall be withdrawn at the latest by March 2006.

This European Standard is one of a series of standards as listed below:

EN 12274-1, *Slurry surfacing – Test methods – Part 1: Sampling for binder extraction.*

EN 12274-2, *Slurry surfacing – Test methods – Part 2: Determination of residual binder content.*

EN 12274-3, *Slurry surfacing – Test methods – Part 3: Consistency.*

EN 12274-4, *Slurry surfacing – Test methods – Part 4: Determination of cohesion of the mix.*

EN 12274-5, *Slurry surfacing – Test methods – Part 5: Determination of wearing.*

EN 12274-6, *Slurry surfacing – Test methods – Part 6: Rate of application.*

EN 12274-7, *Slurry surfacing – Test methods – Part 7: Shaking abrasion test.*

EN 12274-8, *Slurry surfacing – Test methods – Part 8: Visual assessment of defects.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies qualitative and quantitative test methods of the visual assessment of defects of slurry surfacing.

This European Standard is applicable to all slurry surfacing (roads, airfields and other areas).

The visual assessment reports for both methods have identical records and thus both may be used to check the specification for visual assessment of defects.

Defects emanating from the substrate (existing road) must not be taken into consideration.

NOTE 1 The qualitative and quantitative tests may be used separately or sequentially. This may relate to different types of sites (for example lightly trafficked roads may not be required to be quantitatively assessed).

NOTE 2 The test may be used to evaluate the durability of slurry surfacing.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13036-1, *Road and airfield surface characteristics — Test methods — Part 1: Measurement of pavement surface macrotexture depth using a volumetric measurement patch technique*

3 Terms, definitions and symbols

For the purposes of this European Standard, the following terms, definitions and symbols apply.

3.1 Terms and definitions

3.1.1

defect

state of a slurry surfacing where the material is affected by one or more of the effects defined in this European Standard (see 3.1.2 to 3.1.13).

3.1.2

bleeding, fatting up and tracking

appearance of free binder at the surface

NOTE This may be due to the binder migrating to the surface (bleeding) or to coarse aggregate migrating downwards (fatting up) or a combination of the two, it is often difficult to visually separate the two causes. Tracking is evident as shiny areas caused by traffic resulting in loss of macrotexture normally in the wheel tracks.

3.1.3

delamination

detachment of the slurry surfacing from the underlying road or from a lower layer of a multi-layer slurry surfacing

3.1.4

wearing and loss of slurry surfacing

loss of mass of material