# Vask ja vasesulamid. Keskmise kristallisuuruse määramine

Copper and copper alloys - Estimation of average grain size



### EESTI STANDARDI EESSÕNA

### NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 2624:2000 sisaldab Euroopa standardi EN ISO 2624:1995 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 2624:2000 consists of the English text of the European standard EN ISO 2624:1995.
Standard on kinnitatud Eesti Standardikeskuse 11.01.2000 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.	This standard is ratified with the order of Estonian Centre for Standardisation dated 11.01.2000 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.
Standard on kättesaadav esti standardiorganisatsioonist.	The standard is available from Estonian standardisation organisation.
ICS 77.120.30	nowiew of management of the transfer of the tr
Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või nillisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.	

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega: Aru 10 Tallinn 10317 Eesti; <u>www.evs.ee</u>; Telefon: 605 5050; E-post: <u>info@evs.ee</u>

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation: Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

#### **EUROPEAN STANDARD**

**EN ISO 2624** 

#### NORME EUROPÉENNE

#### EUROPÄISCHE NORM

May 1995

#### ICS 77.040.30

٤.

Descriptors:

° 1995

copper, copper alloys, grain size analysis, microstructure, grain structure, microscopy, microphotography



All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN ISO 2624:1995 E

Page 2 EN ISO 2624:1995

#### Foreword

The text of the International Standard from ISO/TC 26 "Copper and copper alloys" of the International Organization for Standardization (ISO) has been taken over as a European Standard by CEN/TC 133 "Copper and copper alloys".

. .

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1995, and conflicting national standards shall be with awn at the latest by November 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy uxembourg, Netherlands, Norway, Portugal, Spain, Sweden,

Greece, Iceland, Ireland, Ireland, Italy, Greece, Iceland, United Kingdom. Switzerland, United Kingdom. Endorsement notice The text of the International Standard ISO 2624:1990 was approved by CEN as a European Standard without any modification. preview of ner area by the

## INTERNATIONAL STANDARD

Second edition 1990-02-01

2624

ISO





Reference number ISO 2624 : 1990 (E)

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee, International organizations, govern-mental and non-governmental, in liaison with SO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with SO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 2624 was prepared by Technical Complittee ISO/TC 26, Copper and copper alloys.

This second edition cancels and replaces the first edition (ISO 2624 : 1973) of which it Jenerated by FLS constitutes a minor revision.

Annex A forms an integral part of this International Standard.

© ISO 1990

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

A provide the p

two fields of observation can be exactly the same. Practical masters limit the number of grains that can reasonably be counted to less than the number statistically desirable.

this document is a period of the providence of t

# Copper and copper alloys — Estimation of average grain size

#### 1 Scope

This International Standard profiles three procedures for estimating, and rules for expressing, the average grain size of copper and copper alloys consisting principally of a single phase. The respective procedures are termed the comparison procedure, the intercept procedure and the planimetric procedure.

The comparison procedure (comparing the specimen with a standard chart) is most convenient and is sufficiently accurate for most commercial purposes.

Higher degreees of accuracy in estimating grain size are obtainable by using the intercept (Heyn) or planimetric (Jeffries) procedures. In cases of dispute, it is recommended that the use of one of these procedures be agreed between the parties.

For material with non-equiaxial structures it is recommended that the intercept procedure be used.

#### 2 Symbols and designations

Symbol	Designation
f	Jeffries' multiplier used to obtain number of grains per square millimetre by planimetric method
т	Number of grains per square millimetre
d	Average grain ''diameter'' in millimetres; an arbitrary measure defined as $1/\sqrt{m}$
1	Average intercept length
Y	Magnification

#### 3 Test samples

**3.1** Grain size estimations shall be made on three or more representative fields of each sample section. In known equiaxial structures only a representative section need be taken on the sample. For non-equiaxial or unknown structures three sections must be prepared, each at right angles to the other.

**3.2** The specimen shall be carefully prepared to reveal the grain boundaries using a contrast etch to match the standard charts.

#### 4 Procedures

#### 4.1 Comparison procedure

The estimation of grain size is made by direct comparison of a projected image of a photomicrograph of a representative field of the test specimen, either with the photomicrographs of the standard grain size series or with suitable reproductions of them (for standard grain size charts, see annex A); when a projection microscope is not available a bench microscope may be used. It is recommended that, to facilitate comparison, mechanical arrangements be made to permit bringing the standard photomicrographs successively into juxtaposition with the projected image.

## Intercept procedure

**4.2.1** The grain size is estimated by counting, on the ground glass screen of a projection microscope, on the image in a bench microscope fitted with a graticule, on a photomicrograph of a representative field of the specimen, or on the specimen itself, the number of grains intercepted by one or more straight lines sufficiently long to yield at least 10 intercepts per line and at least 50 intercepts for all lines for normal purposes and at least 200 intercepts for referee purposes. Grains touched by the end of the line count only as half grains. The length of the line or lines in millimetres at the surface of the section, divided by the number of grains intersected by it, gives the average intercept length *i*. For practical purposes, the average intercept length, *l*, may be legarded as equal to the average grain diameter  $d^{1}$ .

**4.2.2** For non-equiaxial structures, measurements should be made on longitudinal and transverse sections along lines that lie in all three principal directions of the specimen. For each direction, the average grain "diameters" should be calculated as in 4.2.1.

<sup>1)</sup> To achieve compatibility with estimations of grain "diameter" made by the planimetric or comparison procedure, the intercept length, *I*, should be multiplied by the factor 1,13.