

**Advanced technical ceramics -  
Mechanical properties of ceramic  
composites at high temperature under  
inert atmosphere - Determination of  
compression properties**

Advanced technical ceramics - Mechanical  
properties of ceramic composites at high  
temperature under inert atmosphere - Determination  
of compression properties

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 12290:2005 sisaldab Euroopa standardi EN 12290:2005 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 29.08.2005 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 12290:2005 consists of the English text of the European standard EN 12290:2005.</p> <p>This document is endorsed on 29.08.2005 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p><b>Käsitlusala:</b> This European Standard specifies the conditions for determination of compression properties of ceramic matrix composite materials with continuous fibre reinforcement for temperatures up to 2 000 °C under vacuum or a gas atmosphere which is inert to the material under test.</p>	<p><b>Scope:</b> This European Standard specifies the conditions for determination of compression properties of ceramic matrix composite materials with continuous fibre reinforcement for temperatures up to 2 000 °C under vacuum or a gas atmosphere which is inert to the material under test.</p>
--	--

ICS 81.060.30

Võtmesõnad:

English version

**Advanced technical ceramics - Mechanical properties of ceramic  
composites at high temperature under inert atmosphere -  
Determination of compression properties**

Céramiques techniques avancées - Propriétés mécaniques  
des céramiques composites à haute température en  
atmosphère neutre - Détermination des caractéristiques en  
compression

Hochleistungskeramik - Mechanische Eigenschaften von  
keramischen Verbundwerkstoffen bei hoher Temperatur in  
inertter Atmosphäre - Bestimmung der Eigenschaften unter  
Druck

This European Standard was approved by CEN on 12 May 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

page

Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms, definitions and symbols.....	4
4 Principle.....	6
5 Apparatus .....	6
5.1 Test machine .....	6
5.2 Load train.....	6
5.3 Gastight test chamber.....	7
5.4 Set-up for heating .....	7
5.5 Extensometer .....	7
5.6 Temperature measurement devices .....	7
5.7 Data recording system .....	8
5.8 Micrometers.....	8
6 Test specimens .....	8
6.1 General.....	8
6.2 Compression between platens.....	8
6.3 Test specimen used with grips .....	9
7 Test specimen preparation .....	12
7.1 Machining and preparation.....	12
7.2 Number of test specimens.....	12
8 Test procedures .....	12
8.1 Test set-up: Temperature considerations.....	12
8.2 Test set-up: other considerations.....	13
8.3 Testing technique .....	14
8.4 Test validity .....	15
9 Calculation of results .....	15
9.1 Test specimen origin.....	15
9.2 Compression strength .....	15
9.3 Strain at maximum compression force .....	16
9.4 Proportionality ratio or pseudo-elastic modulus, elastic modulus.....	16
10 Test report .....	17
Annex A (normative) Buckling: How to proceed when buckling is suspected.....	18
A.1 Preliminary room temperature test.....	18
A.2 Test with two different specimens.....	18
Bibliography .....	19

## Foreword

This document (EN 12290:2005) has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2005, and conflicting national standards shall be withdrawn at the latest by December 2005.

This document supersedes ENV 12290:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This European Standard specifies the conditions for determination of compression properties of ceramic matrix composite materials with continuous fibre reinforcement for temperatures up to 2 000 °C under vacuum or a gas atmosphere which is inert to the material under test.

NOTE The use of these environments is aimed at avoiding changes of the material to be tested due to chemical reaction with its environment during the test.

This European Standard applies to all ceramic matrix composites with a continuous fibre reinforcement, unidirectional (1D), bidirectional (2D), and tridirectional ( $x$ D, with  $2 < x \leq 3$ ), loaded along one principal axis of reinforcement.

Two types of compression are distinguished:

- a) compression between platens;
- b) compression using grips.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10002-4, *Metallic materials - Tensile test - Part 4: Verification of extensometers used in uniaxial testing*.

EN 60584-1, *Thermocouples - Part 1: Reference tables (IEC 60584-1:1995)*.

EN 60584-2, *Thermocouples — Part 2: Tolerances (IEC 60584-2:1982 + A1:1989)*.

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force measuring system (ISO 7500-1:2004)*.

ISO 3611, *Micrometer callipers for external measurement*.

## 3 Terms, definitions and symbols

For the purposes of this European Standard, the following terms and definitions apply.

### 3.1

#### **test temperature, $T$**

temperature of the test piece at the centre of the gauge length

### 3.2

#### **calibrated length, $l$**

part of the test specimen that has uniform and minimum cross-section area

### 3.3

#### **gauge length, $L_0$**

initial distance between reference points on the test specimen in the calibrated length