

Timber structures - Test methods - Load bearing
stapled joints

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 1381:2016 sisaldab Euroopa standardi EN 1381:2016 ingliskeelset teksti.	This Estonian standard EVS-EN 1381:2016 consists of the English text of the European standard EN 1381:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.02.2016.	Date of Availability of the European standard is 17.02.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Timber structures - Test methods - Load bearing stapled joints

Structures en bois - Méthodes d'essai - Assemblages
agrafés porteurs

Holzbauwerke - Prüfverfahren - Tragende
Klammerverbindungen

This European Standard was approved by CEN on 19 December 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Symbols and abbreviations	5
5 Materials.....	7
5.1 Timber.....	7
5.2 Wood-based materials.....	7
5.3 Staples.....	7
6 Test methods	8
6.1 General.....	8
6.2 Conditioning.....	8
6.3 Fabrication of the test pieces.....	8
6.4 Preparation of the test pieces.....	8
6.4.1 Load parallel to grain.....	8
6.4.2 Load perpendicular to grain	9
6.5 Test procedure.....	9
6.6 Test Result	11
6.7 Test Report.....	11
Bibliography.....	13

European foreword

This document (EN 1381:2016) has been prepared by Technical Committee CEN/TC 124 “Timber Structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1381:1999.

Compared to EN 1381:1999, the following changes have been made:

- replacement of EN 28970 by EN ISO 8970;
- improvement to figures and definitions.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies test methods for determining the strength and deformation characteristics of stapled joints in load-bearing timber structures.

The methods assess joints with members of timber (solid timber and glued laminated timber) or wood-based products in the combination proposed for use in service and using all types of staples up to 3 mm diameter for circular cross-section staples or 4 mm x 2 mm for rectangular or oval cross-section staples.

The methods determine load-slip characteristics and maximum load of joints with laterally loaded staples where various angles between the applied force and the timber grain direction or the main direction of the wood-based products, respectively, are possible.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 322, *Wood-based panels - Determination of moisture content*

EN 323, *Wood-based panels - Determination of density*

EN 14592, *Timber Structures – Dowel-type-fasteners – Requirements*

EN 26891:1991, *Timber structures - Joints made with mechanical fasteners - General principles for the determination of strength and deformation characteristics (ISO 6891:1983)*

EN ISO 8970:2010, *Timber structures - Testing of joints made with mechanical fasteners - Requirements for wood density (ISO 8970:2010)*

ISO 13061-1, *Physical and mechanical properties of wood — Test methods for small clear wood specimens — Part 1: Determination of moisture content for physical and mechanical tests*

ISO 13061-2, *Physical and mechanical properties of wood — Test methods for small clear wood specimens — Part 2: Determination of density for physical and mechanical tests*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

staple

double-bent, u-shaped piece of round, square, rectangular or oval wire with pointed

3.2

staple crown

connection between the two staple legs

3.3

staple leg diameter or side length

nominal diameter of a round staple leg, the side length of a rectangular leg, or the diameter of an oval cross section as defined in EN 14592