

Kivistunud betooni katsetamine. Osa 1: Kuju, mõõtmed ja muud katsekehadele ja vormidele esitatavad nõuded

Testing hardened concrete - Part 1: Shape, dimensions and other requirements for specimens and moulds

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12390-1:2012 sisaldab Euroopa standardi EN 12390-1:2012 ingliskeelset teksti.	This Estonian standard EVS-EN 12390-1:2012 consists of the English text of the European standard EN 12390-1:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 12.09.2012.	Date of Availability of the European standard is 12.09.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Testing hardened concrete - Part 1: Shape, dimensions and other requirements for specimens and moulds

Essai pour béton durci - Partie 1 : Forme, dimensions et autres exigences aux éprouvettes et aux moules

Prüfung von Festbeton - Teil 1: Form, Maße und andere Anforderungen für Probekörper und Formen

This European Standard was approved by CEN on 13 July 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Shape, dimensions and tolerances of specimens	5
4.1 General	5
4.2 Cubes	6
4.2.1 Nominal sizes	6
4.2.2 Designated sizes	6
4.2.3 Tolerances	6
4.3 Cylinders	7
4.3.1 Nominal sizes	7
4.3.2 Designated sizes	7
4.3.3 Tolerances	7
4.3.4 Applicability of tolerances	7
4.4 Prisms	8
4.4.1 Nominal sizes	8
4.4.2 Designated sizes	8
4.4.3 Tolerances	8
4.5 Measurement of dimensions and shape of specimens	8
5 Moulds	9
5.1 General	9
5.2 Calibrated moulds	9
Annex A (normative) Application of EN ISO 1101 to concrete test specimens and moulds	11
A.1 General	11
A.2 Flatness	11
A.3 Perpendicularity	11
A.4 Straightness	12
Annex B (normative) Assessment of flatness of specimens and moulds	13

Foreword

This document (EN 12390-1:2012) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2013, and conflicting national standards shall be withdrawn at the latest by March 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN [and/or] CENELEC shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12390-1:2000.

This standard is one of a series on testing concrete.

EN 12390, *Testing hardened concrete*, consists of the following parts:

- *Part 1: Shape, dimensions and other requirements for specimens and moulds;*
- *Part 2: Making and curing specimens for strength tests;*
- *Part 3: Compressive strength of test specimens;*
- *Part 4: Compressive strength — Specification for testing machines;*
- *Part 5: Flexural strength of test specimens;*
- *Part 6: Tensile splitting strength of test specimens;*
- *Part 7: Density of hardened concrete;*
- *Part 8: Depth of penetration of water under pressure;*
- *Part 9: Freeze-thaw resistance — Scaling (technical specification);*
- *Part 10: Determination of the relative carbonation resistance of concrete (technical specification);*
- *Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion (technical specification).*

The following amendments have been made to the former edition:

- editorial revision;
- increases in the allowable tolerances for the dimensions of the specimens which reflect current industry practice.

This standard recognises alternative approaches towards obtaining test specimens of the correct sizes and shapes. The first is to use moulds whose life is limited and to measure the specimens to ensure conformity. The second is to cast specimens in calibrated metal moulds which meet tighter tolerances than for specimens. The use of calibrated moulds allows relaxation on the requirement for measuring the specimens.

Annex A gives the application of EN ISO 1101 to measuring the shapes of concrete test specimens and moulds.

Annex B gives a method to measure the flatness of specimens and moulds.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This European Standard specifies the shape, dimensions and tolerances of cast concrete test specimens in the form of cubes, cylinders and prisms, and of the moulds required to produce them.

NOTE The tolerances specified in this European Standard are based on the needs of strength testing, but they can be applicable to tests for other properties.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 1101:2005, *Geometrical Product Specifications (GPS) — Geometrical tolerancing — Tolerances of form, orientation, location and run-out (ISO 1101:2004)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 1101:2005 and the following apply.

3.1

nominal size

commonly used description of specimen size

3.2

designated size

specimen size in millimetres, selected and declared by the user of this standard from amongst the allowed range of nominal sizes

4 Shape, dimensions and tolerances of specimens

4.1 General

For application of EN ISO 1101 to the measurement of concrete test specimens and moulds in respect to flatness, perpendicularity and straightness, see Annex A.

For each shape of test specimen, cube, cylinder and prism, the nominal size d (Figures 1, 2 and 3) should be chosen to be at least three and a half times the maximum aggregate size (D_{\max} according to EN 206-1) in the concrete.