

Kivistunud betooni katsetamine. Osa 6: Katsekehade lõhestustõmbetugevus

Testing hardened concrete - Part 6: Tensile splitting strength of test specimens

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 12390-6:2009 sisaldab Euroopa standardi EN 12390-6:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.12.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 02.12.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 12390-6:2009 consists of the English text of the European standard EN 12390-6:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.12.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 02.12.2009.

The standard is available from Estonian standardisation organisation.

ICS 91.100.30

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

English Version

Testing hardened concrete - Part 6: Tensile splitting strength of test specimens

Essais sur béton - Partie 6 : Détermination de la résistance en traction par fendage d'éprouvettes

Prüfung von Festbeton - Teil 6: Spaltzugfestigkeit von Probekörpern

This European Standard was approved by CEN on 1 November 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Principle	5
4 Apparatus	5
5 Test specimens	6
6 Procedure	7
7 Expression of results	8
8 Test report	9
9 Precision	9
Annex A (normative) Determination of tensile splitting strength using cubic or prismatic specimens	10

Foreword

This document (EN 12390-6:2009) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2010, and conflicting national standards shall be withdrawn at the latest by June 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12390-6:2000.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

This standard is one of a series concerned with testing concrete.

EN 12390, *Testing hardened concrete* consists of the following parts:

- *Part 1: Shape, dimensions and other requirements of specimens and moulds*
- *Part 2: Making and curing specimens for strength tests*
- *Part 3: Compressive strength of test specimens*
- *Part 4: Compressive strength — Specification for testing machines*
- *Part 5: Flexural strength of test specimens*
- *Part 6: Tensile splitting strength of test specimens*
- *Part 7: Density of hardened concrete*
- *Part 8: Depth of penetration of water under pressure*

The main change from the previous edition of this European Standard has been to provide an alternative specification for packing strips and requires the selected loading rate to be applied after the initial load does not exceed approximately 20 % of the anticipated failure load.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This test method was one of a number examined in a laboratory inter-comparison part-funded by the EC under Measurement and Testing programme, contract MAT1-CT94-0043. The programme and other references showed the following:

- a) Tensile splitting strengths measured between the normal plane platens of testing machines gave the same results as those using the special curved platens, originally described in ISO 4018. Although, therefore these curved platens have been optionally retained in this standard, they are not necessary for the measurement.
- b) The material used for the packing strips affects the apparent tensile strength measured. This has led to the decision to standardize on hardboard strips, since they provided the lowest standard deviations.
- c) The apparent tensile strength measured depends upon the shape and size of the test specimen used:
 - 1) cubes gave higher measured tensile strengths than cylinders, by approximately 10 %;
 - 2) 150 mm cubes gave lower measured tensile strengths than 100 mm cubes;
 - 3) the effect of cylinder size on measured tensile strength was not found to be significant, possibly due to the variability of the data.

As a result of these conclusions from the laboratory programme, this standard restricts the measurement of tensile splitting strength to cylindrical specimens used with hardboard packing strips, which is the reference method. However, as some countries still test cubical or prismatic specimens, their use has been retained in a normative annex. In cases of dispute, the reference method is the use of cylinders of 150 mm diameter and 300 mm length.

It is recognized good practice to include measurement of density prior to the determination of tensile splitting strength, as a check on compaction.

1 Scope

This European Standard specifies a method for the determination of the tensile splitting strength of cylindrical test specimens of hardened concrete. A method using cubic or prismatic specimens is included in normative Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12350-1, *Testing fresh concrete — Part 1: Sampling*

EN 12390-1, *Testing hardened concrete — Part 1: Shape, dimensions and other requirements of specimens and moulds*

EN 12390-2, *Testing hardened concrete — Part 2: Making and curing specimens for strength tests*

EN 12390-4, *Testing hardened concrete — Part 4: Compressive strength — Specification for testing machines*

EN 316, *Wood fibre boards — Definition, classification and symbols*

3 Principle

A cylindrical specimen is subjected to a compressive force applied to a narrow region along its length. The resulting orthogonal tensile force causes the specimen to fail in tension.

4 Apparatus

4.1 Testing machine, conforming to EN 12390-4, curved steel loading pieces may be used in place of conventional plane platens, when tests are carried out on cubic or prismatic specimen.

4.2 Jig (optional), for positioning the specimen and the packing strips. The jig shall not restrict the deformation of the specimen during the test.

NOTE Suitable jig for cylindrical specimens is shown in Figure 1.

4.3 Packing strips, conforming to EN 316, made of hardboard, of density equal or greater than 900 kg/m^3 and dimensions, width (a) = $(15 \pm 1) \text{ mm}$; thickness (t) = $(4 \pm 1) \text{ mm}$ and a length greater than the length of the line of contact of the test specimen.

Alternatively, packing strips may be used if they meet the following hardness criterion:

When submitted to a punching test by means of a rod of circular cross section, having a diameter of $(16 \pm 0,5) \text{ mm}$ and applying a force at a rate of $(48 \pm 10) \text{ kN/min}$, the instantaneous penetration when the force of $(20 \pm 5) \text{ kN}$ is achieved shall be equal to $(1,2 \pm 0,4) \text{ mm}$.

Packing strips shall be used only once.