

Methods of test for screed materials - Part 3:  
Determination of wear resistance - Böhme

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 13892-3:2015 sisaldab Euroopa standardi EN 13892-3:2014 ingliskeelset teksti.	This Estonian standard EVS-EN 13892-3:2015 consists of the English text of the European standard EN 13892-3:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.12.2014.	Date of Availability of the European standard is 17.12.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 91.100.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

## English Version

**Methods of test for screed materials - Part 3: Determination of wear resistance - Böhme**

Méthodes d'essai des matériaux pour chapes - Partie 3:  
Détermination de la résistance à l'usure Böhme

Prüfverfahren für Estrichmörtel und Estrichmassen - Teil 3:  
Bestimmung des Verschleißwiderstandes nach Böhme

This European Standard was approved by CEN on 16 November 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	3
1 <b>Scope</b> .....	4
2 <b>Normative references</b> .....	4
3 <b>Principle</b> .....	4
4 <b>Symbols and abbreviations</b> .....	4
5 <b>Apparatus</b> .....	4
6 <b>Abrasive material</b> .....	7
7 <b>Preparation of specimens</b> .....	7
8 <b>Testing</b> .....	8
8.1 <b>General</b> .....	8
8.2 <b>Determination of density</b> .....	8
8.3 <b>Procedure</b> .....	8
9 <b>Expression of results</b> .....	8
10 <b>Test report</b> .....	8
Bibliography .....	10

## Foreword

This document (EN 13892-3:2014) has been prepared by Technical Committee CEN/TC 303 "Floor screeds and screed materials", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2015 and conflicting national standards shall be withdrawn at the latest by June 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13892-3:2004.

In comparison with the previous edition, changes have been made in:

- Clause 6, 2<sup>nd</sup> paragraph and Table 2;
- Clause 7, 2<sup>nd</sup> paragraph.

EN 13892, *Methods of test for screed materials*, is divided in the following parts:

- *Part 1: Sampling, making and curing specimens for test;*
- *Part 2: Determination of flexural and compressive strength;*
- *Part 3: Determination of wear resistance – Böhme [the present document];*
- *Part 4: Determination of wear resistance-BCA;*
- *Part 5: Determination of wear resistance to rolling wheel of screed material for wearing layer;*
- *Part 6: Determination of surface hardness;*
- *Part 7: Determination of wear resistance to rolling wheel of screed material with floor coverings;*
- *Part 8: Determination of bond strength.*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard specifies a method for determining the wear resistance of moulded specimens made from cementitious screed material, primarily for hard aggregate wearing screed materials or optionally for other screed materials. The method is also suitable for specimens cut from floor screed. This method is unsuitable for synthetic resin screed materials.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 459-2, *Building lime - Part 2: Test methods*

EN 13813, *Screed material and floor screeds - Screed material - Properties and requirements*

EN 13892-1, *Methods of test for screed materials - Part 1: Sampling, making and curing specimens for test*

ISO 565, *Test sieves - Metal wire cloth, perforated metal plate and electroformed sheet - Nominal sizes of openings*

## 3 Principle

Cast specimens are placed on the Böhme abrader, on the test track of which standard abrasive is strewn, the disk then being rotated and the specimens subjected to an abrasive load of 294 N for a given number of cycles.

## 4 Symbols and abbreviations

$A = \Delta V$  is the wear resistance-Böhme in  $\text{cm}^3$  per  $50 \text{ cm}^2$  and the loss in volume after 16 cycles

$\Delta l = l_0 - l_{16m}$  is the mean reduction in mm after 16 cycles

$l_0$  is the mean thickness of the specimen in mm from the measurements made at all nine measuring points prior to testing

$l_{16m}$  is the mean thickness of the specimen in mm from the measurements made at all nine measuring points after completion of the test

$\Delta m$  is the reduction in mass in g after 16 cycles

$\rho_R$  is the density of the specimen in  $\text{g/cm}^3$  or, in the case of multi-layer specimens, the density of the wearing layer

## 5 Apparatus

The Böhme abrader as shown in Figure 1 consists of a rotating table with a defined test track to receive the abrasive, a specimen holder and a loading device.

The rotating table shall have a diameter of approximately 750 mm and be flat and positioned horizontally. When loaded, its speed shall be  $(30 \pm 1) \text{ r/min}$ .