

Plastid. Voolujuhtivate plastide eritakistuse määramine

Plastics - Measurement of resistivity of conductive
plastics

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 3915:2000 sisaldab Euroopa standardi EN ISO 3915:1999 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 11.01.2000 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 3915:2000 consists of the English text of the European standard EN ISO 3915:1999.</p> <p>This document is endorsed on 11.01.2000 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>This standard specifies the requirements for the laboratory testing of the resistivity of specially prepared specimens of plastics rendered conductive by the inclusion of carbon black. The test is suitable for materials of resistivity less than 166 ohm cm (104 ohm m). The result is not strictly a volume resistivity, because of surface conduction, but the effect of the latter are generally negligible.</p>	<p>Scope:</p> <p>This standard specifies the requirements for the laboratory testing of the resistivity of specially prepared specimens of plastics rendered conductive by the inclusion of carbon black. The test is suitable for materials of resistivity less than 166 ohm cm (104 ohm m). The result is not strictly a volume resistivity, because of surface conduction, but the effect of the latter are generally negligible.</p>
---	---

ICS 83.080.01

Võtmesõnad: laboratory tests, measurement, plastics, resistivity, test specimen, tests

ICS 83.080.00

English version

Plastics

Measurement of resistivity of conductive plastics
(ISO 3915 : 1981)

Plastiques – Mesurage de la
résistivité des plastiques
conducteurs (ISO 3915 : 1981)

Kunststoffe – Messung des
spezifischen elektrischen
Widerstandes von leitfähigen
Kunststoffen (ISO 3915 : 1981)

This European Standard was approved by CEN on 1999-05-06.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Foreword

International Standard

ISO 3915 : 1981 Plastics – Measurement of resistivity of conductive plastics, which was prepared by ISO/TC 61 'Plastics' of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 249 'Plastics', the Secretariat of which is held by IBN, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by December 1999 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3915 : 1981 was approved by CEN as a European Standard without any modification.

This document is a preview generated by EVS

0 Introduction

The method specified in this International Standard is technically similar to that specified for rubber in ISO 1853, *Conducting and antistatic rubbers — Measurement of resistivity*.

However, it differs from that method in certain details, especially those associated with the greater stiffness of the plastic samples, and in particular in the limitation on specimen width. It takes into account two problems encountered in the measurement of resistivity of conductive plastics, namely the sensitivity of these materials to their temperature-history and strain-history, and the difficulty of making adequate electrical contact with them.

The prescribed width of the specimen is mandatory for reference purposes; however, a wider strip may be used, with correspondingly wider electrodes. There is a danger in using a wide strip, if the strip is slightly twisted and at the same time somewhat non-uniform in its resistivity. It is then possible to obtain erroneous results; the potential electrode nearer to the positive current electrode may even be found to be negative with respect to the other potential electrode.

Effect of temperature changes and strain on conductive plastics

As mentioned above, the resistance of these materials is sensitive to their temperature-history and strain-history. The relationships are complex and arise from the kinetic energy and structural configuration of the carbon particles in the polymer.

The resistivity may be increased by the effects of strain produced by (or subsequent to) removal from the mould, and a treatment is described for reducing specimens to a constant strain and temperature condition before measurements are carried out on them. Specimens are also cut in two perpendicular directions to assess anisotropy.

Electrode systems (see 3.3)

Certain types of electrode, when applied to these polymers, have a contact resistance which may be many thousand times greater than the intrinsic resistance of the specimen. Dry contacts under light pressure or point contacts give very high resistances. However, the present test method eliminates the effects of contact resistances unless these are excessively high. (In such a case, no result, rather than a wrong one, is generally obtained.)

1 Scope and field of application

This International Standard specifies the requirements for the laboratory testing of the resistivity of specially prepared specimens of plastics rendered conductive by the inclusion of carbon black. The test is suitable for materials of resistivity less than $10^6 \Omega\cdot\text{cm}$ ($10^4 \Omega\cdot\text{m}$). The result is not strictly a volume resistivity, because of surface conduction, but the effects of the latter are generally negligible.

The principle of the four-terminal method of test is mandatory and the recommended specimen size and electrode design must be adhered to for reference purposes, but it may sometimes be necessary to test a wider strip with electrodes of a different construction.

2 Principle

A stable d.c. current of magnitude (I) is passed between electrodes at the two ends of a strip of the material under test. The voltage drop (ΔU) between two potential electrodes is measured with an electrometer. The resistance of the portion of the strip between the potential electrodes is given by $R = \Delta U/I$, and is independent of contact resistances. Thus the resistivity may be calculated.

3 Apparatus (see figure 1 for schematic diagram of test circuit)

3.1 Current source : a source of direct current which has a minimum resistance to earth of $10^{12} \Omega$ (effected by placing it on a highly insulating sheet), and which will not cause a dissipation of power greater than 0,1 W in the specimen.

3.2. Milliammeter or microammeter, as appropriate, for measuring the current to an accuracy of $\pm 5 \%$.

NOTE — Small currents may be computed from measurement of the voltage drop across a known resistance in series with the specimen, using the electrometer (3.4)

3.3 Electrodes

3.3.1 Current electrodes, of clean metal, together with either suitable clamps or grips approximately 5 mm long and extending across the full width of the specimen, or **conductive paint** to cover the same area.