
**Plastics — Acquisition and
presentation of comparable
multipoint data —**

Part 1:
Mechanical properties

*Plastiques — Acquisition et présentation de données multiples
comparables —*

Partie 1: Propriétés mécaniques



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Specimen preparation	2
5 Conditioning	3
6 Test requirements	4
6.1 General.....	4
6.2 Dynamic modulus: ISO 6721-2 or ISO 6721-4.....	4
6.3 Tensile properties at constant test speed: ISO 527-1 and ISO 527-2.....	4
6.4 Tensile creep: ISO 899-1.....	5
6.5 Charpy impact strength: ISO 179-1 or ISO 179-2.....	5
6.6 Puncture impact behaviour: ISO 6603-2.....	6
7 Presentation of data	6
8 Precision	8
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 2, *mechanical properties*.

This third edition cancels and replaces the second edition (ISO 11403-1:2001), which has been technically revised. The main changes are as follows:

- Annex A was deleted;
- ISO 3167 was deleted and ISO 20753 was added in the [Clause 2](#), Normative references.

ISO 11403 consists of the following parts, under the general title *Plastics — Acquisition and presentation of comparable multipoint data*:

- *Part 1: Mechanical properties*
- *Part 2: Thermal and processing properties*
- *Part 3: Environmental influences on properties*

Introduction

This International Standard has been prepared because users of plastics find sometimes that available data cannot be used readily to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this International Standard is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made.

ISO 10350 is concerned with single-point data. Such data represent the most basic method for characterizing materials and are useful for the initial stages of material selection. The present International Standard identifies test conditions and procedures for the measurement and presentation of a more substantial quantity of data. Each property here is characterized by multipoint data which demonstrate how that property depends upon important variables such as time, temperature and environmental effects. Additional properties are also considered in this standard. These data therefore enable more discriminating decisions to be made regarding a material's suitability for a particular application. Some data are also considered adequate for undertaking predictions of performance in service and of optimum processing conditions for moulding a component, although it should be recognized that, for purposes of design, additional data will often be needed. One reason for this is that some properties are strongly dependent upon the physical structure of the material. The test procedures referred to in this standard employ, where possible, the multipurpose tensile bar, and the polymer structure in this test specimen may be significantly different from that in specific regions of a moulded component. Under these circumstances, therefore, the data will not be suitable for accurate design calculations for product performance. The material supplier should be consulted for specific information on the applicability of data.

ISO 10350 and the various parts of this International Standard together define the means for acquiring and presenting a core set of comparable data for use in material selection. Use of these standards should result in a rationalization of effort and a reduction of cost associated with provision of these data. Furthermore, reference to these standards will simplify the development of data models for the computerized storage and exchange of data concerning material properties.

Where appropriate, values for test variables have been specified by this standard. For some tests however, owing to the wide range of conditions over which different plastics perform, the standard gives guidance in the selection of certain test conditions so that they cover the operating range for that polymer. Because, in general, the properties and performance specifications for different polymers differ widely, there is no obligation to generate data under all the test conditions specified in this standard.

Data on a wide range of properties are needed to enable plastics to be selected and used in the large variety of applications to which they are suited. ISO standards describe experimental procedures which are suitable for the acquisition of relevant information on many of these properties. The standard has therefore been divided into parts so that each part can be developed independently. In this way, additional properties can be included as new or revised standards become available.

Plastics — Acquisition and presentation of comparable multipoint data —

Part 1: Mechanical properties

1 Scope

This part of ISO 11403 specifies test procedures for the acquisition and presentation of multipoint data on the following mechanical properties of plastics:

- dynamic modulus;
- tensile properties at constant test speed;
- ultimate stress and strain;
- tensile stress-strain curves;
- tensile creep;
- Charpy impact strength;
- puncture impact behaviour.

The test methods and test conditions apply predominantly to those plastics that can be injection- or compression-moulded or prepared as sheets of specified thickness from which specimens of the appropriate size can be machined.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*