

**Petroleum and related products -
Determination of the ageing behaviour of
inhibited oils and fluids - TOST test - Part 1:
Procedure for mineral oils**

Petroleum and related products - Determination of
the ageing behaviour of inhibited oils and fluids -
TOST test - Part 1: Procedure for mineral oils

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 4263-1:2005 sisaldab Euroopa standardi EN ISO 4263-1:2004 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 22.02.2005 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 4263-1:2005 consists of the English text of the European standard EN ISO 4263-1:2004.</p> <p>This document is endorsed on 22.02.2005 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>This part of ISO 4263 specifies a method for the determination of the ageing behaviour of rust- and oxidationinhibited mineral oils having a density less than that of water, used as turbine oils (categories TSA, TGA, TSE, TGE of ISO 6743-5, see [4] in the Bibliography), hydraulic oils (categories HL, HM, HR, HV, HG of ISO 6743-4, see [3] in the Bibliography), and circulating oils (category CKB of ISO 6743-6, see [5] in the Bibliography). Oils containing synthetic components can be tested by this procedure, but no precision statement is available yet for such fluids.</p>	<p>Scope:</p> <p>This part of ISO 4263 specifies a method for the determination of the ageing behaviour of rust- and oxidationinhibited mineral oils having a density less than that of water, used as turbine oils (categories TSA, TGA, TSE, TGE of ISO 6743-5, see [4] in the Bibliography), hydraulic oils (categories HL, HM, HR, HV, HG of ISO 6743-4, see [3] in the Bibliography), and circulating oils (category CKB of ISO 6743-6, see [5] in the Bibliography). Oils containing synthetic components can be tested by this procedure, but no precision statement is available yet for such fluids.</p>
--	--

ICS 75.100

Võtmesõnad:

English version

Petroleum and related products

**Determination of the ageing behaviour of inhibited oils
and fluids – TOST test**

Part 1: Procedure for mineral oils
(ISO 4263-1:2003)

Pétrole et produits connexes – Détermination du comportement au vieillissement des fluides et huiles inhibées – Essai TOST – Partie 1: Méthode pour les huiles minérales
(ISO 4263-1:2003)

Mineralölerzeugnisse und verwandte Produkte – Bestimmung des Alterungsverhaltens von inhibierten Ölen und Flüssigkeiten – TOST-Verfahren – Teil 1: Verfahren für Mineralöle
(ISO 4263-1:2003)

This European Standard was approved by CEN on 2004-12-21.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Management Centre: rue de Stassart 36, B-1050 Brussels

Foreword

International Standard

ISO 4263-1:2003 Petroleum and related products – Determination of the ageing behaviour of inhibited oils and fluids – TOST test – Part 1: Procedure for mineral oils,

which was prepared by ISO/TC 28 'Petroleum products and lubricants' of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 19 'Petroleum products, lubricants and related products', the Secretariat of which is held by NEN, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by June 2005 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland, and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 4263-1:2003 was approved by CEN as a European Standard without any modification.

Contents

Page

Foreword	2
1 Scope	3
2 Normative references	3
3 Principle	4
4 Reagents and materials	4
5 Apparatus	5
6 Sampling	8
7 Preparation of materials and apparatus	8
8 Procedure	10
9 Calculation	11
10 Expression of results	11
11 Precision	11
12 Test report	12
Annex A (normative) Liquid-in-glass thermometer specifications	13
Annex B (normative) Procedure for packaging and storage of catalyst coils	14
Annex C (informative) Method for the determination of the insolubles content of mineral oils	15
Annex D (informative) Appearance rating of catalyst coil wires	17
Annex E (informative) Determination of metals content	18
Bibliography	19

WARNING — The use of this part of ISO 4263 may involve hazardous materials, operations and equipment. This part of ISO 4263 does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this part of ISO 4263 to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This part of ISO 4263 specifies a method for the determination of the ageing behaviour of rust- and oxidation-inhibited mineral oils having a density less than that of water, used as turbine oils (categories TSA, TGA, TSE, TGE of ISO 6743-5, see [4] in the Bibliography), hydraulic oils (categories HL, HM, HR, HV, HG of ISO 6743-4, see [3] in the Bibliography), and circulating oils (category CKB of ISO 6743-6, see [5] in the Bibliography). Oils containing synthetic components can be tested by this procedure, but no precision statement is available yet for such fluids.

NOTE 1 For the purposes of this part of ISO 4263, the term "% (m/m)" is used to represent the mass fraction of a material.

NOTE 2 Other signs of oil deterioration, such as the formation of insoluble sludge, catalyst coil corrosion or decrease in pH value, may occur, which indicate oxidation of the oil, but are not reflected in the calculated oxidation lifetime. The correlation of these occurrences with field service is under investigation.

This test method is widely used in specifications and is considered of value in comparing the oxidation stability of oils that are prone to contamination with water. However, because of the large number of individual field-service applications, the correlation between the results of this test and actual service performance can vary markedly, and is best judged on experience.

The precision of this part of ISO 4263 for oxidation life was only determined on inhibited turbine oils, and applies to oxidation lives of 700 h to 3 900 h.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3170:—¹⁾, *Petroleum liquids — Manual sampling*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

1) To be published. (Revision of ISO 3170:1988)

ISO 6618:1997, *Petroleum products and lubricants — Determination of acid or base number — Colour-indicator titration method*

ISO 6619:1988, *Petroleum products and lubricants — Neutralization number — Potentiometric titration method*

ISO 7537:1997, *Petroleum products — Determination of acid number — Semi-micro colour-indicator titration method*

3 Principle

A test portion is reacted, in the absence of light, at 95 °C with oxygen in the presence of water and a steel and copper catalyst coil. Small aliquots of the oil are withdrawn at regular intervals and the acid number is measured (see Note 2 in Clause 1). The test is continued until an acid number of 2,0 mg of potassium hydroxide (KOH) per gram of test portion is reached and the number of hours is recorded as the oxidation life. For some requirements, the test may be discontinued at a fixed number of hours (e.g. 1 000 h) when the value of the acid number is still below 2,0 mg of KOH per gram of test portion.

4 Reagents and materials

4.1 Water, unless otherwise specified, in accordance with the requirements of grade 2 as defined in ISO 3696. Potable water means tap water, unless normal piped supplies are contaminated with particulate or highly soluble mineral content.

4.2 Heptane (C_7H_{16}), of minimum purity 99,75 %.

4.3 Acetone (CH_3COCH_3), of general purpose reagent grade (GPR).

4.4 Propan-2-ol ($CH_3CHOHCH_3$), of general purpose reagent grade (GPR).

4.5 Oxygen, of minimum purity 99,5 %. Supplied through a pressure-regulation system adequate to maintain the specified flow rate throughout the test duration.

Supply from an oxygen cylinder should be via a two-stage regulation system and a needle valve to improve the consistency of gas-flow regulation.

WARNING — Use oxygen only with equipment validated for oxygen service. Do not allow oil or grease to come into contact with oxygen and clean and inspect all regulators, gauges and control equipment. Check the oxygen-supply system regularly for leaks. If a leak is suspected, turn off immediately and seek qualified assistance.

4.6 Cleaning solutions

4.6.1 Strong oxidizing acid solution

The reference strong oxidizing cleaning solution on which precision was based, is chromosulfuric acid (see the following warning), but alternative non-chromium containing solutions, such as ammonium persulfate in concentrated sulfuric acid (8 g/l) have been found to give satisfactory cleanliness. A 10 % solution of three parts of hydrochloric acid (1 mol/l) and one part of orthophosphoric acid (concentrated GPR grade) removes iron oxide deposits.

WARNING — Chromosulfuric acid is a health hazard. It is toxic, a recognized carcinogen as it contains Cr(VI) compounds, highly corrosive and potentially hazardous in contact with organic materials. When using chromosulfuric acid cleaning solution, eye protection and protective clothing are essential. Never pipette the cleaning solution by mouth. After use, do not pour cleaning solution down the drain, but neutralize it with great care owing to the concentrated sulfuric acid present, and dispose of it in