

Steel and iron - Determination of total silicon content - Gravimetric method

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 439:2010 sisaldab Euroopa standardi EN ISO 439:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.06.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 21.04.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 439:2010 consists of the English text of the European standard EN ISO 439:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.06.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 21.04.2010.

The standard is available from Estonian standardisation organisation.

ICS 77.080.01

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

English Version

Steel and iron - Determination of total silicon content -
Gravimetric method (ISO 439:1994)

Aciers et fontes - Dosage du silicium total - Méthode
gravimétrique (ISO 439:1994)

Stahl und Eisen - Bestimmung des Gesamtsiliziumgehaltes
- Gravimetrisches Verfahren (ISO 439:1994)

This European Standard was approved by CEN on 18 March 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

The text of ISO 439:1994 has been prepared by Technical Committee ISO/TC 17 “Steel” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 439:2010 by Technical Committee ECISS/TC 102 “Methods of chemical analysis for iron and steel” the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2010, and conflicting national standards shall be withdrawn at the latest by October 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 439:1994 has been approved by CEN as a EN ISO 439:2010 without any modification.

Steel and iron — Determination of total silicon content — Gravimetric method

1 Scope

This International Standard specifies a gravimetric method for the determination of the total silicon content in steel and iron.

The method is applicable to silicon contents between 0,10 % (*m/m*) and 5,0 % (*m/m*) (see note 1).

NOTE 1 For samples containing molybdenum, niobium, tantalum, titanium, tungsten, zirconium or high levels of chromium, the results are less precise than for unalloyed steels (see annex A).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 377-2:1989, *Selection and preparation of samples and test pieces of wrought steels — Part 2: Samples for the determination of the chemical composition*.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests*.

3 Principle

Attack of a test portion by hydrochloric and nitric acids.

Conversion of acid-soluble silicon compounds to hydrated silicon dioxide by evaporation with perchloric acid until white fumes appear. Filtration of the hydrated silicon dioxide and acid-insoluble silicon compounds, ignition to form impure silicon dioxide and then weighing.

Treatment of the ignited residue with hydrofluoric and sulfuric acids, followed by ignition and weighing.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and grade 2 water as specified in ISO 3696.

4.1 Hydrochloric acid, ρ about 1,19 g/ml.

4.2 Hydrochloric acid, ρ about 1,19 g/ml, diluted 1 + 1.

4.3 Hydrochloric acid, ρ about 1,19 g/ml, diluted 1 + 19.

4.4 Nitric acid, ρ about 1,40 g/ml, diluted 3 + 1.

4.5 Hydrofluoric acid, ρ about 1,14 g/ml.