

INTERNATIONAL STANDARD

ISO
10119

Second edition
2002-05-01

Carbon fibre — Determination of density

Fibre de carbone — Détermination de la masse volumique



Reference number
ISO 10119:2002(E)

© ISO 2002

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Term and definition	1
4 Test specimens — General requirements	1
5 Conditioning and test conditions	2
6 Test methods	2
6.1 Method A: Liquid-displacement method	2
6.2 Method B: Sink/float method	5
6.3 Method C: Density-gradient column	6
7 Precision	7
8 Test report	8
Annex A (normative) Preparation of the density-gradient column	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10119 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This second edition cancels and replaces the first edition (ISO 10119:1992), which has been technically revised.

Annex A forms a normative part of this International Standard.

Carbon fibre — Determination of density

1 Scope

This International Standard specifies three methods for the determination of the density of carbon fibre yarn:

- method A: liquid-displacement method;
- method B: sink/float method;
- method C: density-gradient column method.

Method C is the reference method.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 1675, *Plastics — Liquid resins — Determination of density by the pyknometer method*

ISO 10548, *Carbon fibre — Determination of size content*

3 Term and definition

For the purposes of this International Standard, the following term and definition apply.

3.1

density

the mass per unit volume of a substance at a specified temperature

NOTE This property is expressed in grams per cubic centimetre or in kilograms per cubic metre at the specified temperature. The recommended temperature is 23 °C.

4 Test specimens — General requirements

Test specimens shall be taken from desized samples unless otherwise agreed between the supplier and the customer. To remove the size, use the solvent extraction, chemical digestion or pyrolysis method specified in ISO 10548. The determination of the density may also be carried out on sized fibre by agreement between customer and supplier. The density of sized fibre may be taken to be identical to that of unsized fibre when the size content is low.