Plastics - Acquisition and presentation of comparable multipoint data - Part 3: Environmental influences on 3: 3-3:2\ Bellion Ochological Alberta properties (ISO 11403-3:2014)



#### **EESTI STANDARDI EESSÕNA**

#### **NATIONAL FOREWORD**

See Eesti standard EVS-EN ISO 11403-3:2014 sisaldab Euroopa standardi EN ISO 11403-3:2014 inglisekeelset teksti.	This Estonian standard EVS-EN ISO 11403-3:2014 consists of the English text of the European standard EN ISO 11403-3:2014.		
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.		
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 18.06.2014.	Date of Availability of the European standard is 18.06.2014.		
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.		

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

#### Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

#### The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation: Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

## EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

**EN ISO 11403-3** 

June 2014

ICS 83.080.01

Supersedes EN ISO 11403-3:2001

#### **English Version**

# Plastics - Acquisition and presentation of comparable multipoint data - Part 3: Environmental influences on properties (ISO 11403-3:2014)

Plastiques - Acquisition et présentation de données multiples comparables - Partie 3: Effets induits par l'environnement sur les propriétés (ISO 11403-3:2014) Kunststoffe - Ermittlung und Darstellung von vergleichbaren Vielpunkt-Kennwerten - Teil 3: Umgebungseinflüsse auf Eigenschaften (ISO 11403-3:2014)

This European Standard was approved by CEN on 7 June 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

#### **Foreword**

This document (EN ISO 11403-3:2014) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014, and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11403-3:2001.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

#### **Endorsement notice**

The text of ISO 11403-3:2014 has been approved by CEN as EN ISO 11403-3:2014 without any modification.

Co	ntent	ts	Page
Fore	eword		iv
Intr	oductio	on	v
1	Scop	oe	1
2	Norn	mative references	1
3	Tern	ns and definitions	2
4	Spec	cimen preparation	2
5	Cond	ditioning	3
6	6.1 6.2 6.3 6.4 6.5 6.6 6.7 6.8 6.9 6.10		3 4 4 4 4 4 5 5 auses A.4 6 7 7 8 8 8
7	6.11	Set of exposure conditions 3: Behind glass, high temperature	
7		cision	
8			
		nformative) Information relating to certain test requirements	
Ann	ex B (no resis	ormative) Chemicals for chemical resistance and environmental stress cracki stance tests	ing 13
Rihl		hy	

#### Introduction

This International Standard has been prepared because users of plastics find sometimes that available data cannot be used readily to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they often allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this International Standard is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made. These data are not necessarily suitable for design.

ISO 10350[4][5] is concerned with single-point data. Such data represent the most basic method for characterizing materials and are useful for the initial stages of material selection. The present International Standard identifies test conditions and procedures for the measurement and presentation of a more substantial quantity of data. Each property here is characterized by multipoint data which demonstrate how that property depends upon important variables such as time, temperature and environmental effects. Additional properties are also considered in this standard. These data therefore enable more discriminating decisions to be made regarding the material's suitability for a particular application. Some data are also considered adequate for undertaking predictions of performance in service and of optimum processing conditions for moulding a component, although it should be recognized that, for purposes of design, additional data will often be needed. One reason for this is that some properties are strongly dependent upon the physical structure of the material. The test procedures referred to in this standard employ standard test specimens, and the polymer structure in these specimens may be significantly different from that in specific regions of a moulded component. Under these circumstances, therefore, the data will not be suitable for accurate design calculations for product performance. The material supplier should be consulted for specific information on the applicability of data.

ISO 10350 and the various parts of this International Standard together define the means for acquiring and presenting a core set of comparable data for use in material selection. Use of these standards should result in a rationalization of effort and a reduction of cost associated with provision of these data. Furthermore, reference to these standards will simplify the development of data models for the computerized storage and exchange of data concerning material properties.

Where appropriate, values for test variables have been specified by this standard. For some tests however, owing to the wide range of conditions over which different plastics perform, the standard gives guidance in the selection of certain test conditions so that they cover the operating range for that polymer. Because, in general, the properties and performance specifications for different polymers differ widely, there is no obligation to generate data under all the test conditions specified in this standard.

Data on a wide range of properties are needed to enable plastics to be selected and used in the large variety of applications to which they are suited. ISO standards describe experimental procedures which are suitable for the acquisition of relevant information on many of these properties. For other properties, however, ISO standards either do not exist or exhibit shortcomings that complicate their use at present for the generation of comparable data (see <a href="#">Annex A</a>). The standard has therefore been divided into parts so that each part can be developed independently. In this way, additional properties can be included as new or revised standards become available.

# Plastics — Acquisition and presentation of comparable multipoint data —

#### Part 3:

### **Environmental influences on properties**

#### 1 Scope

This part of ISO 11403 specifies test procedures for the acquisition and presentation of multipoint data which demonstrate the behaviour of plastics under the following environments:

- prolonged exposure to heat;
- liquid chemicals;
- environmental stress cracking under a constant tensile stress;
- artificial weathering.

The tests are listed in order of increasing severity of the environment. By testing under the least severe environments first, it is possible to make informed judgements regarding whether tests under more severe conditions are worthwhile.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 175, Plastics — Methods of test for the determination of the effects of immersion in liquid chemicals

ISO 291, Plastics — Standard atmospheres for conditioning and testing

ISO 293, Plastics — Compression moulding of test specimens of thermoplastic materials

ISO 294-1, Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens

ISO 294-2, Plastics — Injection moulding of test specimens of thermoplastic materials — Part 2: Small tensile bars

ISO 295, Plastics — Compression moulding of test specimens of thermosetting materials

ISO 527-1, Plastics — Determination of tensile properties — Part 1: General principles

ISO 1268 (all parts), Fibre-reinforced plastics — Methods of producing test plates

ISO 1817, Rubber, vulcanized or thermoplastic — Determination of the effect of liquids

ISO 2578, Plastics — Determination of time-temperature limits after prolonged exposure to heat

ISO 2818, Plastics — Preparation of test specimens by machining

ISO 4892-2:2013, Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps

ISO 10724-1, Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles and moulding of multipurpose test specimens

ISO 10724-2, Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 2: Small plates

ISO 11403-1, Plastics — Acquisition and presentation of comparable multipoint data — Part 1: Mechanical properties

ISO 20753, Plastics — Test specimens

#### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

#### multipoint data

data characterizing the behaviour of a plastics material by means of a number of test results for a property measured over a range of test conditions

#### 3.2

#### indicative property

property that has been selected to reveal the influence of an environment on a material through a comparison of measurements of the property before and after exposure

#### 3.3

#### indicative data

ratios of mean values of indicative properties after and before exposure

Note 1 to entry: They give a measure of the severity of the influence of an environment on a material for specific exposure conditions (see <u>Clause A.1</u>).

#### 3.4

#### tensile work to break

 $W_{tF}$ 

area under a plot of the applied stress against the grip displacement in a tensile test, the applied stress being determined from the ratio of the tensile force to the minimum initial cross-sectional area of the specimen

Note 1 to entry: It is expressed in kilojoules per square metre  $(kJ/m^2)$ .

#### 4 Specimen preparation

In the preparation of specimens by injection or compression moulding, the procedures described in ISO 293, ISO 294-1, ISO 294-2, ISO 295, ISO 10724-1, ISO 10724-2 or ISO 1268 shall be used. The method of moulding and the conditions depend on the material being moulded. If these conditions are specified in the International Standard appropriate to the material, then they shall be adopted, where possible, for the preparation of every specimen on which data are obtained using this part of ISO 11403. For those plastics for which moulding conditions have not yet been standardized, the conditions employed shall be within the range recommended by the polymer manufacturer and shall, for each of the processing methods, be the same for every specimen. Where moulding conditions are not stipulated in any International Standard, the values used for the parameters in Table 1 shall be recorded with the data for that material.