

Founding - Ultrasonic examination - Part 3: Spheroidal graphite cast iron castings

Founding - Ultrasonic examination - Part 3:
Spheroidal graphite cast iron castings

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 12680-3:2003 sisaldab Euroopa standardi EN 12680-3:2003 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 18.02.2003 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 12680-3:2003 consists of the English text of the European standard EN 12680-3:2003.</p> <p>This document is endorsed on 18.02.2003 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>This European Standard specifies the requirements for the ultrasonic examination of spheroidal graphite cast iron castings and the methods for determining internal discontinuities by the pulse-echo technique. This European Standard does not deal with the ultrasonic examination of the nodularity of spheroidal graphite cast irons</p>	<p>Scope:</p> <p>This European Standard specifies the requirements for the ultrasonic examination of spheroidal graphite cast iron castings and the methods for determining internal discontinuities by the pulse-echo technique. This European Standard does not deal with the ultrasonic examination of the nodularity of spheroidal graphite cast irons</p>
---	---

ICS 77.040.20

Võtmesõnad: area, cast iron, def, definitions, determination, evaluations, finishes, foundries, foundry practice, nodular-graphite cast-iron, pulse replies, specification (approval), specifications, surface discontinuities, surfaces, testing, ultrasonic testing, wall thicknesses

ICS 77.040.20

English version

**Founding - Ultrasonic examination - Part 3: Spheroidal graphite
cast iron castings**

Fonderie - Contrôle par ultrasons - Partie 3: Pièces
moulées en fonte à graphite sphéroïdal

Gießereiwesen - Ultraschallprüfung - Teil 3: Gussstücke
aus Gusseisen mit Kugelgraphit

This European Standard was approved by CEN on 21 November 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Requirements	5
4.1 Order information	5
4.2 Extent of examination.....	5
4.3 Maximum permissible size of discontinuities.....	5
4.4 Personnel qualification	5
4.5 Wall section zones.....	5
5 Test method.....	5
5.1 Principles.....	5
5.2 Material.....	5
5.3 Equipment, coupling medium, calibration and sensitivity	6
5.4 Preparation of casting surfaces for examination	8
5.5 Examination procedure	8
5.6 Examination report	10
Bibliography	16

Foreword

This document (EN 12680-3:2003) has been prepared by Technical Committee CEN /TC 190 "Foundry Technology", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2003, and conflicting national standards shall be withdrawn at the latest by July 2003.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 4.10 "Inner defects" to prepare the following standard:

EN 12680-3, *Founding — Ultrasonic examination — Part 3: Spheroidal graphite cast iron castings.*

This is one of three European Standards for ultrasonic examination. The other standards are:

EN 12680-1, *Founding — Ultrasonic examination — Part 1: Steel castings for general purposes.*

EN 12680-2, *Founding — Ultrasonic examination — Part 2: Steel castings for highly stressed components.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the requirements for the ultrasonic examination of spheroidal graphite cast iron castings and the methods for determining internal discontinuities by the pulse-echo technique.

This European Standard does not deal with the ultrasonic examination of the nodularity of spheroidal graphite cast irons.

This European Standard does not cover the transmission technique.

NOTE The transmission technique has insufficient sensitivity to detect the discontinuities found in spheroidal graphite cast iron castings and is used in exceptional cases only.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 583-1, *Non-destructive testing — Ultrasonic examination — Part 1: General principles.*

EN 583-2, *Non-destructive testing — Ultrasonic examination — Part 2: Sensitivity and range setting.*

EN 583-3, *Non-destructive testing — Ultrasonic examination — Part 3: Transmission technique.*

EN 583-5, *Non-destructive testing — Ultrasonic examination — Part 5: Characterization and sizing of discontinuities.*

EN 1330-4, *Non-destructive testing — Terminology — Part 4: Terms used in ultrasonic testing.*

EN 12223, *Non-destructive testing — Ultrasonic examination — Specification for calibration block No. 1.*

EN 12668-1, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 1: Instruments.*

EN 12668-2, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 2: Probes.*

EN 12668-3, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 3: Combined equipment.*

EN 27963, *Welds in steel — Calibration block No. 2 for ultrasonic examination of welds (ISO 7963:1985).*

NOTE Informative references to documents used in the preparation of this standard, and cited at the appropriate places in the text, are listed in the bibliography.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 1330-4 apply.