

Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2016)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 6892-1:2016 sisaldab Euroopa standardi EN ISO 6892-1:2016 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 6892-1:2016 consists of the English text of the European standard EN ISO 6892-1:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 27.07.2016.	Date of Availability of the European standard is 27.07.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.040.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Metallic materials - Tensile testing - Part 1: Method of test
at room temperature (ISO 6892-1:2016)**

Matériaux métalliques - Essai de traction - Partie 1:
Méthode d'essai à température ambiante (ISO 6892-
1:2016)

Metallische Werkstoffe - Zugversuch - Teil 1:
Prüfverfahren bei Raumtemperatur (ISO 6892-1:2016)

This European Standard was approved by CEN on 15 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European Foreword

This document (EN ISO 6892-1:2016) has been prepared by Technical Committee ISO/TC 164 “Mechanical testing of metals” in collaboration with Technical Committee ECISS/TC 101 “Test methods for steel (other than chemical analysis)” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2017, and conflicting national standards shall be withdrawn at the latest by January 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6892-1:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6892-1:2016 has been approved by CEN as EN ISO 6892-1:2016 without any modification.

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	6
5 Principle	7
6 Test pieces	8
6.1 Shape and dimensions	8
6.1.1 General	8
6.1.2 Machined test pieces	8
6.1.3 Unmachined test pieces	9
6.2 Types	9
6.3 Preparation of test pieces	9
7 Determination of original cross-sectional area	9
8 Original gauge length and extensometer gauge length	10
8.1 Choice of the original gauge length	10
8.2 Marking the original gauge length	10
8.3 Choice of the extensometer gauge length	10
9 Accuracy of testing apparatus	10
10 Conditions of testing	11
10.1 Setting the force zero point	11
10.2 Method of gripping	11
10.3 Testing rates	11
10.3.1 General information regarding testing rates	11
10.3.2 Testing rate based on strain rate (method A)	11
10.3.3 Testing rate based on stress rate (method B)	13
10.3.4 Report of the chosen testing conditions	15
11 Determination of the upper yield strength	15
12 Determination of the lower yield strength	15
13 Determination of proof strength, plastic extension	15
14 Determination of proof strength, total extension	16
15 Method of verification of permanent set strength	16
16 Determination of the percentage yield point extension	16
17 Determination of the percentage plastic extension at maximum force	17
18 Determination of the percentage total extension at maximum force	17
19 Determination of the percentage total extension at fracture	17
20 Determination of percentage elongation after fracture	18
21 Determination of percentage reduction of area	18
22 Test report	19
23 Measurement uncertainty	20
23.1 General	20
23.2 Test conditions	20
23.3 Test results	20

Annex A (informative) Recommendations concerning the use of computer-controlled tensile testing machines	34
Annex B (normative) Types of test pieces to be used for thin products: sheets, strips, and flats between 0,1 mm and 3 mm thick	40
Annex C (normative) Types of test pieces to be used for wire, bars, and sections with a diameter or thickness of less than 4 mm	43
Annex D (normative) Types of test pieces to be used for sheets and flats of thickness equal to or greater than 3 mm and wire, bars, and sections of diameter or thickness equal to or greater than 4 mm	44
Annex E (normative) Types of test pieces to be used for tubes	48
Annex F (informative) Estimation of the crosshead separation rate in consideration of the stiffness (or compliance) of the testing equipment	50
Annex G (normative) Determination of the modulus of elasticity of metallic materials using a uniaxial tensile test	52
Annex H (informative) Measuring the percentage elongation after fracture if the specified value is less than 5 %	61
Annex I (informative) Measurement of percentage elongation after fracture based on subdivision of the original gauge length	62
Annex J (informative) Determination of the percentage plastic elongation without necking, A_{wn}, for long products such as bars, wire, and rods	64
Annex K (informative) Estimation of the uncertainty of measurement	65
Annex L (informative) Precision of tensile testing — Results from interlaboratory programmes	69
Bibliography	76

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*.

This second edition cancels and replaces the first edition (ISO 6892-1:2009), which has been technically revised with the following changes:

- a) renumbering of [Clause 10](#);
- b) additional information about the use of Method A and B;
- c) new denomination for:
 - 1) Method A closed loop → A1
 - 2) Method A open loop → A2;
- e) addition of [A.5](#);
- f) addition in Annex F for determination of the stiffness of the testing equipment;
- g) new normative Annex G: Determination of the modulus of elasticity of metallic materials using a uniaxial tensile test;
- h) the old Annex G is renamed to Annex H, Annex H to Annex I, etc.

ISO 6892 consists of the following parts, under the general title *Metallic materials — Tensile testing*:

- *Part 1: Method of test at room temperature*
- *Part 2: Method of test at elevated temperature*
- *Part 3: Method of test at low temperature*
- *Part 4: Method of test in liquid helium*

Introduction

During discussions concerning the speed of testing in the preparation of ISO 6892, it was decided to recommend the use of strain rate control in future revisions.

In this part of ISO 6892, there are two methods of testing speeds available. The first, method A, is based on strain rates (including crosshead separation rate) and the second, method B, is based on stress rates. Method A is intended to minimize the variation of the test rates during the moment when strain rate sensitive parameters are determined and to minimize the measurement uncertainty of the test results. Therefore, and out of the fact that often the strain rate sensitivity of the materials is not known, the use of method A is strongly recommended.

Metallic materials — Tensile testing —

Part 1: Method of test at room temperature

1 Scope

This part of ISO 6892 specifies the method for tensile testing of metallic materials and defines the mechanical properties which can be determined at room temperature.

NOTE Annex A contains further recommendations for computer controlled testing machines.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE In what follows, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, are used on various occasions (as figure axis labels or in explanations for the determination of different properties). However, for a general description or point on a curve, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, can be interchanged.

3.1 gauge length

L

length of the parallel portion of the test piece on which elongation is measured at any moment during the test

3.1.1 original gauge length

L_0

length between *gauge length* (3.1) marks on the test piece measured at room temperature before the test

3.1.2 final gauge length after fracture

L_u

length between *gauge length* (3.1) marks on the test piece measured after rupture, at room temperature, the two pieces having been carefully fitted back together so that their axes lie in a straight line