

Bituminous mixtures - Test methods for hot mix asphalt - Part 43: Resistance to fuel

Bituminous mixtures - Test methods for hot mix asphalt - Part 43: Resistance to fuel

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 12697-43:2005 sisaldab Euroopa standardi EN 12697-43:2005 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 15.07.2005 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 12697-43:2005 consists of the English text of the European standard EN 12697-43:2005.</p> <p>This document is endorsed on 15.07.2005 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>This European Standard specifies a test method to determine the resistance of a bituminous mixture or pavement to fuels. The procedure involves initial soaking of a test specimen made in the laboratory or cored from a pavement in a fuel, followed by a brushing period with a steel brush mounted in a mixer.</p>	<p>Scope:</p> <p>This European Standard specifies a test method to determine the resistance of a bituminous mixture or pavement to fuels. The procedure involves initial soaking of a test specimen made in the laboratory or cored from a pavement in a fuel, followed by a brushing period with a steel brush mounted in a mixer.</p>
--	--

ICS 93.080.20

Võtmesõnad: asphalts, brushes, carriageways, construction, fuels

ICS 93.080.20

English version

**Bituminous mixtures - Test methods for hot mix asphalt - Part
43: Resistance to fuel**

Mélanges bitumineux - Essais pour enrobés à chaud -
Partie 43: Résistance aux carburants

Asphalt - Prüfverfahren für Heiasphalt - Teil 43:
Treibstoffbestndigkeit

This European Standard was approved by CEN on 8 April 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	3
1 Scope	6
2 Normative references	6
3 Term and definition	6
4 Principle	6
5 Equipment	7
5.1 Fume cupboard	7
5.2 Beaker with glass rod	7
5.3 Glass funnel	7
5.4 Balance	7
5.5 Oven	7
5.6 Impact hammer or gyrator	7
5.7 Mixer	7
5.8 Steel brush	7
5.9 Connection pin between brush and mixer	8
5.10 Frame to press the specimen to the brush	8
6 Solvents	9
7 Preparation of test specimens	9
8 Procedure	10
8.1 Soaking in fuel and removing the fuel	10
8.1.1 Sample preparation	10
8.1.2 Immersion	10
8.1.3 Cleaning the specimen	10
8.1.4 Loss of mass due to immersion	10
8.2 The brush test	11
8.2.1 General	11
8.2.2 Brush test for a porous asphalt specimen	11
8.2.3 Brush test for a non-porous asphalt specimen	11
8.3 Calculation and expression of results	12
9 Test report	12
10 Precision	13
Bibliography	14

Foreword

This European Standard (EN 12697-43:2005) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2005, and conflicting national standards shall be withdrawn at the latest by November 2005.

This document is one of a series of standards as listed below:

EN 12697-1, *Bituminous mixtures — Test methods for hot mix asphalt — Part 1: Soluble binder content*

EN 12697-2, *Bituminous mixtures — Test methods for hot mix asphalt — Part 2: Determination of particle size distribution*

EN 12697-3, *Bituminous mixtures — Test methods for hot mix asphalt — Part 3: Bitumen recovery: Rotary evaporator*

EN 12697-4, *Bituminous mixtures — Test methods for hot mix asphalt — Part 4: Bitumen recovery: Fractionating column*

EN 12697-5, *Bituminous mixtures — Test methods for hot mix asphalt — Part 5: Determination of the maximum density*

EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-7, *Bituminous mixtures — Test methods for hot mix asphalt — Part 7: Determination of bulk density of bituminous specimens by gamma rays*

EN 12697-8, *Bituminous mixtures — Test methods for hot mix asphalt — Part 8: Determination of void characteristics of bituminous specimens*

EN 12697-9, *Bituminous mixtures — Test methods for hot mix asphalt — Part 9: Determination of the reference density*

EN 12697-10, *Bituminous mixtures — Test methods for hot mix asphalt — Part 10: Compactibility*

EN 12697-11, *Bituminous mixtures — Test methods for hot mix asphalt — Part 11: Determination of the affinity between aggregates and bitumen*

EN 12697-12, *Bituminous mixtures — Test methods for hot mix asphalt — Part 12: Determination of the water sensitivity of bituminous specimens*

EN 12697-13, *Bituminous mixtures — Test methods for hot mix asphalt — Part 13: Temperature measurement*

EN 12697-14, *Bituminous mixtures — Test methods for hot mix asphalt — Part 14: Water content*

EN 12697-15, *Bituminous mixtures — Test methods for hot mix asphalt — Part 15: Determination of the segregation sensitivity*

EN 12697-16, *Bituminous mixtures — Test methods for hot mix asphalt — Part 16: Abrasion by studded tyres*

EN 12697-17, *Bituminous mixtures — Test methods for hot mix asphalt — Part 17: Particle loss of porous asphalt specimen*

EN 12697-18, *Bituminous mixtures — Test methods for hot mix asphalt — Part 18: Binder drainage*

EN 12697-19, *Bituminous mixtures — Test methods for hot mix asphalt — Part 19: Permeability of specimen*

EN 12697-20, *Bituminous mixtures — Test methods for hot mix asphalt — Part 20: Indentation using cube or Marshall specimens*

EN 12697-21, *Bituminous mixtures — Test methods for hot mix asphalt — Part 21: Indentation using plate specimens*

EN 12697-22, *Bituminous mixtures — Test methods for hot mix asphalt — Part 22: Wheel tracking*

EN 12697-23, *Bituminous mixtures — Test methods for hot mix asphalt — Part 23: Determination of the indirect tensile strength of bituminous specimens*

EN 12697-24, *Bituminous mixtures — Test methods for hot mix asphalt — Part 24: Resistance to fatigue*

EN 12697-25, *Bituminous mixtures — Test methods for hot mix asphalt — Part 25: Cyclic compression test*

EN 12697-26, *Bituminous mixtures — Test methods for hot mix asphalt — Part 26: Stiffness*

EN 12697-27, *Bituminous mixtures — Test methods for hot mix asphalt — Part 27: Sampling*

EN 12697-28, *Bituminous mixtures — Test methods for hot mix asphalt — Part 28: Preparation of samples for determining binder content, water content and grading*

EN 12697-29, *Bituminous mixtures — Test methods for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen*

EN 12697-30, *Bituminous mixtures — Test methods for hot mix asphalt — Part 30: Specimen preparation by impact compactor*

EN 12697-31, *Bituminous mixtures — Test methods for hot mix asphalt — Part 31: Specimen preparation by gyratory compactor*

EN 12697-32, *Bituminous mixtures — Test methods for hot mix asphalt — Part 32: Laboratory compaction of bituminous mixtures by vibratory compactor*

EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*

EN 12697-34, *Bituminous mixtures — Test methods for hot mix asphalt — Part 34: Marshall test*

EN 12697-35, *Bituminous mixtures — Test methods for hot mix asphalt — Part 35: Laboratory mixing*

EN 12697-36, *Bituminous mixtures — Test methods for hot mix asphalt — Part 36: Determination of the thickness of a bituminous pavement*

EN 12697-37, *Bituminous mixtures — Test methods for hot mix asphalt — Part 37: Hot sand test for the adhesivity of binder on pre-coated chippings for hot rolled asphalt*

EN 12697-38, *Bituminous mixtures — Test methods for hot mix asphalt — Part 38: Common equipment and calibration*

EN 12697-39, *Bituminous mixtures — Test methods for hot mix asphalt — Part 39: Binder content by ignition*

prEN 12697-40, *Bituminous mixtures — Test methods for hot mix asphalt — Part 40: In-situ drainability*

EN 12697-41, *Bituminous mixtures — Test methods for hot mix asphalt — Part 41: Resistance to de-icing fluids*

EN 12697-42, *Bituminous mixtures — Test methods for hot mix asphalt — Part 42: Amount of foreign matter in reclaimed asphalt*

EN 12697-43, *Bituminous mixtures — Test methods for hot mix asphalt — Part 43: Resistance to fuel*

No existing European Standard is superseded.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies a test method to determine the resistance of a bituminous mixture or pavement to fuels. The procedure involves initial soaking of a test specimen made in the laboratory or cored from a pavement in a fuel, followed by a brushing period with a steel brush mounted in a mixer. The material loss of the specimen is a measure of the resistance to that fuel for that bituminous mixture.

NOTE The test is normally carried out with jet fuel.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-27, *Bituminous mixtures — Test methods for hot mix asphalt — Part 27: Sampling*

EN 12697-30, *Bituminous mixtures — Test methods for hot mix asphalt — Part 30: Specimen preparation by impact compactor*

EN 12697-31, *Bituminous mixtures — Test methods for hot mix asphalt — Part 31: Specimen preparation by gyratory compactor*

EN 12697-35, *Bituminous mixtures — Test methods for hot mix asphalt — Part 35: Laboratory mixing*

3 Term and definition

For the purposes of this European Standard, the following term and definition apply.

fuels

liquid (petroleum product) that might be spilled accidentally or sprayed deliberately onto an asphalt pavement and can cause damage to the asphalt mixture

4 Principle

A cylindrical test specimen with a known mass is immersed partly in a bath with the specified fuel for a specified period of time. For bituminous mixtures with paving grade bitumen this period is 24 h; for mixtures with a polymer-modified bitumen a 72 h period is used. After removal from the bath, cleaning with water and drying for 24 h in a ventilated oven at 25 °C, the loss of mass of the specimen is measured and the immersed surface is visually inspected. The type of affection and the material loss of the immersed surface are also recorded. Then the test specimen is put in a steel mould with the immersed surface up. At the bottom of the specimen a pneumatic cylinder pushes the immersed surface onto a steel brush, which is moving in epicycloids passages over the surface. After 30 s the brushing stops and the specimen is removed from the mould. Then the loss of mass is measured and the brushed surface is visually inspected. After that the specimen is put back in the mould and the same procedure is carried out again after 30 s and after 60 s, when the brushed surface is visually inspected again.

The total brushing time is 120 s (two brushing periods of 30 s and one of 60 s). The material loss after the immersion and/or the brush test is a measure for the resistance to that particular fuel.