

Plastid. Suitsu teke. Osa 2: Optilise tiheduse määramine ühe kambri katselt (ISO 5659-2:2012)

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO 5659-2:2012)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 5659-2:2012 sisaldab Euroopa standardi EN ISO 5659-2:2012 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 5659-2:2012 consists of the English text of the European standard EN ISO 5659-2:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.12.2012.	Date of Availability of the European standard is 01.12.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 13.220.40, 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO 5659-2:2012)

Plastiques - Production de fumée - Partie 2: Détermination de la densité optique par un essai en enceinte unique (ISO 5659-2:2012)

Kunststoffe - Rauchentwicklung - Teil 2: Bestimmung der optischen Dichte durch Einkammerprüfung (ISO 5659-2:2012)

This European Standard was approved by CEN on 30 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 5659-2:2012) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2013, and conflicting national standards shall be withdrawn at the latest by June 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 5659-1:1999 and EN ISO 5659-2:2006.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 5659-2:2012 has been approved by CEN as a EN ISO 5659-2:2012 without any modification.

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principles of the test	3
5 Suitability of a material for testing	3
5.1 Material geometry	3
5.2 Physical characteristics	3
6 Specimen construction and preparation	3
6.1 Number of specimens	3
6.2 Size of specimens	3
6.3 Specimen preparation	4
6.4 Wrapping of specimens	4
6.5 Conditioning	4
7 Apparatus and ancillary equipment	5
7.1 General	5
7.2 Test chamber	5
7.3 Specimen support and heating arrangements	9
7.4 Gas supply	14
7.5 Photometric system	15
7.6 Chamber leakage	17
7.7 Cleaning materials	17
7.8 Ancillary equipment	17
8 Test environment	18
9 Setting-up and calibration procedures	18
9.1 General	18
9.2 Alignment of photometric system	19
9.3 Selection of compensating filter(s)	19
9.4 Linearity check	20
9.5 Calibration of range-extension filter	20
9.6 Chamber leakage rate test	20
9.7 Burner calibration	20
9.8 Radiator cone calibration	21
9.9 Cleaning	21
9.10 Frequency of checking and calibrating procedure	21
10 Test procedure	22
10.1 General	22
10.2 Preparation of test chamber	22
10.3 Tests with pilot flame	22
10.4 Preparation of the photometric system	22
10.5 Loading the specimen	22
10.6 Recording of light transmission	23
10.7 Observations	23
10.8 Termination of test	24
10.9 Testing in different modes	24
11 Expression of results	25
11.1 Specific optical density D_s	25
11.2 Clear-beam correction factor D_c	25

12	Precision	25
13	Test report	26
Annex A (normative)	Calibration of heat flux meter	27
Annex B (informative)	Variability in the specific optical density of smoke measured in the single-chamber test	28
Annex C (informative)	Determination of mass optical density	30
Annex D (informative)	Precision data from tests on intumescent materials	35
Annex E (informative)	Guidance on optical density testing	37
Bibliography		45

Introduction

Fire is a complex phenomenon: its development and effects depend upon a number of interrelated factors. The behaviour of materials and products depends upon the characteristics of the fire, the method of use of the materials and the environment in which they are exposed (see also ISO/TR 3814^[1] and ISO 13943).

A test such as is specified in this part of ISO 5659 deals only with a simple representation of a particular aspect of the potential fire situation, typified by a radiant heat source, and it cannot alone provide any direct guidance on behaviour or safety in fire. A test of this type may, however, be used for comparative purposes or to ensure the existence of a certain quality of performance (in this case, smoke production) considered to have a bearing on fire behaviour generally. It would be wrong to attach any other meaning to results from this test.

The term “smoke” is defined in ISO 13943 as a visible suspension of solid and/or liquid particles in gases resulting from incomplete combustion. It is one of the first response characteristics to be manifested and should almost always be taken into account in any assessment of fire hazard as it represents one of the greatest threats to occupants of a building or other enclosure, such as a ship or train, on fire.

The responsibility for the preparation of ISO 5659 was transferred during 1987 from ISO/TC 92 to ISO/TC 61 on the understanding that the scope and applicability of the standard for the testing of materials should not be restricted to plastics but should also be relevant to other materials where possible, including building materials.

Plastics — Smoke generation —

Part 2:

Determination of optical density by a single-chamber test

1 Scope

1.1 This part of ISO 5659 specifies a method of measuring smoke production from the exposed surface of specimens of materials, composites or assemblies. It is applicable to specimens that have an essentially flat surface and do not exceed 25 mm in thickness when placed in a horizontal orientation and subjected to specified levels of thermal irradiance in a closed cabinet with or without the application of a pilot flame. This method of test is applicable to all plastics and may also be used for the evaluation of other materials (e.g. rubbers, textile-coverings, painted surfaces, wood and other materials).

1.2 It is intended that the values of optical density determined by this test be taken as specific to the specimen or assembly material in the form and thickness tested, and are not to be considered inherent, fundamental properties.

1.3 The test is intended primarily for use in research and development and fire safety engineering in buildings, trains, ships, etc. and not as a basis for ratings for building codes or other purposes. No basis is provided for predicting the density of smoke that might be generated by the materials upon exposure to heat and flame under other (actual) exposure conditions. This test procedure excludes the effect of irritants on the eye.

NOTE This test procedure addresses the loss of visibility due to smoke density, which generally is not related to irritancy potency (see Annex E).

1.4 It is emphasized that smoke production from a material varies according to the irradiance level to which the specimen is exposed. The results yielded from the method specified in this part of ISO 5659 are based on exposure to the specific irradiance levels of 25 kW/m² and 50 kW/m².

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13943, *Fire safety — Vocabulary*

ISO 14934-3, *Fire tests — Calibration and use of heat flux meters — Part 3: Secondary calibration method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 and the following apply.

3.1

assembly

fabrication of materials and/or composites

NOTE 1 Sandwich panels are an example of an assembly.

NOTE 2 The assembly may include an air gap.