

Hardmetals - Metallographic determination of microstructure - Part 4: Characterisation of porosity, carbon defects and eta-phase content (ISO 4499-4:2016)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 4499-4:2016 sisaldab Euroopa standardi EN ISO 4499-4:2016 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 4499-4:2016 consists of the English text of the European standard EN ISO 4499-4:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.03.2016.	Date of Availability of the European standard is 16.03.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.040.99, 77.160

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Hardmetals - Metallographic determination of
microstructure - Part 4: Characterisation of porosity,
carbon defects and eta-phase content (ISO 4499-4:2016)**

Métaux-durs - Détermination métallographique de la
microstructure - Partie 4: Caractérisation de la
porosité, des défauts carbone et de la teneur en phase
êta (ISO 4499-4:2016)

Hartmetalle - Metallographische Bestimmung der
Mikrostruktur - Teil 4: Charakterisierung von
Porosität, Kohlenstofffehlern und Anteil an Eta-Phase
(ISO 4499-4:2016)

This European Standard was approved by CEN on 4 February 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 4499-4:2016) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 24505:1993.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4499-4:2016 has been approved by CEN as EN ISO 4499-4:2016 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and Units	1
5 Principle	2
6 Apparatus	2
7 Calibration of measurement apparatus	2
8 Preparation of test samples	2
8.1 Methods of preparation	2
8.2 Characterisation of porosity and carbon (graphite) defects	3
8.3 Characterisation of eta-phase	3
9 Procedure	3
9.1 General	3
9.2 Determination of porosity	3
9.3 Determination of carbon defects	4
9.4 Determination of the η -phase (eta-phase)	7
10 Uncertainty of measurement	9
11 Test report	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 119, *Powder metallurgy*, Subcommittee SC 4, *Sampling and testing methods for hardmetals*.

This first edition of ISO 4499-4 cancels and replaces ISO 4505:1978, which has been technically revised.

ISO 4499 consists of the following parts, under the general title *Hardmetals — Metallographic determination of microstructure*:

- *Part 1: Photomicrographs and description*
- *Part 2: Measurement of WC grain size*
- *Part 3: Measurement of microstructural features in Ti (C,N) and WC/cubic carbide based hardmetals*
- *Part 4: Characterisation of porosity, carbon defects and eta-phase content*

Introduction

In standard WC/Co hardmetals, the chemistry, magnetic properties and density are generally controlled so that only two phases WC and Co are present.^{[1][2][3]} The Co phase is an alloy and contains some W and C in solid solution. The WC phase is stoichiometric. If the composition is either high or low in total carbon content, then it is possible to see a third phase in the structure. For high C, this is graphite; for low C, it is eta phase (η); typically, an M_6C or $M_{12}C$ carbide where M is (Co_xW_y) . This part of ISO 4499 is concerned with the detection and measurement of these microstructural features together with the measurement of porosity levels. Porosity is important since these materials are manufactured by a powder metallurgical route and although the technique of liquid phase sintering is used to consolidate the multiphase structure, low levels of porosity can arise in some instances and affect properties such as density and strength.

Hardmetals — Metallographic determination of microstructure —

Part 4: Characterisation of porosity, carbon defects and eta-phase content

1 Scope

This part of ISO 4499 specifies methods for the metallographic determination of the presence, type, and distribution of porosity, uncombined carbon and eta-phase in hardmetals.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4499-2:2008, *Hardmetals — Metallographic determination of microstructure — Part 2: Measurement of WC grain size*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

carbon defects

macroscopic precipitates of carbon (graphite) which can be in the form of large angular rosettes or small flakes

3.2

eta-phase

η -phase

cubic carbide based on M_6C or $M_{12}C$ structure where M is a mixture of Co and W usually in equal proportions; and which can be present as large (up to 100 μm diameter) rosettes or small micrometre-sized particles

4 Symbols and Units

ECD Equivalent Circle Diameter of a specified phase, in micrometres (μm)

L total line length in a specified phase, in millimetres (mm)

l_i measured length of individual intercepts in a specified phase, in micrometres (μm)

$\sum l_i$ sum of the measured length of each individual intercept

l_x arithmetic mean linear intercept in phase x, in micrometres (μm)