

Wool - Determination of fibre diameter - Projection microscope method (ISO 137:2015)

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

|   |  |
|---|--|
| See Eesti standard EVS-EN ISO 137:2015 sisaldab Euroopa standardi EN ISO 137:2015 ingliskeelset teksti.             | This Estonian standard EVS-EN ISO 137:2015 consists of the English text of the European standard EN ISO 137:2015.                  |
| Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas   | This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation. |
| Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.12.2015. | Date of Availability of the European standard is 16.12.2015.   |
| Standard on kättesaadav Eesti Standardikeskusest.   | The standard is available from the Estonian Centre for Standardisation.  |

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 59.060.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

ICS 59.060.10

English Version

## Wool - Determination of fibre diameter - Projection microscope method (ISO 137:2015)

Laine - Détermination du diamètre des fibres -  
Méthode du microscope à projection (ISO 137:2015)

Wolle - Bestimmung des Faserdurchmessers -  
Mikroskop-Projektionsverfahren (ISO 137:2015)

This European Standard was approved by CEN on 26 September 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## European foreword

This document (EN ISO 137:2015) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### Endorsement notice

The text of ISO 137:2015 has been approved by CEN as EN ISO 137:2015 without any modification.

# Contents

|   | Page      |
|---|-----------|
| <b>Foreword</b> .....   | <b>iv</b> |
| <b>1 Scope</b> .....  | <b>1</b>  |
| <b>2 Normative references</b> .....   | <b>1</b>  |
| <b>3 Terms and definitions</b> .....  | <b>1</b>  |
| <b>4 Principle</b> .....  | <b>1</b>  |
| <b>5 Apparatus</b> .....  | <b>2</b>  |
| <b>6 Sampling and preparation of the test specimens</b> .....                         | <b>5</b>  |
| 6.1 Raw wool.....   | 5         |
| 6.2 Slivers, rovings and yarns.....   | 5         |
| 6.3 Cutting of snippets.....  | 5         |
| 6.3.1 Using a fibre holder and pusher.....  | 5         |
| 6.3.2 Using a microtome.....  | 5         |
| 6.4 Mounting of test specimen.....  | 5         |
| <b>7 Test procedure</b> .....   | <b>6</b>  |
| 7.1 General.....  | 6         |
| 7.2 Examination of the test specimen.....   | 6         |
| 7.3 Focusing.....   | 7         |
| 7.4 Measuring the width of a fibre image.....   | 7         |
| 7.5 Recording of measurements.....  | 8         |
| <b>8 Measurement procedure</b> .....  | <b>8</b>  |
| <b>9 Calculation and expression of results</b> .....                                  | <b>8</b>  |
| <b>10 Test report</b> .....   | <b>9</b>  |
| <b>Annex A (informative) Example of calculation</b> .....                             | <b>10</b> |
| <b>Annex B (informative) Accuracy of results and confidence limits for mean</b> ..... | <b>12</b> |
| <b>Bibliography</b> .....   | <b>13</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This second edition cancels and replaces the first edition (ISO 137:1975), which has been technically revised.

This second edition to ISO 137 is based on the test method IWTO-8:2011, drawn up by the International Wool Textile Organization (IWTO).

# Wool — Determination of fibre diameter — Projection microscope method

## 1 Scope

This International Standard specifies the procedure and the measurement conditions for the determination of the wool fibre diameter using a projection microscope.

The method is suitable for wool fibres in any form and also for other fibres of reasonably circular cross-section. (In the case of dyed, bleached or finished fibres, the diameter might be different from that of fibres not subjected to such treatments. The estimates of fibre diameter obtained at the various stages of processing one lot of wool will not necessarily be the same.)

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1130:1975, *Textile fibres — Some methods of sampling for testing*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **mean diameter**

average value of the projected width of either the wool fibre or another fibre of reasonably circular cross-section

### 3.2

#### **total sample**

sample intended to be representative of a large bulk of material, in the state in which it is sent to the laboratory

Note 1 to entry: The total sample is prepared according to the procedure specified in ISO 1130.

### 3.3

#### **subsample**

sample randomly drawn from and representative of the total sample, which has been suitably cleaned, dried and conditioned where appropriate

### 3.4

#### **test specimen**

part of a subsample which is tested at one time

## 4 Principle

Projection on a screen of the magnified images of the profiles of wool fibre snippets, and measurement of their width by means of a graduated scale. The operating technique ensures a random sampling of the fibres to be measured.