
**Textiles- Determination of the fabric
propensity to surface pilling, fuzzing
or matting —**

**Part 3:
Random tumble pilling method**

*Textiles - Détermination de la propension des étoffes à l'ébouriffage en
surface et au boulochage —*

*Partie 3: Méthode de boulochage par projections aléatoires dans une
chambre cylindrique*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and auxiliary materials	2
5.1 Apparatus	2
5.2 Auxiliary materials	3
6 Conditioning and testing atmosphere	4
7 Preparation of test specimens	4
7.1 Pretreatment	4
7.2 Sampling	5
7.3 Fixation of specimen edges	5
7.4 Number of specimens and marking	5
8 Preparation of apparatus	5
8.1 Polychloroprene liners	5
9 Procedure	5
10 Assessment of pilling and/or fuzzing and/or matting	6
11 Results	7
12 Test report	7
Annex A (normative) Checking of apparatus and preparation of liners	9
Annex B (informative) Alternative procedure	10
Annex C (informative) Rationale	11
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 24, *Conditioning atmospheres and physical tests for textile fabrics*.

ISO 12945 consists of the following parts, under the general title *Textiles — Determination of fabric propensity to surface pilling, fuzzing or matting*:

- *Part 1: Pilling box method*
- *Part 2: Modified Martindale method*
- *Part 3: Random tumble pilling method*

Introduction

Pills are formed when fibres on a fabric surface “tease out” and become entangled during wear. Such surface deterioration is generally undesirable, but the degree of consumer tolerance for a given level of pilling will depend on the garment type and fabric end use.

Generally, the level of pilling which develops is determined by the rates of the following parallel processes:

- a) fibre entanglement leading to pill formation;
- b) development of more surface fibre;
- c) fibre and pill wear-off.

The rates of these processes depend on the fibre, yarn, and fabric properties. Examples of extreme situations are found in fabrics containing strong fibres versus fabric containing weak fibres. A consequence of the strong fibre is a rate of pill formation that exceeds the rate of wear-off. This results in an increase of pilling with an increase of wear. With a weak fibre, the rate of pill formation competes with the rate of wear-off. This would result in a fluctuation of pilling with an increase of wear. There are other constructions where surface fibre wear-off occurs before pill formation. Each of these examples demonstrates the complexity of evaluating the surface change on different types of fabric.

The ideal laboratory test would accelerate the wear processes a), b), and c) by exactly the same factor and would be universally applicable to all fibre, yarn, and fabric types. No such test has been developed. However, a test procedure has been established in which fabrics can be ranked in the same order of fuzzing and pilling propensity as is likely to occur in end use wear.

Particular attention is drawn to [Annex A](#) which gives advice on the maintenance and checking of the apparatus and liners. It is recommended that [Annex A](#) be studied prior to carrying out the procedure.

In Bibliography, some listed national standards have been taken into consideration as they refer to the use of the equipment, on which this part of ISO 12945 is based.

Textiles- Determination of the fabric propensity to surface pilling, fuzzing or matting —

Part 3: Random tumble pilling method

1 Scope

This part of ISO 12945 describes a method for the determination of the resistance to pilling, fuzzing, and matting of textile fabrics using the random tumble pilling tester. This method is applicable to most of woven and knitted fabrics, including napped fabrics (fleeces, inlay fabrics).

This method is not applicable to fabrics which cannot tumble freely.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply:

3.1

fuzzing

roughing up of the surface fibres and/or teasing out of the fibres from the fabric, which produces a visible surface change

Note 1 to entry: This change can occur during washing, dry cleaning, and/or wearing.

3.2

pills

entangling of fibres into balls (pills) which stand proud of the fabric and are of such density that light will not penetrate and will cast a shadow

Note 1 to entry: This change can occur during washing, dry cleaning, and/or wearing.

3.3

pilling

generation of pills over the surface of the fabric

3.4

jamming, wedging, or entanglement

when specimens either become entangled on the impeller or lie on the side of the cylinder wall resulting in the fabric not tumbling in the required random action