

Superconductivity - Part 21: Superconducting wires -  
Test methods for practical superconducting wires -  
General characteristics and guidance

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

|                                                                                                                     |                                                                                                                                    |
|---------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------|
| See Eesti standard EVS-EN 61788-21:2015 sisaldab Euroopa standardi EN 61788-21:2015 ingliskeelset teksti.           | This Estonian standard EVS-EN 61788-21:2015 consists of the English text of the European standard EN 61788-21:2015.                |
| Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas                                                   | This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation. |
| Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 03.07.2015. | Date of Availability of the European standard is 03.07.2015.                                                                       |
| Standard on kättesaadav Eesti Standardikeskusest.                                                                   | The standard is available from the Estonian Centre for Standardisation.                                                            |

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 17.220, 29.050, 77.040.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

ICS 17.220; 29.050; 77.040.10

English Version

Superconductivity - Part 21: Superconducting wires - Test  
methods for practical superconducting wires - General  
characteristics and guidance  
(IEC 61788-21:2015)

Supraconductivité - Partie 21: Fils supraconducteurs -  
Méthodes d'essai pour fils supraconducteurs à usage  
pratique - Caractéristiques générales et lignes directrices  
(IEC 61788-21:2015)

Supraleitfähigkeit - Teil 21: Supraleiterdrähte -  
Prüfverfahren für technische Supraleiterdrähte - Allgemeine  
Eigenschaften und Anleitung  
(IEC 61788-21:2015)

This European Standard was approved by CENELEC on 2015-06-23. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

## European foreword

The text of document 90/353/FDIS, future edition 1 of IEC 61788-21, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 61788-21:2015.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2016-03-23
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2018-06-23

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

## Endorsement notice

The text of the International Standard IEC 61788-21:2015 was approved by CENELEC as a European Standard without any modification.

## Annex ZA

(normative)

### Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cenelec.eu](http://www.cenelec.eu).

| <u>Publication</u> | <u>Year</u> | <u>Title</u>                                                                                                                                                         | <u>EN/HD</u> | <u>Year</u> |
|--------------------|-------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------|-------------|
| IEC 60050          | series      | International electrotechnical vocabulary                                                                                                                            | -            | -           |
| IEC 61788-1        | -           | Superconductivity -<br>Part 1: Critical current measurement - DC critical current of Nb-Ti composite superconductors                                                 | EN 61788-1   | -           |
| IEC 61788-2        | -           | Superconductivity -<br>Part 2: Critical current measurement - DC critical current of Nb <sub>3</sub> Sn composite superconductors                                    | EN 61788-2   | -           |
| IEC 61788-3        | -           | Superconductivity -<br>Part 3: Critical current measurement - DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors          | EN 61788-3   | -           |
| IEC 61788-4        | -           | Superconductivity -<br>Part 4: Residual resistance ratio measurement - Residual resistance ratio of Nb-Ti composite superconductors                                  | EN 61788-4   | -           |
| IEC 61788-5        | -           | Superconductivity -<br>Part 5: Matrix to superconductor volume ratio measurement - Copper to superconductor volume ratio of Cu/Nb-Ti composite superconducting wires | EN 61788-5   | -           |
| IEC 61788-6        | -           | Superconductivity -<br>Part 6: Mechanical properties measurement - Room temperature tensile test of Cu/Nb-Ti composite superconductors                               | EN 61788-6   | -           |

| <u>Publication</u> | <u>Year</u> | <u>Title</u>                                                                                                                                                                                                           | <u>EN/HD</u> | <u>Year</u> |
|--------------------|-------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------|-------------|
| IEC 61788-8        | -           | Superconductivity -<br>Part 8: AC loss measurements - Total AC loss measurement of round superconducting wires exposed to a transverse alternating magnetic field at liquid helium temperature by a pickup coil method | EN 61788-8   | -           |
| IEC 61788-10       | -           | Superconductivity -<br>Part 10: Critical temperature measurement - Critical temperature of composite superconductors by a resistance method                                                                            | EN 61788-10  | -           |
| IEC 61788-11       | -           | Superconductivity -<br>Part 11: Residual resistance ratio measurement - Residual resistance ratio of Nb <sub>3</sub> Sn composite superconductors                                                                      | EN 61788-11  | -           |
| IEC 61788-12       | -           | Superconductivity -<br>Part 12: Matrix to superconductor volume ratio measurement - Copper to non-copper volume ratio of Nb <sub>3</sub> Sn composite superconducting wires                                            | EN 61788-12  | -           |
| IEC 61788-13       | -           | Superconductivity -<br>Part 13: AC loss measurements - Magnetometer methods for hysteresis loss in superconducting multifilamentary composites                                                                         | EN 61788-13  | -           |
| IEC 61788-18       | -           | Superconductivity -<br>Part 18: Mechanical properties measurement - Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223 and Bi-2212 composite superconductors                                        | EN 61788-18  | -           |
| IEC 61788-19       | -           | Superconductivity -<br>Part 19: Mechanical properties measurement - Room temperature tensile test of reacted Nb <sub>3</sub> Sn composite superconductors                                                              | EN 61788-19  | -           |

## CONTENTS

|                                                                            |    |
|----------------------------------------------------------------------------|----|
| FOREWORD.....                                                              | 3  |
| INTRODUCTION.....                                                          | 5  |
| 1 Scope.....                                                               | 6  |
| 2 Normative references .....                                               | 6  |
| 3 Terms and definitions .....                                              | 7  |
| 4 Characteristic attributes of practical SC wires.....                     | 7  |
| 5 Categories of properties .....                                           | 7  |
| 6 Properties governed by IEC standards.....                                | 7  |
| 6.1 General.....                                                           | 7  |
| 6.2 Properties referring to the operation of SC wires.....                 | 7  |
| 6.3 Properties related to implementation and engineering .....             | 8  |
| Annex A (informative) Characteristic attributes of practical SC wires..... | 9  |
| A.1 General.....                                                           | 9  |
| A.2 Critical temperature .....                                             | 9  |
| A.3 Critical magnetic and irreversibility fields .....                     | 9  |
| A.4 Critical current and $n$ -value.....                                   | 10 |
| A.5 Stability.....                                                         | 10 |
| A.6 AC loss .....                                                          | 10 |
| A.7 Strain-dependent superconducting properties .....                      | 10 |
| A.8 Mechanical properties .....                                            | 11 |
| A.9 Uniformity of properties.....                                          | 11 |
| Bibliography.....                                                          | 12 |

## INTRODUCTION

Superconducting (SC) wires are a central and often enabling technology of many important industrial products. Consensus-based standards for SC wires greatly facilitate the creation of procurement specifications, design and engineering of components, certification of quality, description of operating devices, and generalization of use in industrial technologies.

This part of IEC 61788 is ranked as a first priority for both producers and users of superconducting technology: It provides the measurement methods and test procedures for properties critical to use. Adherence to normative information assists the development of commercial markets and the distribution of products. Standardization in this regard is meant to provide common access to, and unarguable reference information about, characteristics that are most important for superconductor-based technologies.

This part of IEC 61788 includes the measurement principles and measurement techniques together with the relevant terminology and definitions. Specifications of SC wire products take into account the function of the different components of SC wires to meet operational needs, maintain operational (superconducting) conditions, and accommodate mechanical forces and strains. The various forms of SC wire products distributed by manufacturers incorporate these aspects to varying degrees, depending on the superconducting materials used and the intended operating conditions/environment. Design and engineering of devices that use SC wire products take into account the unique properties of SC wires during operation. The general features of practical SC wires are described in IEC TR 61788-20 in terms of simple general characteristics to assist in the specification and use of superconducting wire products. Testing, certification, and quality control apply the relevant standard test methods to SC wires, which are specified in this part of IEC 61788.

## SUPERCONDUCTIVITY –

### Part 21: Superconducting wires – Test methods for practical superconducting wires – General characteristics and guidance

#### 1 Scope

This part of IEC 61788 specifies the test methods used for validating the mechanical, electrical, and superconducting properties of practical SC wires. A wire is considered as being practical if it can be procured in sufficiently continuous lengths under ordinary commercial transactions to build devices. Conductors made of multiple wires, such as cables, are not included in the scope of this part of IEC 61788. Extension of the discussions in this part of IEC 61788 beyond practical SC wires is not intended, even though referenced documents include aspects outside of this scope.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050 (all parts), *International Electrotechnical Vocabulary*. Available from: <http://www.electropedia.org>

IEC 61788-1, *Superconductivity – Part 1: Critical current measurement – DC critical current of Nb-Ti composite superconductors*

IEC 61788-2, *Superconductivity – Part 2: Critical current measurement – DC critical current of Nb<sub>3</sub>Sn composite superconductors*

IEC 61788-3, *Superconductivity – Part 3: Critical current measurement – DC critical current of Ag- and/or Ag alloy-sheathed Bi-2212 and Bi-2223 oxide superconductors*

IEC 61788-4, *Superconductivity – Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti composite superconductors*

IEC 61788-5, *Superconductivity – Part 5: Matrix to superconductor volume ratio measurement – Copper to superconductor volume ratio of Cu/Nb-Ti composite superconducting wires*

IEC 61788-6, *Superconductivity – Part 6: Mechanical properties measurement – Room temperature tensile test of Cu/Nb-Ti composite superconductors*

IEC 61788-8, *Superconductivity – Part 8: AC loss measurements – Total AC loss measurement of round superconducting wires exposed to a transverse alternating magnetic field at liquid helium temperature by a pickup coil method*

IEC 61788-10, *Superconductivity – Part 10: Critical temperature measurement – Critical temperature of composite superconductors by a resistance method*

IEC 61788-11, *Superconductivity – Part 11: Residual resistance ratio measurement – Residual resistance ratio of Nb<sub>3</sub>Sn composite superconductors*

IEC 61788-12, *Superconductivity – Part 12: Matrix to superconductor volume ratio measurement – Copper to non-copper volume ratio of Nb<sub>3</sub>Sn composite superconducting wires*

IEC 61788-13, *Superconductivity – Part 13: AC loss measurements – Magnetometer methods for hysteresis loss in superconducting multifilamentary composites*

IEC 61788-18, *Superconductivity – Part 18: Mechanical properties measurement – Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223 and Bi-2212 composite superconductors*

IEC 61788-19, *Superconductivity – Part 19: Mechanical properties measurement – Room temperature tensile test of reacted Nb<sub>3</sub>Sn composite superconductors*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in IEC 60050-815 apply.

### **4 Characteristic attributes of practical SC wires**

The primary purpose of electrical wires is to carry electrical current. Practical SC wires have the same intended purpose as common electrical wires, with the special ability to carry hundreds or thousands of times more current than a common electrical wire of the same dimension. Standard test methods discussed in this part of IEC 61788 address the determination of current-carrying capacity, called the critical current of practical SC wires. Several by-products of the special circumstances of practical SC wires also necessitate additional standards discussed in this part of IEC 61788 with respect to mechanical and thermal properties as well as properties in magnetic fields. The details are described in Annex A.

### **5 Categories of properties**

The properties necessary for the specification are categorized as follows:

- a) properties referring to the operation of SC wires, e.g. incurred during the initial cool-down to operating temperature, standard continuous operation, and under fault conditions;
- b) properties related to implementation and engineering, e.g. incurred during the fabrication and installation of a device.

With respect to the properties belonging to two categories, their principal test methods have been established as parts of IEC 61788 series indicated in Clause 6.

### **6 Properties governed by IEC standards**

#### **6.1 General**

Several attributes are governed by parts of the IEC 61788 series. Test methods for these attributes shall be used to settle disputes. When a new test method is established as a part of IEC 61788 series, it will be included in Clause 6.

#### **6.2 Properties referring to the operation of SC wires**

For the purpose of consultation, current parts of the IEC 61788 series related to specific properties shall be used to settle disputes. They are categorized in groups as follows.

- a) Critical temperature:
  - Critical temperature measurement – Critical temperature of composite superconductors by a resistance method (IEC 61788-10).