EHITUSLIKUD SOOJUSISOLATSIOONITOOTED. TÖÖSTUSLIKULT VALMISTATUD JÄIGAST VAHTPOLÜURETAANVAHUST (PU) TOOTED. SPETSIFIKATSIOON

Thermal insulation products for buildings - Factory made rigid polyurethane foam (PU) products - Specification



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13165:2012+A1:2015 sisaldab Euroopa standardi EN	This Estonian standard EVS-EN 13165:2012+A1:2015 consists of the English text
13165:2012+A1:2015 ingliskeelset teksti.	of the European standard EN 13165:2012+A1:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 18.02.2015.	Date of Availability of the European standard is 18.02.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

ICS 91.100.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Aru 10, 10317 Tallinn, Eesti; koduleht www.eys.ee; telefon 605 5050; e-post info@eys.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 13165:2012+A1

February 2015

ICS 91.100.60

Supersedes EN 13165:2012

English Version

Thermal insulation products for buildings - Factory made rigid polyurethane foam (PU) products - Specification

Produits isolants thermiques pour le bâtiment - Produits manufacturés en mousse rigide de polyuréthane (PU) -Spécification Wärmedämmstoffe für Gebäude - Werkmäßig hergestellte Produkte aus Polyurethan-Hartschaum (PU) - Spezifikation

This European Standard was approved by CEN on 6 October 2012 and includes Amendment 1 approved by CEN on 15 December 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Cont	ents	Page
Forew	ord	4
1	Scope	6
2	Normative references	6
3	Terms, definitions, symbols, units and abbreviated terms	7
4	Requirements	
5	Test methods	17
6	Designation code	20
7	Assessment and Verification of the Constancy of Performance (AVCP)	20
В	Marking and labelling	21
Annex	A (normative) Determination of the declared values of thermal resistance and thermal conductivity	23
A .1	General	23
A.2	Input data	23
A .3	Declared values	23
Annex	B (normative) A Product type determination (A) (A) PTD (A) and factory production control (FPC)	25
Annex	C (normative) Determination of the aged values of thermal resistance and thermal conductivity	
C.1	General	
C.2	Sampling and test specimen preparation	29
C.3	Determination of the initial value of thermal conductivity	30
C.4	Determination of the accelerated aged value of thermal conductivity	31
C.5	Fixed increment procedure	33
C.6	Declaration of the aged values of thermal resistance and thermal conductivity	35
Annex	D (normative) PU multi-layered insulation products	36
D.1	General	36
D.2	Requirements	36
D.3	Test methods	37
D.4	Evaluation of conformity	37
Annex	E (informative) Additional properties	38
E.1	General	38
E.2	Bending strength	38
E.3	Shear behaviour	38
E.4	Compressive stress at 2% deformation	38
E.5	Long term water absorption by diffusion	38
E.6	Freeze-thaw resistance	38

E.7	Apparent density	39
Annex	ZA (informative) A Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation	40
ZA.1	Scope and relevant characteristics	40
ZA.2	Procedures for AVCP of factory made rigid polyurethane foam products	42
ZA.3	CE Marking and labelling	48
Biblio	graphy	50
Tables		
Table '	1 — Tolerances on length and width	11
Table 2	2 — Classes for thickness tolerances	12
Table :	3 — Deviation from flatness	12
	4 — Test conditions for dimensional stability under specified temperature and humidity ions	13
Table :	5 — Levels for dimensional stability for test conditions 1, 2, 3	13
Table (6 — Levels for dimensional stability for test condition 4	14
Table 1	7 — Levels for deformation under specified compressive load and temperature conditions	14
Table 8	8 — Levels for compressive stress or compressive strength	15
Table 9	9 — Levels for tensile strength perpendicular to faces	15
Table '	10 — Levels for one sided wetting behaviour	16
Table '	11 — Test methods, test specimens and conditions	19
Table A	A.1 — Values for k for one sided 90 % tolerance interval with a confidence level of 90 %	24
Table I	B.1 — Minimum number of tests for \land PTD 🔄 and minimum product testing frequencies	25
Table I	B.2 — Minimum product testing frequencies for the reaction to fire characteristics	27
	C.1 — Safety increments to be added to the measured accelerated aged value of thermal ctivity	32
Table (C.2 — Increments for calculating the aged value of thermal conductivity	34
Table I	E.1 — Test methods, test specimens, conditions and minimum testing frequencies	39
Table 2	ZA.1 — Relevant clauses for factory made rigid polyurethane foam and intended use	41
Table 2	ZA.2 — Systems of AVCP	42
Table 2	ZA.3.1 — Assignment of AVCP tasks for factory made rigid polyurethane foam products system 1 for reaction to fire and system 3 (see Table ZA.2)	
	ZA.3.2 — Assignment of AVCP tasks for factory made rigid polyurethane foam products system 3 (see Table ZA.2)	44
	ZA.3.3 — Assignment of AVCP tasks for factory made rigid polyurethane foam products combined system 4 for reaction to fire and system 3 (see Table ZA.2)	44
Figure	s O'	
Figure	C.1 — Flow chart of the alternative ageing procedures	30
Figure	ZA.1 — Example CE marking information of products under AVCP system 1 and system 3	49

Foreword

This document (EN 13165:2012+A1:2015) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2015, and conflicting national standards shall be withdrawn at the latest by November 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes (A) EN 13165:2012 (A).

This document includes Amendment 1 approved by CEN on 2014-12-15.

The start and finish of text introduced or altered by amendment is indicated in the text by tags [A].

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Construction Products Regulation (CPR), see informative Annex ZA, which is an integral part of this standard. (4)

Compared with EN 13165:2008, the main changes are:

- a) better harmonisation between the different standards of the package (EN 13162 to EN 13171) on definitions, requirements, classes and levels;
- b) new normative annex on multi-layered products;
- c) changes on some editorial and technical content and addition of information on some specific items for PU products such as: PU product term, dimensional stability, point load (cancelled), water absorption, water vapour transmission:
- d) addition of links to EN 15715, Thermal insulation products Instructions for mounting and fixing for reaction to fire testing Factory made products;
- e) changes to the Annex ZA.
- Amendment 1 modifies EN 13165:2012 identifying those clauses of the standard which are needed for the compliance of the European Standard with the Construction Products Regulation (CPR).

2/5

This amendment introduces

- f) an addition to the foreword;
- g) an addition in 3.2;
- h) a new subclause 4.3.11;
- i) modification of Clause 7;
- j) modification of Clause 8;
- k) modification of Annex B;
- I) a new Annex ZA. (A)

This standard is one of a series of standards for thermal insulation products used in buildings, but this standard may be used in other areas where appropriate.

In pursuance of Resolution BT 20/1993 Revised, CEN/TC 88 has proposed defining the standards listed below as a package of documents.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

EN 13162, Thermal insulation products for buildings — Factory made mineral wool (MW) products — Specification

EN 13163, Thermal insulation products for buildings — Factory made expanded polystyrene (EPS) products — Specification

EN 13164, Thermal insulation products for buildings — Factory made extruded polystyrene foam (XPS) products — Specification

EN 13165, Thermal insulation products for buildings — Factory made rigid polyurethane foam (PU) products — Specification

EN 13166, Thermal insulation products for buildings — Factory made phenolic foam (PF) products — Specification

EN 13167, Thermal insulation products for buildings — Factory made cellular glass (CG) products — Specification

EN 13168, Thermal insulation products for buildings — Factory made wood wool (WW) products — Specification

EN 13169, Thermal insulation products for buildings — Factory made expanded perlite board (EPB) products — Specification

EN 13170, Thermal insulation products for buildings — Factory made products of expanded cork (ICB) — Specification

EN 13171, Thermal insulation products for buildings — Factory made wood fibre (WF) products — Specification

The reduction in energy used and emissions produced during the installed life of insulation products exceeds by far the energy used and emissions made during the production and disposal processes.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the requirements for factory made rigid polyurethane foam (PU) products, with or without facings or coatings, which are used for the thermal insulation of buildings. PU includes both PIR and PUR products. The products are manufactured in the form of boards.

(A) This European Standard includes PU multi-layered insulation products, see Annex D. (A)

Products covered by this standard are also used in prefabricated thermal insulation systems and (A) composite insulation products (A); the performance of systems incorporating these products is not covered.

This standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

This standard does not specify the required level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application are to be found in regulations or non-conflicting standards.

Products with a declared thermal resistance lower than 0,25 m²·K/W or a declared thermal conductivity greater than 0,060 W/(m·K) at 10 °C are not covered by this European Standard.

This standard does not cover in situ insulation products and products intended to be used for the insulation of building equipment and industrial installations (covered by EN 14308).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- EN 822, Thermal insulating products for building applications Determination of length and width
- EN 823, Thermal insulating products for building applications Determination of thickness
- EN 824, Thermal insulating products for building applications Determination of squareness
- EN 825, Thermal insulating products for building applications Determination of flatness
- EN 826, Thermal insulating products for building applications Determination of compression behaviour
- EN 1604, Thermal insulating products for building applications Determination of dimensional stability under specified temperature and humidity conditions
- EN 1605, Thermal insulating products for building applications Determination of deformation under specified compressive load and temperature conditions
- EN 1606, Thermal insulating products for building applications Determination of compressive creep
- EN 1607, Thermal insulating products for building applications Determination of tensile strength perpendicular to faces
- EN 1609, Thermal insulating products for building applications Determination of short term water absorption by partial immersion
- EN 12086:1997, Thermal insulating products for building applications Determination of water vapour transmission properties

EN 12087, Thermal insulating products for building applications — Determination of long term water absorption by immersion

EN 12667:2001, Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Products of high and medium thermal resistance

EN 12939, Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance

EN 13172:2012, Thermal insulating products — Evaluation of conformity

EN 13501-1, Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests

EN 13820, Thermal insulating materials for building applications — Determination of organic content

EN 13823, Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item

EN 15715:2009, Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing - Factory made products

EN ISO 354, Acoustics — Measurement of sound absorption in a reverberation room (ISO 354)

EN ISO 1182, Reaction to fire tests for building products — Non-combustibility test (ISO 1182)

EN ISO 1716, Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value) (ISO 1716)

EN ISO 4590, Rigid cellular plastics — Determination of the volume percentage of open cells and closed cells(ISO 4590)

EN ISO 9229:2007, Thermal insulation — Vocabulary (ISO 9229:2007)

EN ISO 11654, Acoustics — Sound absorbers for use in buildings — Rating of sound absorption (ISO 11654)

EN ISO 11925-2, Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2)

ISO 16269-6:2005, Statistical interpretation of data — Part 6: Determination of statistical tolerance intervals

3 Terms, definitions, symbols, units and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 9229:2007 apply with exception or in addition of the following:

3.1.1

rigid polyurethane foam (PU)

family of rigid cellular thermoset polymeric insulation products with a substantially closed cell structure including both polymer types based on PIR and PUR