

## **Plaadiliimid. Libisemise määramine**

Adhesives for tiles - Determination of slip

**EESTI STANDARDI EESSÕNA****NATIONAL FOREWORD**

Käesolev Eesti standard EVS-EN 1308:2007 sisaldb Euroopa standardi EN 1308:2007 ingliskeelset teksti.	This Estonian standard EVS-EN 1308:2007 consists of the English text of the European standard EN 1308:2007.
Käesolev dokument on jõustatud 30.10.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.	This document is endorsed on 30.10.2007 with the notification being published in the official publication of the Estonian national standardisation organisation.
Standard on kättesaadav Eesti standardiorganisatsioonist.	The standard is available from Estonian standardisation organisation.

**Käsitlusala:**

See Euroopa standard määrab kindlaks teimimeetodi, mille abil määritatakse, kuidas kahliliim peab vastu kahli libisemisele püstseinal. Seda standardit saab rakendada kõigi kahliliimide korral kahlite paigaldamiseks seintele sise- ja välistingimustes. See Euroopa standard ei sisalda käitusnöudeid ega soovitusi kahlite projekteerimiseks ja paigaldamiseks.

**Scope:**

This European Standard specifies the test method to be used to determine the adhesive's resistance to slip of a ceramic tile on a vertical wall. This European Standard applies to all ceramic tile adhesives for internal and external tiling on walls.

**ICS** 83.180, 91.100.10

**Võtmesõnad:** keraamika, libisemine, liim, plaadid, teimid, teimiolud

**EUROPEAN STANDARD**  
**NORME EUROPÉENNE**  
**EUROPÄISCHE NORM**

**EN 1308**

August 2007

ICS 83.180; 91.100.10

Supersedes EN 1308:1996

English Version

**Adhesives for tiles - Determination of slip**

Colles à carrelage - Détermination du glissement

Mörtel und Klebstoffe für Fliesen und Platten - Bestimmung  
des Abrutschens

This European Standard was approved by CEN on 21 January 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

**Contents**

	Page
<b>Foreword</b> .....	<b>3</b>
1 <b>Scope</b> .....	4
2 <b>Normative references</b> .....	4
3 <b>Sampling</b> .....	4
4 <b>Test conditions</b> .....	4
5 <b>Test materials</b> .....	4
5.1 <b>General</b> .....	4
5.2 <b>Ceramic tiles</b> .....	4
5.3 <b>Concrete slab</b> .....	5
6 <b>Apparatus</b> .....	5
6.1 <b>Steel straight edge</b> .....	5
6.2 <b>Clamps</b> .....	5
6.3 <b>Masking tape</b> .....	5
6.4 <b>Notched trowel</b> .....	5
6.5 <b>Spacers</b> .....	5
6.6 <b>Weight</b> .....	5
6.7 <b>Vernier caliper</b> .....	5
7 <b>Mixing of the adhesive</b> .....	5
8 <b>Procedure</b> .....	6
9 <b>Test report</b> .....	6

## Foreword

This document (EN 1308:2007) has been prepared by Technical Committee CEN/TC 67 "Ceramic tiles", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

This document supersedes EN 1308:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This European Standard specifies the method for the determination of the resistance to slip of a tile applied to an adhesive on a vertical surface.

This European Standard applies to all ceramic tile adhesives for internal and external tiling on walls.

This European Standard does not contain performance requirements or recommendations for the design and installation of ceramic tiles.

**NOTE** Ceramic tile adhesives can be used also for other kinds of tiles (natural and agglomerated stones etc.), if they do not adversely affect the stones.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2005, *Methods of testing cement — Part 1: Determination of strength*

EN 1067, *Adhesives — Examination and preparation of samples for testing*

EN 1323, *Adhesives for tiles — Concrete slabs for tests*

EN 14411, *Ceramic tiles — Definitions, classification, characteristics and marking*

EN ISO 15605, *Adhesives — Sampling (ISO 15605:2000)*

## 3 Sampling

Take at least 2 kg sample of the adhesive in accordance with EN ISO 15605 and EN 1067.

## 4 Test conditions

Standard conditions shall be  $(23 \pm 2)^\circ\text{C}$  and  $(50 \pm 5)\%$  relative humidity and the speed of air in the testing area less than 0,2 m/s.

## 5 Test materials

### 5.1 General

Condition all test materials for at least 24 h under standard conditions.

The adhesive to be tested shall be within its shelf life, where this is specified.

### 5.2 Ceramic tiles

The tiles shall be checked prior to conditioning to ensure that they are new, clean and dry.