
**Clothing for protection against contact
with blood and body fluids —
Determination of resistance of protective
clothing materials to penetration by
blood-borne pathogens — Test method
using Phi-X174 bacteriophage**

Vêtements de protection contre les contacts avec le sang et les fluides corporels — Détermination de la résistance à la pénétration par des pathogènes véhiculés par le sang des matériaux entrant dans la fabrication des vêtements de protection — Méthode d'essai utilisant le bactériophage Phi-X174



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	4
5 Microorganisms and reagents	4
6 Apparatus and materials	5
7 Test specimens	6
7.1 Selection	6
7.2 Preparation of test specimens	6
8 Procedure	6
8.1 Preparation of test media	6
8.2 Preparation of controls	7
8.3 Determination of material compatibility	8
8.4 Procedure for preparation of bacteriophage suspension	8
8.5 Preparation of settle plates	9
8.6 Preliminary material measures	9
8.7 Preparation of test cell	9
8.8 Exposure of material to bacteriophage challenge suspension	10
8.9 Procedure for quantification of assay fluid	11
8.10 Interpretation of tests results	12
9 Test report	12
Annex A (informative) Sources of supplies and apparatus	15
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16604 was prepared by Technical Committee ISO/TC 94, *Personal safety — Protective clothing and equipment*, Subcommittee SC 13, *Protective clothing*. It is based on ASTM F1671-97b.

Introduction

Workers, primarily those in the health care profession, involved in treating and caring for individuals injured or sick, can be exposed to biological liquids capable of transmitting disease. These diseases, which may be caused by a variety of microorganisms, can pose significant risks to life and health. This is especially true of blood-borne viruses which cause hepatitis [hepatitis B virus (HBV) and hepatitis C virus (HCV)] and acquired immune deficiency syndrome (AIDS) [human immunodeficiency viruses (HIV)]. Since engineering controls cannot eliminate all possible exposures, attention is placed on reducing the potential of direct skin contact through the use of protective clothing.

This International Standard is concerned with protective clothing and related protective devices designed to protect against the penetration of blood or body fluids.

Given the variety of health care settings, activities, and the potential for exposure to blood or body fluids, the barrier requirements for protective clothing materials will change with the application.

This International Standard describes a hydrostatic pressure test for measuring the viral penetration resistance of clothing materials to a surrogate virus. The choice of an appropriate test method depends on the specific application of protective clothing and its intended use. A risk assessment should be performed to determine the level of risk for determining the appropriate test method.^[1]

This test method does not apply to all forms or conditions of blood-borne pathogen exposure. Users of this test method should review modes for worker clothing exposure and assess the appropriateness of this test method for their specific applications. This test method has been specifically defined for modelling the viral penetration of hepatitis (B and C) and human immunodeficiency viruses transmitted in blood and other potentially infectious body fluids. The surrogate microbe, Phi-X174 bacteriophage, used in this test method, is similar to HCV in size and shape but also serves as a surrogate for HBV and HIV. Inferences for protection from other pathogens should be assessed on a case-by-case basis.

This test method addresses only the performance of materials or certain material constructions (e.g. seams) used in protective clothing. This test method does not address the design, overall construction and components, or interfaces of garments or other factors which may affect the overall protection offered by the protective clothing. It is emphasized that the test does not necessarily simulate conditions that clothing materials are likely to be exposed to in practice. The use of test data should therefore be restricted to broad comparative assessment of such material according to their viral penetration resistance characteristics.

Testing prior to degradation by physical, chemical, and thermal stresses which could negatively impact the performance of the protective barrier, could lead to a false sense of security. Consider tests which assess the impact of sterilization, storage conditions, and shelf life on the penetration resistance for disposable products, and the effects of laundering and sterilization on the penetration resistance for reusable products. The integrity of the protective barrier can also be compromised during use by such effects as flexing and abrasion.^[1] It is also possible that pre-wetting by contaminating materials such as alcohol and perspiration also compromises the integrity of the protective barrier. If these conditions are of concern, evaluate the performance of protective clothing materials for Phi-X174 bacteriophage penetration following an appropriate preconditioning technique representative of the expected conditions of use.

Medical protective clothing materials are intended to be a barrier to blood, body fluids, and other potentially infectious materials. Many factors can affect the wetting and penetration characteristics of body fluids, such as surface tension, viscosity, and polarity of the fluid, as well as the structure and relative hydrophilicity or hydrophobicity of the materials. The surface tension range for blood and body fluids (excluding saliva) is approximately 0,042 N/m to 0,060 N/m.^[2] In order to help simulate the wetting characteristics of blood and body fluids, the surface tension of the Phi-X174 bacteriophage challenge suspension is adjusted to approximate the lower end of this surface tension range. The resulting surface tension of the Phi-X174 bacteriophage challenge suspension is $(0,042 \pm 0,002)$ N/m.

Part of this method for exposing the protective clothing material specimens with Phi-X174 bacteriophage challenge suspension involves pressurization of the test cell to 14,0 kPa (in Procedures A and B). This hydrostatic pressure has been documented to produce test results that correlate with visual penetration results that are obtained with a human factors validation.^[3] Some studies, however, suggest that mechanical pressures exceeding 345 kPa can occur during clinical use.^[4] ^[5] Therefore, it is important to understand that this test method does not simulate all the physical stresses and pressures that are exerted on protective clothing garments during actual use. Procedures C and D use a stepped pressurization approach with pressures up to 20,0 kPa. These procedures simulate a range of possible pressures for ranking material performance.

This document is a preview generated by EVS

Clothing for protection against contact with blood and body fluids — Determination of resistance of protective clothing materials to penetration by blood-borne pathogens — Test method using Phi-X174 bacteriophage

1 Scope

This International Standard describes a laboratory test method for measuring the resistance of materials used in protective clothing to penetration by blood-borne pathogens. This test method uses a surrogate microbe under conditions of continuous liquid contact. Protective clothing “pass/fail” determinations are based on the detection of viral penetration at a specific hydrostatic pressure using the ISO 13994 test apparatus.

This test method is not always effective in testing protective clothing materials having thick, inner liners which readily absorb the challenge fluid.

This test method involves a sensitive assay procedure. Because of the length of time required to complete this test method, it might not be suitable for use as a material or protective clothing quality control or assurance procedure.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 304, *Surface active agents — Determination of surface tension by drawing up liquid films*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 3801, *Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area*

ISO 5084, *Textiles — Determination of thickness of textiles and textile products*

ISO 13994, *Clothing for protection against liquid chemicals — Determination of the resistance of protective clothing materials to penetration by liquids under pressure*

ISO 16603, *Clothing for protection against contact with blood and body fluids — Determination of the resistance of protective clothing materials to penetration by blood and body fluids — Test method using synthetic blood*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1

agar

semi-solid culture medium used to support the growth of bacteria and other microorganisms