

**Preparation of steel substrates before
application of paints and related
products - Surface preparation
methods - Part 2: Abrasive blast-
cleaning**

Preparation of steel substrates before application of
paints and related products - Surface preparation
methods - Part 2: Abrasive blast-cleaning

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

| | |
|--|---|
| <p>Käesolev Eesti standard EVS-EN ISO 8504-2:2002 sisaldab Euroopa standardi EN ISO 8504-2:2001 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 16.01.2002 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p> | <p>This Estonian standard EVS-EN ISO 8504-2:2002 consists of the English text of the European standard EN ISO 8504-2:2001.</p> <p>This document is endorsed on 16.01.2002 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p> |
|--|---|

| | |
|--|--|
| <p>Käsitlusala: This part of EN ISO 8504 describes abrasive blast-cleaning methods for the preparation of steel surfaces before coating with paints and related products.</p> | <p>Scope: This part of EN ISO 8504 describes abrasive blast-cleaning methods for the preparation of steel surfaces before coating with paints and related products.</p> |
|--|--|

ICS 25.220.10

Võtmesõnad: area, p, pre-treatment of surfaces, protective coatings, specification (approval), specifications, steel products, steels, structural steel work, substrates (insulating), surface finishes, surface preparation, surface treatment, surfaces, testing, tools, varnishes

English version

**Preparation of steel substrates before application of paints
and related products – Surface preparation methods**

**Part 2: Abrasive blast-cleaning
(ISO 8504-2 : 2000)**

Préparation des substrats d'acier
avant application de peintures et de
produits assimilés – Méthodes de
préparation des substrats – Partie 2:
Décapage par projection d'abrasif
(ISO 8504-2 : 2000)

Vorbereitung von Stahloberflächen
vor dem Auftragen von Beschichtungs-
stoffen – Verfahren für die
Oberflächenvorbereitung – Teil 2:
Strahlen (ISO 8504-2 : 2000)

This European Standard was approved by CEN on 2001-03-07.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Management Centre: rue de Stassart 36, B-1050 Brussels

Foreword

International Standard

ISO 8504-2 : 2000 Preparation of steel substrates before application of paints and related products – Surface preparation methods – Part 2: Abrasive blast-cleaning,

which was prepared by ISO/TC 35 'Paints and varnishes' of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 139 'Paints and varnishes', the Secretariat of which is held by DIN, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by November 2001 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 8504-2 : 2000 was approved by CEN as a European Standard without any modification.

NOTE: Normative references to international publications are listed in Annex ZA (normative).

Contents

Page

| | |
|---|----|
| Foreword..... | 2 |
| Introduction | 3 |
| 1 Scope | 4 |
| 2 Normative references | 4 |
| 3 Terms and definitions | 6 |
| 4 Abrasives..... | 6 |
| 5 Abrasive blast-cleaning methods | 9 |
| 6 Procedure | 13 |
| Annex A (informative) International Standards for metallic and non-metallic blast-cleaning abrasives... | 14 |

Introduction

The performance of protective coatings of paint and related products applied to steel is significantly affected by the state of the steel surface immediately prior to painting. The principal factors that are known to influence this performance are:

- a) the presence of rust and mill scale;
- b) the presence of surface contaminants, including salts, dust, oils and greases;
- c) the surface profile.

International Standards ISO 8501, ISO 8502 and ISO 8503 have been prepared to provide methods of assessing these factors, while ISO 8504 provides guidance on the preparation methods that are available for cleaning steel substrates, indicating the capabilities of each in attaining specified levels of cleanliness.

These International Standards do not contain recommendations for the protective coating system to be applied to the steel surface. Neither do they contain recommendations for the surface quality requirements for specific situations even though surface quality can have a direct influence on the choice of protective coating to be applied and on its performance. Such recommendations are found in other documents such as national standards and codes of practice. It will be necessary for the users of these International Standards to ensure the qualities specified are

- compatible and appropriate both for the environmental conditions to which the steel will be exposed and for the protective coating system to be used;
- within the capability of the cleaning procedure specified.

The four International Standards referred to below deal with the following aspects of preparation of steel substrates:

ISO 8501 — *Visual assessment of surface cleanliness;*

ISO 8502 — *Tests for the assessment of surface cleanliness;*

ISO 8503 — *Surface roughness characteristics of blast-cleaned steel substrates;*

ISO 8504 — *Surface preparation methods.*

Each of these International Standards is in turn divided into separate parts.

The primary objective of surface preparation is to ensure the removal of deleterious matter and to obtain a surface that permits satisfactory adhesion of the priming paint to steel. It should also assist in reducing the amounts of contaminants that initiate corrosion.

This part of ISO 8504 describes abrasive blast-cleaning methods. It should be read in conjunction with ISO 8504-1.

Abrasive blast-cleaning is a most effective method for mechanical surface preparation. It is widely applicable because this method of surface preparation has a number of versatile features listed below.

- a) The method allows a high production rate.
- b) The equipment can be stationary or mobile and is adaptable to the objects to be cleaned.
- c) The method is applicable to most types and forms of steel surface.
- d) Many different surface states can be produced, for example different preparation grades and surface profiles.
- e) Effects such as cleaning, peening, roughening, levelling and lapping can be produced.
- f) It is possible to remove selectively partly failed coatings, leaving sound coatings intact.

WARNING — The procedures described in this part of ISO 8504 are intended to be carried out by suitably trained and/or supervised personnel. The substances and procedures used in these methods may be injurious to health if adequate precautions are not taken. Attention is drawn in the text to certain specific hazards. This part of ISO 8504 refers only to the technical suitability of the methods and does not absolve the user from statutory obligations relating to health and safety.

1 Scope

This part of ISO 8504 describes abrasive blast-cleaning methods for the preparation of steel surfaces before coating with paints and related products. It also contains information on the effectiveness of the individual methods and their fields of application.

ISO 8504 is applicable to new and corroded steel surfaces and to steel surfaces that are uncoated or have been previously coated with paints and related products. For limitations, see note 2.

NOTE 1 These methods are essentially intended for hot-rolled steel to remove mill scale, rust, etc., but could also be used for cold-rolled steel of sufficient thickness to withstand the deformation caused by the impact of abrasive.

NOTE 2 There are several items that should be included in the purchaser's procurement documents to supplement this part of ISO 8504. Items that should be considered as a part of surface preparation before coating are edge grinding, removal of grease and oil, porosity of welds, removal of weld spatter, removal of burrs and other sharp edges, grinding of welds, filling of pits and other surface imperfections that may cause premature failure of the coating system (see ISO 8501-3 for more information) and the removal of water-soluble contaminants.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 8504. For dated references, subsequent amendments to, or revisions of any of these publications do not apply. However, parties to agreements based on this part of ISO 8504 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 4628-3:1982, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 3: Designation of degree of rusting.*

ISO 8501-1:1988, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings.*

ISO 8501-1:1988/Suppl:1994, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel*

substrates and of steel substrates after overall removal of previous coatings — Informative Supplement: Representative photographic examples of the change of appearance imparted to steel when blast-cleaned with different abrasives.

ISO 8501-2:1994, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 2: Preparation grades of previously coated steel substrates after localized removal of previous coatings.*

ISO 8501-3:¹⁾, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 3: Preparation grades of welds, cut edges and other areas with surface imperfections.*

ISO/TR 8502-1:1991, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 1: Field test for soluble iron corrosion products.*

ISO 8502-2:1992, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 2: Laboratory determination of chloride on cleaned surfaces.*

ISO 8502-3:1992, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method).*

ISO 8502-9:1998, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts.*

ISO 8502-10:1999, *Preparation of steel substrates before the application of paints and related products — Tests for the assessment of surface cleanliness — Part 10: Field method for the titrimetric determination of water-soluble chloride.*

ISO 8503-1:1988, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 1: Specifications and definitions for ISO surface profile comparators for the assessment of abrasive blast-cleaned surfaces.*

ISO 8503-2:1988, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure.*

ISO 8504-1:2000, *Preparation of steel substrates before application of paints and related products — Surface preparation methods — Part 1: General principles.*

ISO 8504-3:1993, *Preparation of steel substrates before application of paints and related products — Surface preparation methods — Part 3: Hand- and power-tool cleaning.*

ISO 11124 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives.*

ISO 11126 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives.*

NOTE The titles of all parts of ISO 11124 and of ISO 11126 are listed in annex A for information.

1) To be published.