

**Toiduainetega kokku puutuvad
materjalid ja esemed. Piirangute alla
kuuluvad plastained. Osa 8:
Isotsüanaatide sisalduse
kindlaksmääramine plastikmaterjalides**

Materials and articles in contact with foodstuffs -
Plastics substances subject to limitation - Part 8:
Determination of isocyanates in plastics

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 13130-8:2004 sisaldab Euroopa standardi EN 13130-8:2004 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 23.09.2004 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 13130-8:2004 consists of the English text of the European standard EN 13130-8:2004.</p> <p>This document is endorsed on 23.09.2004 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>This part of this European Standard describes a method for the determination of individual and total levels of residual isocyanates in plastics materials and articles. This method is applicable to the analysis of polyurethane polymers. The total level of isocyanate monomers in materials and articles determined according to the procedure described in this standard is given in milligrams of NCO per kilogram of material or article. The method is capable of quantitative determination of individual isocyanates measured as NCO at 0,04 mg/kg and total isocyanates at 1,0 mg/kg.</p>	<p>Scope:</p> <p>This part of this European Standard describes a method for the determination of individual and total levels of residual isocyanates in plastics materials and articles. This method is applicable to the analysis of polyurethane polymers. The total level of isocyanate monomers in materials and articles determined according to the procedure described in this standard is given in milligrams of NCO per kilogram of material or article. The method is capable of quantitative determination of individual isocyanates measured as NCO at 0,04 mg/kg and total isocyanates at 1,0 mg/kg.</p>
--	--

ICS 67.250

Võtmesõnad:

ICS 67.250

English version

**Materials and articles in contact with foodstuffs - Plastics
substances subject to limitation - Part 8: Determination of
isocyanates in plastics**

Matériaux et objets en contact avec les denrées
alimentaires - Substances dans les matières plastiques
soumises à des limitations - Partie 8 : Détermination des
isocyanates dans les matières plastiques

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln
- Substanzen in Kunststoffen, die Beschränkungen
unterliegen - Teil 8: Bestimmung von Isocyanaten in
Kunststoffen

This European Standard was approved by CEN on 24 March 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	6
2 Normative references	6
3 Principle.....	6
4 Reagents.....	6
4.1 Analytes	7
4.2 Reagents.....	7
5 Apparatus	9
5.1 General.....	9
6 Samples	9
7 Procedure	10
7.1 Test sample screening	10
7.1.1 Test sample extraction and derivatization	10
7.1.2 Preparation of reagent blank sample.....	10
7.1.3 Preparation of internal standard check sample	10
7.1.4 Preparation of un-derivatized sample blank	10
7.1.5 Chromatographic determination	10
7.2 Quantification of isocyanates by standard addition	11
7.2.1 General.....	11
7.2.2 Preparation of standard solutions for quantification (0 µg/ml to 5 µg/ml).....	11
7.2.3 Procedure for standard addition	12
7.2.4 Control sample.....	12
7.2.5 Analysis	12
7.3 Evaluation of data	12
7.3.1 General.....	12
7.3.2 HPLC interferences.....	12
8 Expression of results	13
8.1 Calculation by least squares regression.....	13
8.2 Graphical determination using internal standard	14
8.3 Precision data and detection limit	15
8.3.1 General.....	15
8.3.2 Repeatability.....	15
8.3.3 Reproducibility.....	15
8.3.4 Detection limits	15
9 Confirmation.....	16
9.1 Requirement for confirmation	16
9.2 Confirmation by re-analysis on an HPLC column of different elution characteristics.....	16
10 Test report	16
Annex A (normative) Calibration by standard addition omitting the internal standard	18
Annex B (informative)	19
Annex C (informative) Suggested gradient profile	20
Bibliography.....	21

Foreword

This document (EN 13130-8:2004) has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This document was prepared by Subcommittee SC1 of TC 194 as one of a series of analytical test methods for plastics materials and articles in contact with foodstuffs.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2004, and conflicting national standards shall be withdrawn at the latest by November 2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This standard is intended to support Directives 2002/72/EC [1], 89/109/EEC [2], 82/711/EEC [3] and its amendments 93/8/EEC [4] and 97/48/EC [5], and 85/572/EEC [6].

At the time of preparation and publication of this part of EN 13130 the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of a test or tests described in this standard.

EN 13130-8 should be read in conjunction with EN 13130-1

Further parts of EN 13130, under the general title *Materials and articles in contact with foodstuffs - Plastics substances subject to limitation*, have been prepared, and others are in preparation, concerned with the determination of specific migration from plastics materials into foodstuffs and food simulants and the determination of specific monomers and additives in plastics. The other parts of EN 13130 are as follows.

- Part 1: *Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants*
- Part 2: *Determination of terephthalic acid in food simulants*
- Part 3: *Determination of acrylonitrile in food and food simulants*
- Part 4: *Determination of 1,3-butadiene in plastics*
- Part 5: *Determination of vinylidene chloride in food simulants*
- Part 6: *Determination of vinylidene chloride in plastics*
- Part 7: *Determination of monoethylene glycol and diethylene glycol in food simulants*
- Part 9: *Determination of acetic acid, vinyl ester in food simulants*
- Part 10: *Determination of acrylamide in food simulants*
- Part 11: *Determination of 11-aminoundecanoic acid in food simulants*
- Part 12: *Determination of 1,3-benzenedimethanamine in food simulants*
- Part 13: *Determination of 2,2-bis(4-hydroxyphenyl)propane (Bisphenol A) in food simulants*
- Part 14: *Determination of 3,3-bis(3-methyl-4-hydroxyphenyl)-2-indoline in food simulants*

- Part 15: *Determination of 1,3-butadiene in food simulants*
- Part 16: *Determination of caprolactam and caprolactam salt in food simulants*
- Part 17: *Determination of carbonyl chloride in plastics*
- Part 18: *Determination of 1,2-dihydroxybenzene, 1,3- dihydroxybenzene, 1,4- dihydroxybenzene, 4,4'-dihydroxybenzophenone and 4,4'-dihydroxybiphenyl in food simulants*
- Part 19: *Determination of dimethylaminoethanol in food simulants*
- Part 20: *Determination of epichlorohydrin in plastics*
- Part 21: *Determination of ethylenediamine and hexamethylenediamine in food simulants*
- Part 22: *Determination of ethylene oxide and propylene oxide in plastics*
- Part 23: *Determination of formaldehyde and hexamethylenetetramine in food simulants*
- Part 24: *Determination of maleic acid and maleic anhydride in food simulants*
- Part 25: *Determination of 4-methyl-pentene in food simulants*
- Part 26: *Determination of 1-octene and tetrahydrofuran in food simulants*
- Part 27: *Determination of 2,4,6-triamino-1,3,5-triazine in food simulants*
- Part 28: *Determination of 1,1,1-trimethylpropane in food simulants*

Parts 1 to 8 are European Standards.

Parts 9 to 28 are Technical Specifications, prepared within the Standards, Measurement and Testing project, MAT1-CT92-0006, "Development of Methods of Analysis for Monomers".

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Isocyanates, characterised by the -NCO group, are monomers used for the manufacture of materials and articles intended to come in contact with food. During manufacture residual isocyanates can remain in the polymer and can migrate into food coming into contact with the polymer.

1 Scope

This part of this European Standard describes a method for the determination of individual and total levels of residual isocyanates in plastics materials and articles.

This method is applicable to the analysis of polyurethane polymers. The total level of isocyanate monomers in materials and articles determined according to the procedure described in this standard is given in milligrams of NCO per kilogram of material or article. The method is capable of quantitative determination of individual isocyanates measured as NCO at 0,04 mg/kg and total isocyanates at 1,0 mg/kg.

NOTE The method has been applied to the analysis of 9 isocyanate monomers listed in 3.1. It has not been applied to the analysis of octadecyl isocyanate, diphenylether-4,4'-diisocyanate or 3,3'-dimethyl-4,4'-diisocyanatobiphenyl as samples of these monomers have not been obtained. There is no reason to anticipate that the method may not be suitable for the analysis of these monomers also.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 13130-1:2004, *Materials and articles in contact with foodstuffs - Plastics substances subject to limitation - Part 1: Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants.*

3 Principle

The procedure consists of two parts: screening and, if necessary, quantitative determination. Quantitative determination is applied only if isocyanates are detected by the screening procedure.

Materials and articles are initially screened for residual isocyanates by solvent extraction with dichloromethane and concurrent derivatization with 9-(methylaminomethyl)anthracene. 1-Naphthyl isocyanate is used during the screening procedure to check that the derivatization procedure has been successful. The resultant fluorescent derivatives are analysed by high performance liquid chromatography with fluorescence detection.

Materials found to contain residual isocyanates are quantified by standard addition to the material or article under test, using 1-naphthyl isocyanate as internal standard.

If interferences are experienced with the internal standard then calibration is carried out by standard addition omitting the internal standard, as described in annex A.

Confirmation of isocyanate levels is carried out by re-analysing the sample extracts on an HPLC column with different elution characteristics.

4 Reagents

WARNING: All chemicals are hazardous to health to a greater or lesser extent. It is beyond the scope of this standard to give instructions for the safe handling of all chemicals, that meet, in full, the legal obligations in all countries in which this standard may be followed. Therefore, specific warnings are