
Textiles — Tests for colour fastness —
Part B02:
Colour fastness to artificial light:
Xenon arc fading lamp test

Textiles — Essais de solidité des coloris —

*Partie B02: Solidité des coloris à la lumière artificielle: Lampe à arc
au xénon*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Terms and definitions	2
5 Materials and apparatus	3
5.1 Reference materials	3
5.2 Laboratory exposure devices	4
6 Preparation of test specimens	5
7 Exposure conditions	6
8 Procedure	7
8.1 Apparatus set-up	7
8.2 Adjustment of the effective humidity (see Clause 7 and Annex E)	7
8.3 Exposure methods	9
9 Assessment of colour fastness	16
10 Test report	17
Annex A (normative) Requirements for xenon arc exposure devices	20
Annex B (normative) Procedures for measuring the irradiance uniformity in the specimen exposure area (for apparatus manufacturers only)	23
Annex C (informative) Light exposure equivalents for blue wool lightfastness references L2 to L9	25
Annex D (informative) General information on colour fastness to light	26
Annex E (informative) Guidelines for conducting testing	28
Bibliography	36

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This sixth edition cancels and replaces the fifth edition (ISO 105-B02:2013), of which it constitutes a minor revision.

ISO 105 consists of many parts designated by a part letter and a two-digit serial number (e.g. A01), under the general title *Textiles — Tests for colour fastness*. A complete list of these parts is given in ISO 105-A01.

Textiles — Tests for colour fastness —

Part B02:

Colour fastness to artificial light: Xenon arc fading lamp test

1 Scope

This part of ISO 105 specifies a method intended for determining the effect on the colour of textiles of all kinds and in all forms to the action of an artificial light source representative of natural daylight (D65). The method is also applicable to white (bleached or optically brightened) textiles.

This method allows the use of two different sets of blue wool references. The results from the two different sets of references may not be identical.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-B01:2014, *Textiles — Tests for colour fastness — Part B01: Colour fastness to light: Daylight*

ISO 105-B05, *Textiles — Tests for colour fastness — Part B05: Detection and assessment of photochromism*

ISO 105-B08, *Textiles — Tests for colour fastness — Part B08: Quality control of blue wool reference materials 1 to 7*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

CIE¹⁾ Publication No. 51, *Method for assessing the quality of daylight simulators for colorimetry*

3 Principle

A specimen of the textile to be tested is exposed to artificial light under controlled conditions, together with a set of reference materials. The colour fastness is assessed by comparing the change in colour of the test specimen with that of the reference materials used.

NOTE General information on colour fastness to light is given in [Annex D](#).

1) Commission Internationale de l'Éclairage, CIE Central Bureau, Kegelgasse 27, A-1030, Vienna, Austria www.cie.co.at.