Ehituslikud soojusisolatsioonitooted. Tööstuslikult valmistatud ekstrudeeritud vahtpolüstüreentooted (XPS). Spetsifikatsioon

Thermal insulation products for buildings - Factory ane of the second of the secon made extruded polystyrene foam (XPS) products -**Specification**



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

	This Estonian standard EVS-EN 13164:2012 consists of the English text of the European standard EN
teksti.	13164:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
, and a second s	Date of Availability of the European standard is 28.11.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

ICS 91.100.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation: Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 13164

NORME EUROPÉENNE EUROPÄISCHE NORM

November 2012

ICS 91.100.60

Supersedes EN 13164:2008

English Version

Thermal insulation products for buildings - Factory made extruded polystyrene foam (XPS) products - Specification

Produits isolants thermiques pour le bâtiment - Produits manufacturés en mousse de polystyrène extrudé (XPS) -Spécification Wärmedämmstoffe für Gebäude - Werkmäßig hergestellte Produkte aus extrudiertem Polystyrolschaum (XPS) -Spezifikation

This European Standard was approved by CEN on 6 October 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Cont	ents	Page
Faraur	ord	_
rorew 1	Scope	
_	• 9	
2	Normative references	
3	Terms, definitions, symbols, units, abbreviated terms	8
4	Requirements	
4.1	General	
4.2	For all applications	
4.2.1	Thermal resistance and thermal conductivity	12
4.2.2	Length, width, squareness, flatness	
4.2.3	Thickness	
4.2.4	Reaction to fire of the product as placed on the market	
4.2.5	Durability characteristics	
4.3	For specific applications	
4.3.1	General	
4.3.2	Dimensional stability under specified conditions	
4.3.3	Deformation under specified compressive load and temperature conditions	
4.3.4	Compressive stress or compressive strength	
4.3.5	Tensile strength perpendicular to faces	
4.3.6	Compressive creep	
4.3.7	Water absorption	
4.3.8	Freeze-thaw resistance	
4.3.9	Water vapour transmission	
4.3.10	Release of dangerous substances	18
4.3.11	Reaction to fire of the product in standardized assemblies simulating end-use	40
4 0 40	applications	18
4.3.12		
4.3.13	Shear strength	
5	Test methods	
5.1	Sampling	
5.2	Conditioning	
5.3	Testing	19
5.3.1	General	
5.3.2	Thermal resistance and thermal conductivity	19
6	Designation code	21
0		
7	Evaluation of conformity	
7.1	General	
7.2	Initial type testing	22
7.3	Factory production control	22
В	Marking and labelling	23
Δηηρν	A (normative) Determination of the declared values of thermal resistance and thermal	
	conductivity	24
A .1	General	
A.2	Input data	
A.3	Declared values	
A.3.1	General	
A.3.2	Case where thermal resistance and thermal conductivity are declared	
A.3.3	Case where only thermal resistance is declared	
	•	
Annex	B (normative) Initial type testing (ITT) and Factory production control (FPC)	27

Annex	C (normative) Determination of the aged values of thermal resistance and thermal	
	conductivity	
C.1	General	30
C.2	Procedure for XPS foam without diffusion tight facings	
C.2.1	Principle	
C.2.2	Sample preparation	
C.2.3	Procedure	30
C.3	Procedure for XPS foam for use with diffusion tight facing on both sides	
C.3.1 C.3.2	Principle	
C.3.2 C.4	Ageing procedure Determination of value after ageing: "aged value"	
C.4.1	Determination of aged value for XPS products without diffusion tight facings on both	
C.4.2	Determination of aged value for XPS products for use with diffusion tight facing on both sides	
C.5	Blowing agent	
C.6	Product grouping	
Annex	D (normative) XPS multi-layered insulation products	34
D.1	General	
D.2	Requirements	
D.2.1	For all applications	
D.2.2	For specific applications	
D.3	Test methods	
D.4	Evaluation of conformity	35
Annex	E (informative) Additional properties	36
E.1	General	36
E.2	Behaviour under cyclic loading	36
E.3	Compressive modulus of elasticity	36
E.4	Bending strength	
E.5	Determination of volume percentage of closed cells	36
	F (informative) Plan for cutting test specimen	38
Annex	ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Directive	40
ZA.2	Procedures for attestation of conformity of factory made extruded polystyrene foam products	42
ZA.2.1	Systems of attestation of conformity	
Diblios	graphy	40
Tables		40
	— Tolerances of length, width, squareness and flatness	13
	2 — Classes for thickness tolerances	
	3 — Dimensional stability under specified conditions	
	Levels for deformation under specified compressive load and temperature conditions	
	5 — Levels for compressive stress or compressive strength	
	S — Levels for tensile strength, perpendicular to faces	
Table 7	— Levels for long term water absorption by total immersion	17
Table 8	B — Levels for long term water absorption by diffusion	17

EVS-EN 13164:2012

able 9 — Test methods, test specimens and conditions	20
able A.1 — Values for k for one sided 90 % tolerance interval with a confidence level of 90 %	25
able B.1 — Minimum number of tests for ITT and minimum product testing frequencies	27
able B.2 — Minimum product testing frequencies for the reaction to fire characteristics	29
able E.1 — Test methods, test specimens, conditions and minimum testing frequencies	37
able ZA.1 — Relevant clauses for extruded polystyrene foam products	41
able ZA.2 — Systems of attestation of conformity	42
able ZA.3.1 — Assignment of evaluation of conformity tasks for products under system 1 for reaction to f and system 3 for other characteristics	
able ZA.3.2 — Assignment of evaluation of conformity tasks for products under system 3 or system combined with system 4 for reaction to fire	
igures	
	47
igure ZA.1 — Example CE marking information	
2	

Foreword

This document (EN 13164:2012) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2013, and conflicting national standards shall be withdrawn at the latest by May 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13164:2008.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Compared with EN 13164:2008, the main changes are:

- a) better harmonisation between the individual standards of the package (EN 13162 to EN 13171) on definitions, requirements, classes and levels;
- b) new normative annex on multi-layered products;
- c) changes of some editorial and technical content and addition of information on some specific items such as for XPS: Annex C;
- d) addition to links to EN 15715, Thermal insulation products Instructions for mounting and fixing for reaction to fire testing Factory made products;
- e) changes to the Annex ZA.

This European Standard is one of a series of standards for thermal insulation products used in buildings, but this standard may be used in other areas where appropriate.

In pursuance of resolution BT 20/1993 revised, CEN/TC 88 have proposed defining the standards listed below as a package of documents.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products; all of which come within the scope of CEN/TC 88:

EN 13162, Thermal insulation products for buildings — Factory made mineral wool (MW) products — Specification

EN 13163, Thermal insulation products for buildings — Factory made expanded polystyrene (EPS) products — Specification

EN 13164, Thermal insulation products for buildings — Factory made extruded polystyrene foam (XPS) products — Specification

EN 13165, Thermal insulation products for buildings — Factory made rigid polyurethane foam (PU) products — Specification

EN 13166, Thermal insulation products for buildings — Factory made phenolic foam (PF) products — Specification

EN 13167, Thermal insulation products for buildings — Factory made cellular glass (CG) products — Specification

EN 13168, Thermal insulation products for buildings — Factory made wood wool (WW) products — Specification

EN 13169, Thermal insulation products for buildings — Factory made expanded perlite board (EPB) products — Specification

EN 13170, Thermal insulation products for buildings — Factory made products of expanded cork (ICB) — Specification

EN 13171, Thermal insulation products for buildings — Factory made wood fibre (WF) products — Specification

The reductions in energy used and emissions produced during the installed life of the insulation products exceeds by far the energy used and emissions made during the production and disposal processes.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, mbc, pand, 1 Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the requirements for factory made products of extruded polystyrene foam, with or without facings or coatings, which are used for thermal insulation of buildings. The products are manufactured in the form of boards which are also available with special edge and surface treatment (tongue & grooves, shiplap etc.).

Products covered by this standard are also used in prefabricated thermal insulating systems and composite panels; the performance of systems incorporating these products is not covered.

This standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

The standard does not specify the required level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application are to be found in regulations or non-conflicting standards.

Products with a declared thermal resistance lower than $0.25~m^2 \cdot K/W$ or a declared thermal conductivity greater than $0.060~W/(m \cdot K)$ at $10~^{\circ}C$ are not covered by this standard.

This standard does not cover in situ insulation products, nor products intended to be used for the insulation of building equipment and industrial installations (covered by EN 14307), or civil engineering applications (covered by EN 14934).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- EN 822, Thermal insulating products for building applications Determination of length and width
- EN 823, Thermal insulating products for building applications Determination of thickness
- EN 824, Thermal insulating products for building applications Determination of squareness
- EN 825, Thermal insulating products for building applications Determination of flatness
- EN 826, Thermal insulating products for building applications Determination of compression behaviour
- EN 1604, Thermal insulating products for building applications Determination of dimensional stability under specified temperature and humidity conditions
- EN 1605, Thermal insulating products for building applications Determination of deformation under specified compressive load and temperature conditions
- EN 1606, Thermal insulating products for building applications Determination of compressive creep
- EN 1607, Thermal insulating products for building applications Determination of tensile strength perpendicular to faces
- EN 12086:1997, Thermal insulating products for building applications Determination of water vapour transmission properties
- EN 12087, Thermal insulating products for building applications Determination of long term water absorption by immersion

EN 12088, Thermal insulating products for building applications — Determination of long term water absorption by diffusion

EN 12090, Thermal insulating products for building applications — Determination of shear behaviour

EN 12091, Thermal insulating products for building applications — Determination of freeze-thaw resistance

EN 12667, Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hotplate and heat flow meter methods — Products of high and medium thermal resistance

EN 12939, Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance

EN 13172:2012, Thermal insulation products — Evaluation of conformity

EN 13501-1, Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests

EN 13820, Thermal insulating materials for building applications — Determination of organic content

EN 13823, Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item

EN 15715:2009, Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing — Factory made products

EN ISO 1182, Reaction to fire tests for products — Non-combustibility test (ISO 1182)

EN ISO 1716, Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value) (ISO 1716)

EN ISO 9229:2007, Thermal insulation — Vocabulary (ISO 9229:2007)

EN ISO 11925-2, Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2)

ISO 16269-6:2005 Statistical interpretation of data — Part 6: Determination of statistical tolerance intervals

3 Terms, definitions, symbols, units, abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 9229:2007 apply with exception or in addition of the following:

3.1.1

extruded polystyrene foam

rigid cellular plastics insulation material expanded and extruded with or without a skin, from polystyrene or one of its copolymers and which has a closed cell structure

3.1.2

level

value which is the upper or lower limit of a requirement and given by the declared value of a characteristic concerned