

ASFALTSEGUD. KATSEMEETODID. OSA 2:
TERASTIKULISE KOOSTISE MÄÄRAMINE

Bituminous mixtures - Test methods - Part 2:
Determination of particle size distribution

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12697-2:2015 sisaldab Euroopa standardi EN 12697-2:2015 ingliskeelset teksti.	This Estonian standard EVS-EN 12697-2:2015 consists of the English text of the European standard EN 12697-2:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 29.04.2015.	Date of Availability of the European standard is 29.04.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Bituminous mixtures - Test methods - Part 2: Determination of particle size distribution

Mélanges bitumineux - Méthode d'essai - Partie 2:
Granulométrie

Asphalt - Prüfverfahren - Teil 2: Korngrößenverteilung

This European Standard was approved by CEN on 19 March 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Significance and use	7
5 Principle	8
6 Apparatus	8
7 Sample preparation	8
8 Procedure	8
9 Calculation	9
10 Report	9
11 Precision	9
Bibliography	11

Foreword

This document (EN 12697-2:2015) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2015 and conflicting national standards shall be withdrawn at the latest by October 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-2:2002+A1:2007.

The following is a list of changes since the previous edition:

- the series title no longer makes the method exclusively for hot mix asphalt;
- clarification of what defines constant mass to be consistent with EN 933-1;
- limit size of sample to less than 1 kg;
- clarification of procedure when washing the aggregate is required.

This European Standard is one of a series of standards as follows:

- EN 12697-1, *Bituminous mixtures — Test methods for hot mix asphalt — Part 1: Soluble binder content*
- EN 12697-2, *Bituminous mixtures — Test methods — Part 2: Determination of particle size distribution*
- EN 12697-3, *Bituminous mixtures — Test methods for hot mix asphalt — Part 3: Bitumen recovery: Rotary evaporator*
- EN 12697-4, *Bituminous mixtures — Test methods — Part 4: Bitumen recovery: Fractionating column*
- EN 12697-5, *Bituminous mixtures — Test methods for hot mix asphalt — Part 5: Determination of the maximum density*
- EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*
- EN 12697-7, *Bituminous mixtures — Test methods for hot mix asphalt — Part 7: Determination of bulk density of bituminous specimens by gamma rays*
- EN 12697-8, *Bituminous mixtures — Test methods for hot mix asphalt — Part 8: Determination of void characteristics of bituminous specimens*
- EN 12697-10, *Bituminous mixtures — Test methods for hot mix asphalt — Part 10: Compactability*
- EN 12697-11, *Bituminous mixtures — Test methods for hot mix asphalt — Part 11: Determination of the affinity between aggregate and bitumen*
- EN 12697-12, *Bituminous mixtures — Test methods for hot mix asphalt — Part 12: Determination of the water sensitivity of bituminous specimens*

- EN 12697-13, *Bituminous mixtures — Test methods for hot mix asphalt — Part 13: Temperature measurement*
- EN 12697-14, *Bituminous mixtures — Test methods for hot mix asphalt — Part 14: Water content*
- EN 12697-15, *Bituminous mixtures — Test methods for hot mix asphalt — Part 15: Determination of the segregation sensitivity*
- EN 12697-16, *Bituminous mixtures — Test methods for hot mix asphalt — Part 16: Abrasion by studded tyres*
- EN 12697-17, *Bituminous mixtures — Test methods for hot mix asphalt — Part 17: Particle loss of porous asphalt specimen*
- EN 12697-18, *Bituminous mixtures — Test methods for hot mix asphalt — Part 18: Binder drainage*
- EN 12697-19, *Bituminous mixtures — Test methods for hot mix asphalt — Part 19: Permeability of specimen*
- EN 12697-20, *Bituminous mixtures — Test methods for hot mix asphalt — Part 20: Indentation using cube or cylindrical specimens (CY)*
- EN 12697-21, *Bituminous mixtures — Test methods for hot mix asphalt — Part 21: Indentation using plate specimens*
- EN 12697-22, *Bituminous mixtures — Test methods for hot mix asphalt — Part 22: Wheel tracking*
- EN 12697-23, *Bituminous mixtures — Test methods for hot mix asphalt — Part 23: Determination of the indirect tensile strength of bituminous specimens*
- EN 12697-24, *Bituminous mixtures — Test methods for hot mix asphalt — Part 24: Resistance to fatigue*
- EN 12697-25, *Bituminous mixtures — Test methods for hot mix asphalt — Part 25: Cyclic compression test*
- EN 12697-26, *Bituminous mixtures — Test methods for hot mix asphalt — Part 26: Stiffness*
- EN 12697-27, *Bituminous mixtures — Test methods for hot mix asphalt — Part 27: Sampling*
- EN 12697-28, *Bituminous mixtures — Test methods for hot mix asphalt — Part 28: Preparation of samples for determining binder content, water content and grading*
- EN 12697-29, *Bituminous mixtures — Test method for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen*
- EN 12697-30, *Bituminous mixtures — Test methods for hot mix asphalt — Part 30: Specimen preparation by impact compactor*
- EN 12697-31, *Bituminous mixtures — Test methods for hot mix asphalt — Part 31: Specimen preparation by gyratory compactor*
- EN 12697-32, *Bituminous mixtures — Test methods for hot mix asphalt — Part 32: Laboratory compaction of bituminous mixtures by vibratory compactor*
- EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*

- EN 12697-34, *Bituminous mixtures — Test methods for hot mix asphalt — Part 34: Marshall test*
- EN 12697-35, *Bituminous mixtures — Test methods for hot mix asphalt — Part 35: Laboratory mixing*
- EN 12697-36, *Bituminous mixtures — Test methods for hot mix asphalt — Part 36: Determination of the thickness of a bituminous pavement*
- EN 12697-37, *Bituminous mixtures — Test methods for hot mix asphalt — Part 37: Hot sand test for the adhesivity of binder on precoated chippings for HRA*
- EN 12697-38, *Bituminous mixtures — Test methods for hot mix asphalt — Part 38: Common equipment and calibration*
- EN 12697-39, *Bituminous mixtures — Test methods for hot mix asphalt — Part 39: Binder content by ignition*
- EN 12697-40, *Bituminous mixtures — Test methods for hot mix asphalt — Part 40: In situ drainability*
- EN 12697-41, *Bituminous mixtures — Test methods for hot mix asphalt — Part 41: Resistance to de-icing fluids*
- EN 12697-42, *Bituminous mixtures — Test methods for hot mix asphalt — Part 42: Amount of foreign matter in reclaimed asphalt*
- EN 12697-43, *Bituminous mixtures — Test methods for hot mix asphalt — Part 43: Resistance to fuel*
- EN 12697-44, *Bituminous mixtures — Test methods for hot mix asphalt — Part 44: Crack propagation by semi-circular bending test*
- EN 12697-45, *Bituminous mixtures — Test methods for hot mix asphalt — Part 45: Saturation Ageing Tensile Stiffness (SATS) conditioning test*
- EN 12697-46, *Bituminous mixtures — Test methods for hot mix asphalt — Part 46: Low temperature cracking and properties by uniaxial tension tests*
- EN 12697-47, *Bituminous mixtures — Test methods for hot mix asphalt — Part 47: Determination of the ash content of natural asphalts*
- EN 12697-49, *Bituminous mixtures — Test methods for hot mix asphalt — Part 49: Determination of friction after polishing*
- prCEN/TS 12697-50, *Bituminous mixtures — Test methods for hot mix asphalt — Part 50: Resistance to Scuffing¹⁾*
- FprCEN/TS 12697-51, *Bituminous mixtures — Test methods — Part 51: Surface shear strength test*
- CEN/TS 12697-52, *Bituminous mixtures — Test methods — Part 52: Conditioning to address oxidative ageing*
- prEN 12697-53, *Bituminous mixtures — Test methods — Part 53: Cohesion increase by spreadability-meter method ²⁾*

1) Currently at Enquiry stage.

2) Currently at drafting stage.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This European Standard specifies a procedure for the determination of the particle size distribution of the aggregates of bituminous mixtures by sieving. The test is applicable to aggregates recovered after binder extraction in accordance with EN 12697-1 or EN 12697-39.

The applicability of this European Standard is described in the product standards for bituminous mixtures.

NOTE Fibres, solid (non-soluble during extraction) additives and (some) binder modifiers influence the test result.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 932-6, *Tests for general properties of aggregates — Part 6: Definitions of repeatability and reproducibility*

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 12697-1, *Bituminous mixtures — Test methods for hot mix asphalt — Part 1: Soluble binder content*

EN 12697-39, *Bituminous mixtures — Test methods for hot mix asphalt — Part 39: Binder content by ignition*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 3310-2, *Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

particle size distribution

portion of aggregate on specified sieves expressed as cumulative percentages by mass passing those sieves

3.2

D

upper sieve size of the aggregate in the bituminous mixture in millimetre (mm) according to the relevant material specification standard

4 Significance and use

The composition of a bituminous mixture in terms of binder content and aggregates grading is a significant quality parameter. The European Standard for bituminous mixtures contains some grading specifications. Controlling the mixture grading is an important instrument for product quality management.