

**Plastikud. Ehituslikud plastifitseerimata
polüvinüülkloriidist (PVC-U) profiilid.
Osa 1: Heledate värvitud profiilide
tähistus**

Plastics - Unplasticized poly(vinyl chloride) (PVC-U)
profiles for building applications - Part 1: Designation
of light coloured profiles

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 13245-1:2004 sisaldab Euroopa standardi EN 13245-1:2004 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 21.12.2004 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 13245-1:2004 consists of the English text of the European standard EN 13245-1:2004.</p> <p>This document is endorsed on 21.12.2004 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This part of EN 13245 specifies a method for the designation of light coloured profiles made of unplasticized poly(vinyl chloride) (PVC-U) intended to be used for building applications and gives the relevant test methods. It is intended to be used in product specification when application is specified. Pipes for the distribution of water, of gas or other fluids, as well as discharge and sewage pipes, profiles for the management of electrical power cables, communication cables and power track systems used for the distribution of electrical power, profiles for windows or doors and profiles made from expanded PVC are not covered by this European Standard.</p>	<p>Scope: This part of EN 13245 specifies a method for the designation of light coloured profiles made of unplasticized poly(vinyl chloride) (PVC-U) intended to be used for building applications and gives the relevant test methods. It is intended to be used in product specification when application is specified. Pipes for the distribution of water, of gas or other fluids, as well as discharge and sewage pipes, profiles for the management of electrical power cables, communication cables and power track systems used for the distribution of electrical power, profiles for windows or doors and profiles made from expanded PVC are not covered by this European Standard.</p>
---	---

ICS 83.140.99

Võtmesõnad:

ICS 83.140.99

English version

Plastics - Unplasticized poly(vinyl chloride) (PVC-U) profiles for building applications - Part 1: Designation of light coloured profiles

Plastiques - Profilés en poly(chlorure de vinyle) non plastifié (PVC-U) pour applications dans le bâtiment - Partie 1 : Désignation des profilés de coloris clair

Kunststoffe - Profile aus weichmacherfreiem Polyvinylchlorid (PVC-U) für die Anwendung im Bauwesen - Teil 1: Bezeichnung von hellfarbigen Profilen

This European Standard was approved by CEN on 24 June 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

1	Scope	4
2	Normative references	4
3	Terms and definitions	5
4	Designation of profiles for building applications	5
5	Codification system for blocks 3 to 5	6
5.1	Vicat softening temperature (block 3)	6
5.2	Modulus of elasticity in flexure (block 3)	6
5.3	Nominal linear mass of the profile (block 4)	6
5.3.1	Test method for the determination of the linear mass	6
5.3.2	Codification	7
5.4	Heat reversion at 100 °C (block 4)	7
5.5	Impact resistance (block 4)	7
5.6	Properties after ageing (block 5)	8
5.6.1	General	8
5.6.2	Test methods for ageing	8
5.6.3	Test methods for the assessing of ageing	9
5.6.4	Codification for properties after ageing	10
6	Example of profile designation	11
7	Use of reprocessible and recyclable material	11
Annex A (normative)	Test method for the determination of the impact resistance	12
A.1	Principle	12
A.2	Apparatus	12
A.3	Test specimens	12
A.4	Conditioning	13
A.4.1	Impact resistance at 23 °C	13
A.4.2	Impact resistance at low temperature	13
A.5	Procedure	13
A.6	Expression of results	13
	Bibliography	15

Foreword

This document (EN 13245-1:2004) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2005, and conflicting national standards shall be withdrawn at the latest by June 2006.

This document EN 13245 consists of the following parts, under the general title *Plastics – Unplasticized poly(vinyl chloride) (PVC-U) profiles for building applications*:

- *Part 1: Designation of light coloured profiles*
- *Part 2: Profiles for internal and external wall and ceiling finishes.*
- *Part 3: Designation of coloured profiles*
- *Part 4: Designation of light coloured cellular unplasticized poly(chloride) (PVC-UE) profiles*
- *Part 5: Designation of coloured cellular unplasticized poly(chloride) (PVC-UE) profiles*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This part of EN 13245 specifies a method for the designation of light coloured profiles made of unplasticized poly(vinyl chloride) (PVC-U) intended to be used for building applications and gives the relevant test methods. It is intended to be used in product specification when application is specified.

Pipes for the distribution of water, of gas or other fluids, as well as discharge and sewage pipes, profiles for the management of electrical power cables, communication cables and power track systems used for the distribution of electrical power, profiles for windows or doors and profiles made from expanded PVC are not covered by this document.¹⁾

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 477:1995, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors — Determination of the resistance to impact of main profiles by falling mass.*

EN 479, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors — Determination of heat reversion.*

EN 513:1999, *Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors — Determination of the resistance to artificial weathering.*

EN ISO 178, *Plastics — Determination of flexural properties (ISO 178:2001)*

EN ISO 306:1996, *Plastics — Thermoplastics materials — Determination of Vicat softening temperature (VST) (ISO 306:1994).*

EN ISO 1163-2, *Plastics — Unplasticized poly(vinyl chloride) (PVC-U) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties (ISO 1163-2:1995).*

EN ISO 4892-2:1999, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc sources (ISO 4892-2:1994).*

EN ISO 8256:1996, *Plastics — Determination of tensile-impact strength (ISO 8256:1990, including Technical corrigendum 1:1991).*

ISO 7724-1, *Paints and varnishes — Colorimetry — Part 1: Principles.*

ISO 7724-2, *Paints and varnishes — Colorimetry — Part 2: Colour measurement.*

ISO 7724-3, *Paints and varnishes — Colorimetry — Part 3: Calculation of colour differences.*

1) Products that are excluded are in the scopes of CEN/TC 33, CEN/TC 155, CENELEC/TC 213.