

**Sidumata ja hüdrauliliselt seotud segud. Osa 42:
Katsemeetod proovikehade kaudse tõmbetugevuse
määramiseks**

**Unbound and hydraulically bound mixtures. Part 42:
Test method for the determination of the indirect tensile
strength of test specimens**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13286-42:2003 sisaldab Euroopa standardi EN 13286-42:2003 ingliskeelset teksti.	This Estonian standard EVS-EN 13286-42:2003 consists of the English text of the European standard EN 13286-42:2003.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.03.2003.	Date of Availability of the European standard is 05.03.2003.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Võtmesõnad: density (mass/volume), pavements, road cons, roads, rocks, sample division, samples, sampling, sampling methods, specification (approval), specifications, specimen preparation, tensile strength, tensile testing, test specimens, testing, testing conditions, unbound,

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

ICS 93.080.20

English version

Unbound and hydraulically bound mixtures - Part 42: Test method for the determination of the indirect tensile strength of hydraulically bound mixtures

Mélanges traités et mélanges non traités aux liants hydrauliques - Partie 42: Méthode d'essai pour la détermination de la résistance à la traction indirecte des mélanges traités aux liants hydrauliques

Ungebundene und hydraulisch gebundene Gemische - Teil 42: Prüfverfahren zur Bestimmung der Zugfestigkeit hydraulisch gebundenen Gemischen im indirekten Zugversuch

This European Standard was approved by CEN on 29 November 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovak Republic, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus	6
6 Test specimens	7
6.1 Manufacture of test specimen	7
6.2 Shape and dimension	7
7 Test procedure	7
7.1 Preparation of the test specimen prior to test	7
7.1.1 Dimensions	7
7.1.2 Mass	7
7.1.3 Parallelism tolerance of the generatrix	7
7.2 Specimen positioning	7
7.3 Loading	7
7.4 Data recording	7
8 Expression of result	7
9 Test report	8

Foreword

This document (EN 13286-42:2003) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2003, and conflicting national standards shall be withdrawn at the latest by December 2004.

This European Standard is one of a series of standards as listed below.

EN 13286-1, *Unbound and hydraulically bound mixtures — Part 1: Test methods for laboratory reference density and water content — Introduction, general requirements and sampling.*

prEN 13286-2, *Unbound and hydraulically bound mixtures — Part 2: Test methods for laboratory reference density and water content — Proctor compaction.*

EN 13286-3, *Unbound and hydraulically bound mixtures — Part 3: Test methods for laboratory reference density and water content — Vibrocompression with controlled parameters.*

EN 13286-4, *Unbound and hydraulically bound mixtures — Part 4: Test methods for laboratory reference density and water content — Vibrating hammer.*

EN 13286-5, *Unbound and hydraulically bound mixtures — Part 5: Test methods for laboratory reference density and water content — Vibrating table.*

prEN 13286-7, *Unbound and hydraulically bound mixtures — Part 7: Cyclic load triaxial test for unbound mixtures.*

EN 13286-40, *Unbound and hydraulically bound mixtures — Part 40: Test method for the determination of the direct tensile strength of hydraulically bound mixtures.*

EN 13286-41, *Unbound and hydraulically bound mixtures — Part 41: Test method for the determination of the compressive strength of hydraulically bound mixtures.*

EN 13286-42, *Unbound and hydraulically bound mixtures — Part 42: Test method for the determination of the indirect tensile strength of hydraulically bound mixtures.*

EN 13286-43, *Unbound and hydraulically bound mixtures — Part 43: Test method for the determination of the modulus of elasticity of hydraulically bound mixtures.*

prEN 13286-44, *Unbound and hydraulically bound mixtures — Part 44: Test method for the determination of the alpha coefficient of vitrified blastfurnace slag.*

prEN 13286-45, *Unbound and hydraulically bound mixtures — Part 45: Test method for the determination of the workability period of hydraulically bound mixtures.*

prEN 13286-46, *Unbound and hydraulically bound mixtures — Part 46: Test method for the determination of the moisture condition value.*

prEN 13286-47, *Unbound and hydraulically bound mixtures — Part 47: Test method for the determination of California bearing ratio, immediate bearing index and linear swelling.*

prEN 13286-48, *Unbound and hydraulically bound mixtures — Part 48: Test method for the determination of the degree of pulverisation.*

prEN 13286-49, *Unbound and hydraulically bound mixtures — Part 49: Test method for the determination of the accelerated swelling of soil treated by lime and/or hydraulic binder.*

prEN 13286-50, *Unbound and hydraulically bound mixtures —Part 50: Method for the manufacture of test specimens of hydraulically bound mixtures using Proctor equipment or vibrating table compaction.*

prEN 13286-51, *Unbound and hydraulically bound mixtures —Part 51: Method for the manufacture of test specimens of hydraulically bound mixtures using vibrating hammer compaction.*

prEN 13286-52, *Unbound and hydraulically bound mixtures —Part 52: : Method for the manufacture of test specimens of hydraulically bound mixtures using vibrocompression.*

prEN 13286-53, *Unbound and hydraulically bound mixtures —Part 53: : Method for the manufacture of test specimens of hydraulically bound mixtures using axial compression.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovak Republic, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a test method for the determination of the indirect tensile strength of cylindrical specimens of hydraulically bound mixtures. This European Standard applies to specimens manufactured in the laboratory or prepared from cores.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

prEN 13286-50, *Unbound and hydraulically bound mixtures —Part 50: Method for the manufacture of test specimens of hydraulically bound mixtures using Proctor equipment or vibrating table compaction.*

prEN 13286-51, *Unbound and hydraulically bound mixtures —Part 51: Method for the manufacture of test specimens of hydraulically bound mixtures using vibrating hammer compaction.*

prEN 13286-52, *Unbound and hydraulically bound mixtures —Part 52: Method for the manufacture of test specimens of hydraulically bound mixtures using vibrocompression.*

prEN 13286-53, *Unbound and hydraulically bound mixtures —Part 53: Method for the manufacture of test specimens of hydraulically bound mixtures using axial compression.*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

hydraulically bound mixture

mixture that hardens by hydraulic and/or pozzolanic and/or sulphatic and/or carbonatic reaction, which usually has a workability to suit compaction by rolling and which is generally used in bases, sub-bases and capping layers

3.2

indirect tensile strength

stress at failure of a cylindrical specimen subjected to a compression force applied on two opposite generatrix

3.3

slenderness ratio

ratio of the length to the diameter of a cylindrical specimen

4 Principle

A cylindrical specimen of hydraulically bound mixtures is subjected to a compression force applied along the two opposite generatrix until failure (see Figure 1). The indirect tensile strength is calculated from the failure load.