

Admixtures for concrete, mortar and grout - Test methods - Part 13: Reference masonry mortar for testing mortar admixtures

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 480-13:2015 sisaldab Euroopa standardi EN 480-13:2015 ingliskeelset teksti.	This Estonian standard EVS-EN 480-13:2015 consists of the English text of the European standard EN 480-13:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 03.06.2015.	Date of Availability of the European standard is 03.06.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Admixtures for concrete, mortar and grout - Test methods - Part
13: Reference masonry mortar for testing mortar admixtures**

Adjuvants pour béton, mortier et coulis - Méthodes d'essai -
Partie 13: Mortier à maçonner de référence pour les essais
menés sur les adjuvants de mortier

Zusatzmittel für Beton, Mörtel und Einpressmörtel -
Prüfverfahren - Teil 13: Referenz-Baumörtel für die Prüfung
von Zusatzmitteln für Mauerwerksmörtel

This European Standard was approved by CEN on 10 April 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Constituent materials	4
3.1 Cement.....	4
3.2 Sand	4
3.3 Mixing water	5
4 Reference masonry mortar	5
5 Production of reference mortar with standard consistence	5
5.1 Mix proportions.....	5
5.2 Mixing procedure	6
5.3 Mortar for test after standing.....	6
5.4 Mortar for test after extended mixing.....	6
6 Calculation of water reduction (air entraining/plasticizing admixtures).....	6
7 Test report	7

Foreword

This document (EN 480-13:2015) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2015, and conflicting national standards shall be withdrawn at the latest by December 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 480-13:2009+A1:2011.

This standard differs from EN 480-13:2009+A1:2011 as follows:

- a) Subclause 3.1 has been updated with regard to requirements for the specific surface of cement used.
- b) It has been revised editorially.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the constituent materials, the composition and the mixing procedure to produce a reference masonry mortar with a prescribed consistence for testing mortar admixtures as defined in EN 934-3. It also describes the determination of the water reduction of the test mix compared to the control mix.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement - Part 1: Determination of strength*

EN 196-2, *Method of testing cement - Part 2: Chemical analysis of cement*

EN 196-6, *Methods of testing cement - Part 6: Determination of fineness*

EN 197-1, *Cement - Part 1: Composition, specifications and conformity criteria for common cements*

EN 934-3, *Admixtures for concrete, mortar and grout — Part 3: Admixtures for masonry mortar — Definitions, requirements, conformity, marking and labelling*

EN 1008, *Mixing water for concrete - Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete*

EN 1015-4, *Methods of test for mortar for masonry - Part 4: Determination of consistence of fresh mortar (by plunger penetration)*

EN 1015-7, *Methods of test for mortar for masonry - Part 7: Determination of air content of fresh mortar*

3 Constituent materials

3.1 Cement

The reference masonry mortar shall be made with CEM I cement of strength class 42,5 or 52,5, conforming to EN 197-1.

The cement used shall have a C₃A content of 7 % to 11 % by mass calculated from chemical analysis according to EN 196-2 and a specific surface of (3 200 to 4 600) cm²/g determined according to EN 196-6.

3.2 Sand

A natural sand of normal density (relative density 2,5 – 2,8) shall be used. The size fractions of the sand shall comply with Table 1. The sand shall be used in an oven dry condition.