

## **Dentistry - Water-based cements - Part 1: Powder/liquid acid-base cements**

Dentistry - Water-based cements - Part 1:  
Powder/liquid acid-base cements

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

|  |   |
|--|---|
| <p>Käesolev Eesti standard EVS-EN ISO 9917-1:2007 sisaldab Euroopa standardi EN ISO 9917-1:2007 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 22.11.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p> | <p>This Estonian standard EVS-EN ISO 9917-1:2007 consists of the English text of the European standard EN ISO 9917-1:2007.</p> <p>This document is endorsed on 22.11.2007 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p> |
|--|---|

|   |   |
|---|---|
| <p><b>Käsitlusala:</b><br/>This part of ISO 9917 specifies requirements and test methods for powder/liquid acid-base dental cements intended for permanent cementation, lining and restoration. This part of ISO 9917 is applicable to both handmixed and capsulated cements for mechanical mixing. This part of ISO 9917 specifies limits for each of the properties according to whether the cement is intended for use as a luting agent, a base or liner or as a restorative material. This part of ISO 9917 is not intended to address resin-modified water-based cements.</p> | <p><b>Scope:</b><br/>This part of ISO 9917 specifies requirements and test methods for powder/liquid acid-base dental cements intended for permanent cementation, lining and restoration. This part of ISO 9917 is applicable to both handmixed and capsulated cements for mechanical mixing. This part of ISO 9917 specifies limits for each of the properties according to whether the cement is intended for use as a luting agent, a base or liner or as a restorative material. This part of ISO 9917 is not intended to address resin-modified water-based cements.</p> |
|---|---|

ICS 11.060.10

Võtmesõnad:

EUROPEAN STANDARD

**EN ISO 9917-1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2007

ICS 11.060.10

Supersedes EN ISO 9917-1:2003

English Version

**Dentistry - Water-based cements - Part 1: Powder/liquid acid-base cements (ISO 9917-1:2007)**

Art dentaire - Ciments à base d'eau - Partie 1: Ciments acido-basiques liquides/en poudre (ISO 9917-1:2007)

Zahnheilkunde - Wasserhärtende Zemente - Teil 1: Zemente, die beim Vermischen von Pulver und Flüssigkeit über eine Säure-Base-Reaktion abbinden (ISO 9917-1:2007)

This European Standard was approved by CEN on 8 October 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**Contents**

Page

Foreword.....3

This document is a preview generated by EVS

## Foreword

This document (EN ISO 9917-1:2007) has been prepared by Technical Committee ISO/TC 106 "Dentistry" in collaboration with Technical Committee CEN/TC 55 "Dentistry" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2008, and conflicting national standards shall be withdrawn at the latest by April 2008.

This document supersedes EN ISO 9917-1:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 9917-1:2007 has been approved by CEN as a EN ISO 9917-1:2007 without any modification.

---

---

**Dentistry — Water-based cements —**

Part 1:

**Powder/liquid acid-base cements**

*Art dentaire — Ciments à base d'eau —*

*Partie 1: Ciments acido-basiques liquides/en poudre*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

|  |           |
|--|-----------|
| <b>Foreword</b> .....  | <b>iv</b> |
| <b>1 Scope</b> .....   | <b>1</b>  |
| <b>2 Normative references</b> .....  | <b>1</b>  |
| <b>3 Terms and definitions</b> .....   | <b>1</b>  |
| <b>4 Classification</b> .....  | <b>2</b>  |
| <b>5 Material</b> .....  | <b>2</b>  |
| <b>6 Preparation of test specimens</b> .....   | <b>3</b>  |
| <b>7 Sampling</b> .....  | <b>3</b>  |
| <b>8 Requirements</b> .....  | <b>3</b>  |
| <b>9 Packaging, marking and information to be supplied by manufacturer</b> .....                             | <b>4</b>  |
| <b>Annex A (normative) Determination of net setting time</b> .....   | <b>7</b>  |
| <b>Annex B (informative) Chemical composition and applications of dental cements</b> .....                   | <b>9</b>  |
| <b>Annex C (normative) Determination of film thickness (luting cements only)</b> .....                       | <b>10</b> |
| <b>Annex D (normative) Determination of compressive strength</b> .....                                       | <b>12</b> |
| <b>Annex E (normative) Determination of acid erosion</b> .....   | <b>14</b> |
| <b>Annex F (normative) Determination of optical properties (polyalkenoate restorative cements only) ....</b> | <b>17</b> |
| <b>Annex G (normative) Determination of acid-soluble arsenic and lead contents</b> .....                     | <b>20</b> |
| <b>Annex H (normative) Determination of radio-opacity</b> .....  | <b>21</b> |
| <b>Bibliography</b> .....  | <b>23</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9917-1 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 1, *Filling and restorative materials*.

This second edition cancels and replaces the first edition (ISO 9917-1:2003), of which it constitutes a minor revision.

The main purpose for modification of this part of ISO 9917 was to include a new test method for acid erosion, a new test and requirement for radio-opacity and to distinguish between the requirements for manufacturer's instructions for hand-mixed cements and those for capsulated cements.

Specific qualitative and quantitative requirements for freedom from biological hazard are not included in this part of ISO 9917, but it is recommended that, in assessing possible biological or toxicological hazards, reference should be made to ISO 7405 and ISO 10993-1.

A bibliography has been added to this document.

ISO 9917 consists of the following parts, under the general title *Dentistry — Water-based cements*:

- *Part 1: Powder/liquid acid-base cements*
- *Part 2: Light-activated cements*

# Dentistry — Water-based cements —

## Part 1: Powder/liquid acid-base cements

### 1 Scope

This part of ISO 9917 specifies requirements and test methods for powder/liquid acid-base dental cements intended for permanent cementation, lining and restoration. This part of ISO 9917 is applicable to both hand-mixed and capsulated cements for mechanical mixing. This part of ISO 9917 specifies limits for each of the properties according to whether the cement is intended for use as a luting agent, a base or liner or as a restorative material. This part of ISO 9917 is not intended to address resin-modified water-based cements.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2590, *General method for the determination of arsenic — Silver diethyldithiocarbamate photometric method*

ISO 3665:1996, *Photography — Intra-oral dental radiographic film — Specification*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 7491, *Dental materials — Determination of colour stability*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### **mixing time**

that part of the working time required in order to obtain a satisfactory mix of the components

#### 3.2

##### **working time**

period of time, measured from the start of mixing, during which it is possible to manipulate a dental material without an adverse effect on its properties

#### 3.3

##### **net setting time**

period of time, measured from the end of mixing, until the material has set according to the criteria and conditions specified in Annex A

**NOTE** For the purposes of this part of ISO 9917, in view of the wide variation in mixing times of cements, the net setting time is determined from the end of mixing.