Euronorm 2: Betoontarindite projekteerimine - Osa 1-4: Üldeeskirjad - Kergtäiteainega betoon

Eurocode 2: Design of concrete structures - Part 1-4: General rules - Lightweight aggregate concrete with closed structure



### **FESTI STANDARDI FESSÕNA**

### **NATIONAL FOREWORD**

Käesolev Eesti standard EVS-ENV 1992-1-4:1999 sisaldab Euroopa standardi ENV 1992-1-4:1994 ingliskeelset teksti.

This Estonian standard EVS-ENV 1992-1-4:1999 consists of the English text of the European standard ENV 1992-1-4:1994.

Standard on kinnitatud Eesti Standardikeskuse 22.11.1999 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

This standard is ratified with the order of Estonian Centre for Standardisation dated 22.11.1999 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on .

Date of Availability of the European standard text

Standard on kättesaadav Eesti standardiorganisatsioonist.

The standard is available from Estonian standardisation organisation.

ICS 91.080.40

Võtmesõnad: ehitised, ehitusnormid, kergbetoon, projekteerimiseeskirjad, sarrus,

Inglisekeelsed võtmesõnad: building codes, buildings, design rules, lightweight concrete, reinforcement,

#### Standardite reprodutseerimis- ja levitamisõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega: Aru 10 Tallinn 10317 Eesti; <a href="www.evs.ee">www.evs.ee</a>; Telefon: 605 5050; E-post: <a href="mailto:info@evs.ee">info@evs.ee</a>

## Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation: Aru str 10 Tallinn 10317 Estonia; <a href="www.evs.ee">www.evs.ee</a>; Phone: 605 5050; E-mail: <a href="mailto:info@evs.ee">info@evs.ee</a>

# PRÉNORME EUROPÉENNE

# **EUROPÄISCHE VORNORM**

October 1994

ICS 91.040.00; 91.100.30

**Descriptors:** 

buildings, concrete structure, computation, building codes, rules of calculation

Eriglish version

Eurocode 2: Design of concrete structures - Part 1-4: General rules - Lightweight aggregate concrete with closed structure

Eurocode 2: Calcul des structures en béton -Partie 1-4: Règles générales - Béton de granulats légers à structure fermée Eurocode 2: Plannung von Stahlbeton- und Spannbetontragwerken - Teil 1-4: Allgemeine Regeln - Leichtbeton mit geschlossenem Gefüge

This European Prestandard (ENV) was approved by CEN on 1993-06-25 as a prospective standard for provisional application. The period of validity of this ENV is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the ENV can be converted into an European Standard (EN).

CEN members are required to announce the existance of this ENV in the same way as for an EN and to make the ENV available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the ENV) until the final decision about the possible conversion of the ENV into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

# CEN

European Committee for Standardization Comité Européen de Normalisation Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

# **Contents**

		Page
2:	FOREWORD	4
1	INTRODUCTION	7
1.1	SCOPE	7
1.1.2	SCOPE OF PART 1-4 OF EUROCODE 2	7
	C.	
1.4	DEFINITIONS	7
1.4.2	SPECIAL TERMS USED IN PART 1-4 OF EUROCODE 2	7
1.7	SPECIAL SYMBOLS USED IN THIS PART 1-4 OF EUROCODE 2	7
1.7.2	LATIN UPPER CASE SYMBOLS	. 7
1.7.4	GREEK SYMBOLS	7
1.7.5	SUBSCRIPTS	8
2	BASIS OF DESIGN	8
2.5	ANALYSIS	8
2.5.5	DETERMINATION OF THE EFFECTS OF TIME DEPENDENT DEFORMA-	. 8
	TIONS OF CONCRETE	
2.5.5.1	General	8
3	MATERIAL PROPERTIES	8
3.1	CONCRETE	8
3.1.0	NOTATION	8
3.1.2	LIGHTWEIGHT AGGREGATE CONCRETE	8
3.1.2.1	Definitions	.8
3.1.2.3	Tensile strength	9
3.1.2.4	Strength classes of lightweight aggregate concrete	9
3.1.2.5	Deformation properties	10
4	SECTION AND MEMBER DESIGN	12
4.1	DURABILITY REQUIREMENTS	12
4.1.3	DESIGN	12
4.1.3.3	Concrete cover	12
4.2	DESIGN DATA	12
4.2.1	LIGHTWEIGHT AGGREGATE CONCRETE	12
4.2.1.2	Physical properties	12
4.2.1.3	Mechanical properties	12
4.2.3	PRESTRESSED CONCRETE	16
4.2.3.5	Design of members in prestressed concrete	16
4.3	ULTIMATE LIMIT STATES	16
4.3.2	SHEAR	16
4 3 2 3	Plements not requiring design shear reinforcement	16

4.3.4	PUNCHING	16
4.3.4.5	Shear resistance	16
4.3.5	ULTIMATE LIMIT STATES INDUCED BY STRUCTURAL DEFORMATION	16
4.3.5.2	(BUCKLING) Design procedures	
4.3.3.2	Design procedures	16
4.4	SERVICEABILITY LIMIT STATES	17
4.4.2	LIMIT STATES OF CRACKING	17
4.4.2.2	Minimum reinforcement areas	17
4.4.3	LIMIT STATES OF DEFORMATION	17
4.4.3.2	Cases where calculations may be omitted	17
5	DETAILING PROVISIONS	18
5.0	NOTATION	18
5.1	GENERAL	18
	50	
5.2	STEEL FOR REINFORCED CONCRETE	19
5.2.1	GENERAL DETAILING ARRANGEMENTS	19
5.2.1.2	Permissible curvatures	19
5.2.2	BOND	19
5.2.2.2	Ultimate bond stress	19
5.2.2.3	Basic anchorage length	19
	The anomorage rangem	19
5.2.3	ANCHORAGE	19
5.2.3.2	Anchorage methods	19
5.2.3.4	Required anchorage length	19
5.2.6	ADDITIONAL RULES FOR HIGH BOND BARS EXCEEDING 32 MM	19
	IN DIAMETER	
5.2.6.0	General	20
5.2.6.2	Bond	20
5.2.7	BUNDLED UTON DANG DANG	20
5.2.7.1	BUNDLED HIGH BOND BARS General	20
3.2.7.1	General	20
6	CONSTRUCTION AND WORKMANSHIP	20
	0,	
7	QUALITY CONTROL	20
APPENDIX 1:	ADDITIONAL PROVISIONS FOR THE DETERMINATION OF THE	20
	EFFECTS OF TIME-DEPENDENT DEFORMATION OF CONCRETE	
APPENDIX 2:	NON-LINEAR ANALYSIS	20
		20
APPENDIX 3:	SUPPLEMENTARY INFORMATION ON THE ULTIMATE LIMIT	20
	STATES INDUCED BY STRUCTURAL DEFORMATION	
	- -	
APPENDIX 4:	CHECKING DEFLECTIONS BY CALCULATION	20

# **Foreword**

#### OBJECTIVES OF THE EUROCODES

- (1) The "Structural Eurocodes" comprise a group of standards for the structural and geotechnical design of buildings and civil engineering works.
- (2) They cover execution and control only to the extent that is necessary to indicate the quality of the construction products, and the standard of the workmanship needed to comply with the assumptions of the design rules.
- (3) Until the necessary set of harmonized technical specifications for products and for the methods of testing their performance are available, some of the Structural Eurocodes cover some of these aspects in informative Annexes.

### BACKGROUND OF THE EUROCODE PROGREMME

- (4) The Commission of the European Communities (CEC) initiated the work of establishing a set of harmonized technical rules for the design of building and civil engineering works which would initially serve as an alternative to the different rules in force in the various Member States and would ultimately replace them. These technical rules became known as the "Structural Eurocodes".
- (5) In 1990, after consulting their respective Member States, the CEC transferred the work of further development, issue and updating of the Structural Eurocodes to CEN, and the EFTA Secretariat agreed to support the CEN work.
- (6) CEN Technical Committee CEN/TC250 is responsible for all Structural Eurocodes

# EUROCODE PROGRAMOE

(7) Work is in hand on the following Structural Eurocodes, each generally consisting of a number of parts:

EN 1991 Eurocode 1 Basis of design and actions on structures

EN 1992 Eurocode 2 Design of concrete structures

EN 1993 Eurocode 3 Design of steel structures

EN 1994 Eurocode 4 Design of composite steel and concrete structures

EN 1995 Eurocode 5 Design of timber structures

EN 1996 Eurocode 6 Design of masonry structures

EN 1997 Eurocode 7 Geotechnical design

EN 1998 Eurocode 8 Design provisions for earthquake resistance of structures

EN 1999 Eurocode 9 Design of aluminium alloy structures

(8) Separate sub-committees have been formed by CEN/TC250 for the various Eurocodes listed above.

- (9) This Part 1-4 of Eurocode 2 is being published as a European Prestandard (ENV) with an initial life of three years.
- (10) This Prestandard is intended for experimental application and for the submission of comments.
- (11) After approximately two years CEN members will be invited to submit formal comments to be taken into account in determining future actions.
- (12) Meanwhile feedback and comments on this Prestandard should be sent to the Secretariat of CEN/TC250/SC2 at the following address:

Deutsches Institut für Normung e.V. (DIN)
Burggrafenstrasse 6
D - 10787 Berlin
phone: (+49) 30 - 26 01 - 25 01
fax: (+49) 30 - 26 01 - 12 31

or to your national standards organization.

### NATIONAL APPLICATION DOCUMENTS (NAD'S)

- (13) In view of the responsibilities of authorities in member countries for safety, health and other matters covered by the essential requirements of the Construction Products Directive (CPD), certain safety elements in this ENV have been assigned indicative values which are identified by [ ] ("boxed values"). The authorities in each member country are expected to assign definitive values to these safety elements.
- (14) Some of the supporting European or International standards may not be available by the time this Prestandard is issued. It is therefore anticipated that a National Application Document (NAD) giving definitive values for safety elements, referencing compatible supporting standards and providing national guidance on the application of this Prestandard, will be issued by each member country or its Standards Organization.
- (15) It is intended that this Prestandard is used in conjunction with the NAD valid in the country where the building or civil engineering works is located.

### MATTERS SPECIFIC TO THIS PRESTANDARD

- (16) The scope of Eurocode 2 is defined in 1.1.1 of ENV 1992-1-1 and the scope of this Part of Eurocode 2 is defined in 1.1.2. Additional Parts of Eurocode 2 which are planned are indicated in 1.1.3 of ENV 1992-1-1; these will cover additional technologies or applications, and will complement and supplement this Part.
- (17) In using this Prestandard in practice, particular regard should be paid to the underlying assumptions and conditions given in 1.3 of ENV 1992-1-1.
- (18) The seven chapters of this Prestandard are complemented by four Appendices which have the same normative status as the chapters to which they relate. These Appendices have been introduced by moving some of the more detailed Principles/Application Rules, which are needed in particular cases, out of the main part of the text to aid its clarity.

- (19) As indicated in paragraph (14) of this Foreword, reference should be made to National Application Documents which will give details of compatible supporting standards to be used. For this Part of Eurocode 2, particular attention is drawn to the approved Prestandard ENV 206 (Concrete performance, production, placing and compliance criteria), and the durability requirements given in 4.1 of this Prestandard.
- (20) The provisions of this Prestandard are based substantially on the 1978 edition of the CEB Model Code and other more recent CEB and FIP documents.
- (21) In developing this Prestandard, background documents have been prepared, which give commentaries on and justifications for some of the provisions in this Prestandard.

For ENV 1992-1-4, the following additional sub-clauses apply:

- (22) This Part 1-4 of Eurocode 2 complements ENV 1992-1-1 for the particular aspects of lightweight aggregate concrete with closed structure.
- (23) The framework and structure of this Part 1-4 correspond to ENV 1992-1-1. However, Part 1-4 contains Principles and Application Rules which are specific to structures made with lightweight aggregate concrete with closed structure.
- (24) Where a particular sub-clause of ENV 1992-1-1 is not mentioned in this ENV 1992-1-4, that sub-clause of ENV 1992-1-1 applies as far as deemed appropriate in each case.

Some Principles and Application Rules of ENV 1992-1-1 are modified or replaced in this Part, in which case they are superseded.

Where a Principle or Application Rule in ENV 1992-1-1 is modified or replaced, the new number is identified by the addition of 100 to the original number. Where a new Principle or Application Rule is added, it is identified by a number which follows the last number of ENV 1992-1-1 with 100 added to it.

A subject not covered by ENV 1992-1-1 is introduced in this Part by a new sub-clause. The sub-clause number for this follows the most appropriate clause number in ENV 1992-1-1.

(25) The numbering of equations, figures, footnotes and tables in this Part follow the same principles as the clause numbering in (24) above.

### 1 INTRODUCTION

This clause of ENV 1992-1-1 is applicable except as follows:

#### 1.1 SCOPE

### 1.1.2 SCOPE OF PART 1-4 OF EUROCODE 2

Addition after Principle P(5):

Part 1-4 of Eurocode 2 gives a general basis for the design of buildings and civil engineering works in reinforced and prestressed concrete made with lightweigth aggregate concrete with closed structure as defined in ENV 206.

For plain concrete structures made with lightweight aggregate concrete with closed structure, Part 1-6 of ENV 1992 and this Part 1-4 shall be applied analogously.

- P(107) All clauses of ENV 1992-1-1 are generally applicable, unless they are substituted by special clauses of this Part 1-4.
- P(108) This Part 1-4 applies to all concretes with closed structure made with natural or artificial mineral lightweight aggregates, unless reliable experience indicates that provisions different from those given can be adopted safely.
  - (109) This Part 1-4 does not apply to aerated concrete either autoclaved or normally cured nor to lightweight aggregate concrete with open structure.

### 1.4 DEFINITIONS

# 1.4.2 SPECIAL TERMS USED IN PART 1-4 OF EUROCODE 2

Addition after Principle P(2):

- P(103) Lightweight aggregate concrete: concrete having a closed structure 1) and an oven-dry density of not more than 2000 kg/m<sup>3</sup> consisting of or containing a proportion of artificial or natural lightweight aggregates having a particle density of less than 2000 kg/m<sup>3</sup>.
- 1.7 SPECIAL SYMBOLS USED IN THIS PART 1-4 OF EUROCODE 2

## 1.7.2 LATIN UPPER CASE SYMBOLS

Addition:

LC The strength classes of lightweight aggregate concrete are preceded by the symbol LC.

#### 1.7.4 GREEK SYMBOLS

Addition:

 $\eta_{\rm E}$ ,  $\eta_1$ ,  $\eta_2$ ,  $\eta_3$ ,  $\eta_4$ : conversion coefficient or ratio.

<sup>1)</sup> according to ENV 206, 5.2, so made and compacted as to retain no appreciable amount of entrapped air other than entrained air.